

Transformed.

ISO

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION

**ISO RECOMMENDATION
R 1868**

CARBON BLACK FOR USE IN THE RUBBER INDUSTRY

SPECIFICATION LIMITS FOR LOSS ON HEATING

1st EDITION

November 1970

COPYRIGHT RESERVED

The copyright of ISO Recommendations and ISO Standards belongs to ISO Member Bodies. Reproduction of these documents, in any country, may be authorized therefore only by the national standards organization of that country, being a member of ISO.

For each individual country the only valid standard is the national standard of that country.

Printed in Switzerland

Also issued in French and Russian. Copies to be obtained through the national standards organizations.

BRIEF HISTORY

The ISO Recommendation R 1868, *Carbon black for use in the rubber industry – Specification limits for loss on heating*, was drawn up by Technical Committee ISO/TC 45, *Rubber*, the Secretariat of which is held by the British Standards Institution (BSI).

Work on this question led to the adoption of Draft ISO Recommendation No. 1868, which was circulated to all the ISO Member Bodies for enquiry in June 1969. It was approved, subject to a few modifications of an editorial nature, by the following Member Bodies :

Australia	Iran	Spain
Austria	Israel	Sweden
Brazil	Japan	Switzerland
Canada	Netherlands	Thailand
Czechoslovakia	New Zealand	Turkey
France	Peru	U.A.R.
Germany	Poland	United Kingdom
Greece	Portugal	U.S.A.
Hungary	Romania	U.S.S.R.
India	South Africa, Rep. of	

No Member Body opposed the approval of the Draft.

This Draft ISO Recommendation was then submitted by correspondence to the ISO Council, which decided to accept it as an ISO RECOMMENDATION.

CARBON BLACK FOR USE IN THE RUBBER INDUSTRY

SPECIFICATION LIMITS FOR LOSS ON HEATING

1. SCOPE

This ISO Recommendation specifies the maximum limits for loss on heating at 105 °C of carbon black for use in the rubber industry, shipped in bags or in bulk.

2. SPECIFICATION LIMITS

The maximum permitted loss on heating of carbon black for use in the rubber industry, shipped in bags or in bulk, is as follows :

Type* of carbon black	Maximum heating loss of carbon black, %	
	shipped in bags	shipped in bulk
SAF	3.0	1.0
ISAF-HS, ISAF-HM, ISAF-LM, ISAF-LS	2.5	1.0
N285	2.5	1.0
CF, SCF, ECF	2.5	1.0
EPC, MPC	3.0	1.0
SPF, HAF-HS, HAF, HAF-LS, HAF-LS-SC	2.5	1.0
FF	2.0	1.0
FEF-HS, FEF, FEF-LS, APF	1.5	1.0
GPF, HMF, SRF-HS (MPF), SRF-HM, SRF-LM	1.0	1.0
FT, MT	1.0	1.0

3. SAMPLING

Samples should be taken immediately after delivery to the purchaser; any further increase in moisture is not the responsibility of the supplier.

Sampling should be carried out in accordance with one of the following ISO Recommendations :

ISO/R 1124, *Sampling bulk shipments of carbon black for use in the rubber industry*;

ISO/R 1310, *Carbon black for use in the rubber industry – Sampling packaged shipments*.

4. TEST PROCEDURE

Test procedure should be in accordance with ISO Recommendation R 1126, *Determination of loss on heating of carbon black for use in the rubber industry*.

* This temporary nomenclature will be replaced ultimately by the ISO nomenclature, at present under study.

STANDARDSISO.COM : Click to view the full PDF of ISO/R 1868:1970

ISO

ORGANISATION INTERNATIONALE DE NORMALISATION

RECOMMANDATION ISO R 1868

NOIR DE CARBONE DESTINÉ À L'INDUSTRIE DES ÉLASTOMÈRES

SPÉCIFICATIONS POUR LA PERTE À LA CHALEUR

1^{ère} ÉDITION

Novembre 1970

REPRODUCTION INTERDITE

Le droit de reproduction des Recommandations ISO et des Normes ISO est la propriété des Comités Membres de l'ISO. En conséquence, dans chaque pays, la reproduction de ces documents ne peut être autorisée que par l'organisation nationale de normalisation de ce pays, membre de l'ISO.

Seules les normes nationales sont valables dans leurs pays respectifs.

Imprimé en Suisse

Ce document est également édité en anglais et en russe. Il peut être obtenu auprès des organisations nationales de normalisation.

HISTORIQUE

La Recommandation ISO/R 1868, *Noir de carbone destiné à l'industrie des élastomères - Spécifications pour la perte à la chaleur*, a été élaborée par le Comité Technique ISO/TC 45, *Caoutchouc*, dont le Secrétariat est assuré par la British Standards Institution (BSI).

Les travaux relatifs à cette question aboutirent à l'adoption du Projet de Recommandation ISO N° 1868 qui fut soumis, en juin 1969, à l'enquête de tous les Comités Membres de l'ISO. Il fut approuvé, sous réserve de quelques modifications d'ordre rédactionnel, par les Comités Membres suivants :

Afrique du Sud, Rép. d'	Inde	Roumanie
Allemagne	Iran	Royaume-Uni
Australie	Israël	Suède
Autriche	Japon	Suisse
Brésil	Nouvelle-Zélande	Tchécoslovaquie
Canada	Pays-Bas	Thaïlande
Espagne	Pérou	Turquie
France	Pologne	U.R.S.S.
Grèce	Portugal	U.S.A.
Hongrie	R.A.U.	

Aucun Comité Membre ne se déclara opposé à l'approbation du Projet.

Ce Projet de Recommandation ISO fut alors soumis par correspondance au Conseil de l'ISO, qui décida de l'accepter comme RECOMMANDATION ISO.