

Transformed

ISO

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION

**ISO RECOMMENDATION
R 2144**

PAPER AND BOARD
DETERMINATION OF ASH

1st EDITION

November 1971

COPYRIGHT RESERVED

The copyright of ISO Recommendations and ISO Standards belongs to ISO Member Bodies. Reproduction of these documents, in any country, may be authorized therefore only by the national standards organization of that country, being a member of ISO.

For each individual country the only valid standard is the national standard of that country.

Printed in Switzerland

Also issued in French and Russian. Copies to be obtained through the national standards organizations.

STANDARDSISO.COM : Click to view the full PDF of ISO/R 2144:1971

BRIEF HISTORY

The ISO Recommendation R 2144, *Paper and board – Determination of ash*, was drawn up by Technical Committee ISO/TC 6, *Paper, board and pulps*, the Secretariat of which is held by the Association Française de Normalisation (AFNOR).

Work on this question led to the adoption of Draft ISO Recommendation No. 2144, which was circulated to all the ISO Member Bodies for enquiry in October 1970.

The Draft was approved, subject to a few modifications of an editorial nature, by the following Member Bodies :

Australia	Korea, Rep. of	Sweden
Austria	Netherlands	Switzerland
Czechoslovakia	New Zealand	Thailand
Germany	Norway	Turkey
India	Poland	U.A.R.
Iran	Portugal	United Kingdom
Ireland	Romania	U.S.A.
Israel	South Africa, Rep. of	U.S.S.R.
Japan	Spain	

The following Member Bodies opposed the approval of the Draft :

Belgium
France

This Draft ISO Recommendation was then submitted by correspondence to the ISO Council, which decided to accept it as an ISO RECOMMENDATION.

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO/R 2144:1971

PAPER AND BOARD

DETERMINATION OF ASH

1. SCOPE

This ISO Recommendation describes the apparatus and procedure for the determination of ash of paper and board.

2. DEFINITION

Ash content. The amount of residue of a material left after incineration determined and expressed according to the procedure given in this ISO Recommendation.

3. APPARATUS

3.1 *Crucibles*, complete with well-fitting lids, and made from materials such as platinum, fused alumina, porcelain or silica which do not change in mass under ignition conditions.

NOTE. — As platinum reacts at high temperatures with barium carbonate and zinc compounds, the use of platinum crucibles should be avoided when it is suspected that these materials are present in the sample.

3.2 *Balance*, with overall accuracy of 0.1 mg.

3.3 *Electric muffle furnace*, having an operating temperature of 900 ± 25 °C. A gas-fired muffle or a gas burner may be used provided it is capable of giving a similar temperature.

3.4 *Desiccator*.

4. SAMPLING

Sampling should be carried out in accordance with the procedure given in ISO Recommendation R 186, *Method of sampling paper and board for testing*. *

5. PREPARATION OF TEST PIECE

The test piece should consist of a number of small portions, of total mass not less than 1 g, or sufficient to give an ash of not less than 10 mg; they should be taken from various parts of the sample in such a manner as to be thoroughly representative of it.

In the case of ashless paper or board where the mineral content is extremely low, sufficient paper or board should be taken to give an ash of not less than 2 mg.

It is not necessary to condition the test piece, unless the result is required on an air-dry basis, in which case conditioning should be carried out in accordance with ISO Recommendation R 187, *Method for the conditioning of paper and board test samples*.

Since the result is normally required in terms of the moisture-free condition, however, it is recommended that a test for moisture content be carried out independently according to ISO Recommendation R 287, *Method for the determination of moisture content of paper (oven-drying method)*, on a separate portion of the sample weighed out at the same time. The result should be used to convert the ash content determined on the air-dry sample to the moisture-free (oven-dry) basis. Alternatively, the determination may be carried out on the oven-dried paper or board by drying the test piece to constant mass between 103 and 105 °C and weighing to the nearest 0.1 mg; this may be done with sufficient accuracy for the purpose in the ignited and weighed crucible used for ashing the paper or board (if the lid is sufficiently well-fitting).

6. PROCEDURE

Ignite the crucible and lid, cool in the desiccator and weigh to the nearest 0.1 mg; then weigh the test piece to the nearest 0.1 mg in the crucible. Ignite the crucible and contents, taking care to cover the crucible during the early stages of ignition to avoid loss of small particles. Start the ignition at a low temperature and raise it gradually to 900 ± 25 °C* as the volatile matter is driven off. With an electric muffle furnace this can be accomplished by placing the crucible at the entrance for a few minutes until all volatile matter has been evolved, after which the crucible lid may be carefully removed and put to one side, and the door closed. An ample access of air is necessary because, for example, where barium sulphate is present this could easily be reduced to the sulphite in the presence of carbonaceous matter.

Allow combustion to continue to completion, a condition indicated by the absence of black particles in the ash. Great care is necessary at all stages to protect the crucible and its contents from draughts of air which may cause serious losses. Stirring is not recommended at all, but in the case of large and heavy ashes, it may be necessary to turn the ash fragments over gently with a platinum wire to ensure that complete combustion has taken place. In such cases, extreme caution is necessary to avoid loss of ash.

When combustion is complete, replace the crucible lid and remove the crucible to the desiccator and cool for 45 minutes when porcelain or quartz ware is used, or for 15 minutes when using platinum; then weigh the crucible and contents to the nearest 0.1 mg and repeat the process of ignition and weighing until the mass is constant**.

NOTES

1. In the case of ashless papers or boards, it may be advisable to ignite successive small portions at low temperature in the same covered crucible in order to reduce the bulk and finally to ignite the whole to constant mass. A small platinum crucible should always be used in order to minimize any effect that slight errors in the mass of the crucible would contribute to the final result.
2. It may be desirable in certain instances to work at a lower temperature, for example when paper or board contains an appreciable quantity of calcium carbonate. In such circumstances a temperature of 575 ± 25 °C is recommended.

7. EXPRESSION OF RESULTS

The results of at least two determinations should be consistent to within 5 % of their mean. The ash content should be reported as a percentage of the mass of oven-dry paper calculated from the mean of these results.

The percentage of ash should be reported to three significant figures, except in the case of ashless paper for which two significant figures are sufficient.

* Temperatures should be raised at such a rate that the test piece does not burst into flame, which causes draught and loss of material.

** Two consecutive weighings should not differ by more than 0.5 mg.