

ISO

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION

ISO RECOMMENDATION R 390

SAMPLING AND INSPECTION OF ASBESTOS-CEMENT PRODUCTS

1st EDITION
November 1964

COPYRIGHT RESERVED

The copyright of ISO Recommendations and ISO Standards belongs to ISO Member Bodies. Reproduction of these documents, in any country, may be authorized therefore only by the national standards organization of that country, being a member of ISO.

For each individual country the only valid standard is the national standard of that country.

Printed in Switzerland

Also issued in French and Russian. Copies to be obtained through the national standards organizations.

BRIEF HISTORY

The ISO Recommendation R 390, *Sampling and inspection of asbestos-cement products*, was drawn up by Technical Committee ISO/TC 77, *Products in asbestos-cement*, the Secretariat of which is held by the Association Suisse de Normalisation (SNV).

Work on this question by the Technical Committee began in 1961 and led, in 1963, to the adoption of a Draft ISO Recommendation.

In December 1963, this Draft ISO Recommendation (No. 688) was circulated to all the ISO Member Bodies for enquiry. It was approved, subject to a few modifications of an editorial nature, by the following Member Bodies:

Australia	Israel	Republic of Korea
Austria	Italy	Republic of South Africa
Belgium	Japan	Romania
Brazil	Lebanon	Spain
Colombia	Morocco	Sweden
Czechoslovakia	Mexico	Switzerland
Denmark	Netherlands	Turkey
Finland	New Zealand	U.A.R.
France	Norway	United Kingdom
Germany	Peru	U.S.A.
Greece	Poland	U.S.S.R.
Hungary	Portugal	Venezuela
Ireland		Yugoslavia.

The Draft ISO Recommendation was then submitted by correspondence to the ISO Council, which decided, in November 1964, to accept it as an ISO RECOMMENDATION.

For the practical application of ISO Recommendation R 390, see the "Guide to the use of the Recommendation concerning sampling and inspection of asbestos-cement products", currently under preparation.

CONTENTS

	Pages
1. Scope	4
2. Terminology	4
3. Division of a consignment into inspection lots	4
3.1 Homogeneous consignments	4
3.2 Non-homogeneous consignments	4
4. Sampling	4
5. Inspection	5
6. Determination of acceptability of inspection lots	5
6.1 Inspection by attributes	5
6.2 Inspection by variables	6
Appendix	7

SAMPLING AND INSPECTION OF ASBESTOS-CEMENT PRODUCTS

1. SCOPE

This Recommendation defines certain rules for batching, sampling, inspection and acceptance/rejection of asbestos-cement products.

The purpose of the Recommendation is to provide a uniform method to be used in determining whether supplies of asbestos-cement goods should be accepted as conforming to the relevant Recommendation requirements for such products.

It provides for a double sampling plan for the method of inspection by attributes as well as for an alternative single sampling plan for the method of inspection by variables.

2. TERMINOLOGY

Definitions of the various expressions used in this Recommendation are given in the Appendix.

3. DIVISION OF A CONSIGNMENT INTO INSPECTION LOTS

3.1 Homogeneous consignments

3.1.1 Any homogeneous consignment (or sub-consignment — 3.2) should be divided by the manufacturer into inspection lots, the maximum size of which is given in the relevant Recommendation.

3.1.2 Any fraction of a consignment remaining after taking out the highest possible number of maximum inspection lots and any homogeneous consignment (or sub-consignment) smaller than the maximum lot size, form an inspection lot if larger than the minimum lot size given in the relevant Recommendation.

3.1.3 Consignments or fractions of consignments smaller than the minimum lot size given in the relevant Recommendation are not submitted to sampling and testing.

3.2 Non-homogeneous consignments

Any consignment which is known to be or is expected to be non-homogeneous as regards any of the properties to be tested by sampling should be divided by the manufacturer into assumed homogeneous sub-consignments prior to the division into inspection lots as per 3.1.

4. SAMPLING

4.1 From each inspection lot (3.1.1 and 3.1.2) the purchaser may draw a sample, the size of which is indicated in table 1 (4.2 and 4.3).

4.2 The entry to table 1 is the number of units of product in the inspection lot (column 1), the sample size being indicated in column 2.

- 4.3 For products where all units undergo a compulsory non-destructive test during the manufacture,¹ the reduced sample size obtained by entering table 1 at column 7 may be applied.
- 4.4 The possibility mentioned in 4.3 is also available when the manufacturer guarantees or has his production guaranteed by an independent control organisation.²
- 4.5 When test pieces are cut from the units of the sample, the cutting is carried out by the manufacturer in the presence of the purchaser.
- 4.6 When the relevant Recommendation calls for more than one property to be tested, the sample size should be appropriately multiplied so as to secure for each test a number of test pieces equal to the sample size (4.2 and 4.3). From one unit of a sample one test piece only should be cut for a particular test, but for different tests the necessary test pieces may be cut from the same unit of the sample.

5. INSPECTION

- 5.1 Each unit of the sample should be tested as specified in the relevant Recommendation.
- 5.2 The test results should be evaluated either through the method of inspection by attributes (5.4 and 6.1) or through the method of inspection by variables (5.5 and 6.2).
- 5.3 The method of inspection by attributes should normally be employed. However, by agreement prior to the drawing of the samples (4.1), the method of inspection by variables, if applicable, may be employed.
- 5.4 When the method of inspection by attributes is employed, the number of non-conforming units in the sample should be deduced from the test results and the acceptability of the inspection lot determined as prescribed in 6.1.
- 5.5 When the method of inspection by variables is employed, the test results shall be recorded so as to retain the order in which they are made and the acceptability of the inspection lot determined as prescribed in 6.2.

6. DETERMINATION OF ACCEPTABILITY OF INSPECTION LOTS

6.1 Inspection by attributes

- 6.1.1 When the number of non-conforming units found in the sample is equal to or less than the acceptance number Ac_1 indicated in column 3 of table 1, the inspection lot from which the sample was drawn should be considered acceptable.
- 6.1.2 When the number of non-conforming units found in the sample is equal to or greater than the rejection number Re_1 indicated in column 4 of table 1, this may justify rejection of the inspection lot.
- 6.1.3 When the number of non-conforming units found in the sample lies between the acceptance number and the rejection number (columns 3 and 4 of table 1), a second sample of the same size as the initial sample (4.2, 4.3 and 4.4) should be drawn and examined.
- 6.1.4 The second sample should be inspected as indicated in 4.5, 4.6 and 5.4.
- 6.1.5 The number of non-conforming units found in the initial and in the second samples should be totalled.

¹ Such as the water-tightness test for the pipes.

² For example, use of statistical quality control methods in the works.

- 6.1.6** If the total number of non-conforming units is equal to or less than the acceptance number Ac_2 indicated in column 5 of table 1, the inspection lot should be considered acceptable.
- 6.1.7** If the total number of non-conforming units is equal to or greater than the second rejection number Re_2 indicated in column 6 of table 1, this may justify rejection of the inspection lot.
- 6.1.8** When the relevant Recommendation calls for more than one property to be tested, the second sample taken (6.1.3) should only be inspected in accordance with those tests which at the inspection of the initial sample gave numbers of non-conforming units between the acceptance number Ac_1 and the rejection number Re_1 .

Table 1

1 Size of inspection lot	2 Sample size	3		4		5		6		7		8	
		Initial sample		Initial + second samples		Size of inspection lot for products tested during manufacture		Inspection by variables					
		Acceptance number Ac_1	Rejection number Re_1	Acceptance number Ac_2	Rejection number Re_2			Acceptability criterion ³ k					
- 100	3	0	2	1	2	- 200			0.29				
101- 200	4	0	2	1	2	201- 400			0.34				
201- 400	5	0	2	1	2	401- 800			0.37				
401- 800	7	0	2	1	2	801- 1500			0.40				
801- 1500	10	0	2	2	3	1501- 3000			0.50				
1501- 3000	15	0	3	3	4	3001- 8000			0.51				
3001- 8000	25	1	4	5	6	8001-20000			0.52				
8001-20000	35	2	5	7	8	-			0.53				

6.2 Inspection by variables

- (a) divide the readings in the order made into groups of 5, except when the sample size is 3, 4, 5 or 7, in which cases the group size is the same as the sample size;
- (b) for each group the range R is computed;
- (c) of the group ranges R , the average range \bar{R} is computed;
- (d) compute the sample mean \bar{X} by dividing the sum of measurements by the sample size;
- (e) derive from table 1 (column 8) the acceptability criterion k ;
- (f) compute the acceptability limit AL and determine the acceptability by means of table 2.

Table 2

Relevant Recommendation prescribing	$AL =$	Acceptable if	Rejection justified if
Lower specified limit, L	$L + k \cdot \bar{R}$	$\bar{X} \geq AL$	$\bar{X} < AL$
Upper specified limit, U	$U - k \cdot \bar{R}$	$\bar{X} \leq AL$	$\bar{X} > AL$

³ In applying ISO Recommendation R 390 to the simultaneous inspection of the two limits of a given property, see the "Guide to the use of the Recommendation concerning sampling and inspection of asbestos-cement products", currently under preparation.