

ISO

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION

ISO RECOMMENDATION R 393

ASBESTOS-CEMENT CORRUGATED SHEETS FOR ROOFING AND CLADDING

1st EDITION
November 1964

COPYRIGHT RESERVED

The copyright of ISO Recommendations and ISO Standards belongs to ISO Member Bodies. Reproduction of these documents, in any country, may be authorized therefore only by the national standards organization of that country, being a member of ISO.

For each individual country the only valid standard is the national standard of that country.

Printed in Switzerland

Also issued in French and Russian. Copies to be obtained through the national standards organizations.

BRIEF HISTORY

The ISO Recommendation R 393, *Asbestos-cement corrugated sheets for roofing and cladding*, was drawn up by Technical Committee ISO/TC 77, *Products in asbestos-cement*, the Secretariat of which is held by the Association Suisse de Normalisation (SNV).

Work on this question by the Technical Committee began in 1956 and led, in 1963, to the adoption of a Draft ISO Recommendation.

In December 1963, this Draft ISO Recommendation (No. 691) was circulated to all the ISO Member Bodies for enquiry. It was approved, subject to a few modifications of an editorial nature, by the following Member Bodies:

Australia	Ireland	Republic of South Africa
Austria	Israel	Romania
Belgium	Italy	Spain
Colombia	Lebanon	Sweden
Czechoslovakia	Morocco	Switzerland
Denmark	Netherlands	Turkey
Finland	New Zealand	U.A.R.
France	Norway	United Kingdom
Germany	Poland	U.S.S.R.
Greece	Portugal	Venezuela
Hungary	Republic of Korea	Yugoslavia.

Four Member Bodies opposed the approval of the Draft:

Brazil, Japan, Mexico, Peru.

The Draft ISO Recommendation was then submitted by correspondence to the ISO Council, which decided, in November 1964, to accept it as an ISO RECOMMENDATION.

CONTENTS

	Pages
1. Scope	4
2. Corrugated sheets	4
2.1 Composition	4
2.2 Classification	4
2.2.1 Geometrical classification	4
2.2.2 Mechanical classification	5
2.2.3 Choice of the classifications	5
2.3 General appearance and finish	5
2.4 Characteristics	6
2.4.1 Geometrical characteristics	6
2.4.1.1 Profiles and sizes	6
2.4.1.2 Length, width and coverage	6
2.4.1.3 Thicknesses	6
2.4.1.4 Tolerances on the nominal dimensions	6
2.4.2 Mechanical characteristics	6
2.4.3 Physical characteristics	6
2.4.3.1 Impermeability	6
2.4.3.2 Frost cracking	6
2.5 Tests	7
2.5.1 Measurement of the thicknesses	7
2.5.1.1 Checking of the minimum thickness	7
2.5.1.2 Measurement of the thicknesses in the broken sections	7
2.5.2 Bending tests	7
2.5.2.1 Unit bending stress	8
2.5.2.2 Classifying index	8
2.5.3 Impermeability test	9
2.5.4 Frost cracking test	9
2.6 Marking	9
3. Fittings	9
3.1 Composition	9
3.2 General appearance and finish	9
3.3 Characteristics	9
3.3.1 Geometrical characteristics	9
3.3.1.1 Shapes	9
3.3.1.2 Length, width and coverage	10
3.3.1.3 Thickness	10
3.3.1.4 Tolerances on the nominal dimensions	10
3.3.2 Physical characteristics	10
3.3.2.1 Impermeability	10
3.3.2.2 Frost cracking	10
3.4 Marking	10
4. Sampling, inspection and acceptance	10
4.1 Inspection of each item of the consignment	10
4.2 Inspection by sampling	11
Appendix A — Testing	13
Appendix B — Extracts of ISO Recommendation R 390 “ Sampling and Inspection of Asbestos-Cement Products ”	14

ASBESTOS-CEMENT CORRUGATED SHEETS FOR ROOFING AND CLADDING¹

1. SCOPE

This Recommendation applies to straight or curved asbestos-cement corrugated sheets and fittings without any metallic reinforcing media, to be used for roofing and cladding.

It defines certain conditions of manufacture, dimensions and acceptance tests for these products.

2. CORRUGATED SHEETS

2.1 Composition

The sheets are made from a close and homogeneous mixture essentially consisting of a suitable inorganic hydraulic binder, asbestos fibre and water, excluding any materials liable to cause ultimate deterioration in the quality of the sheets.²

The sheets may be left in their natural colour or colouring matter may be added in the composition; they may also receive adherent coloured or uncoloured coatings on their surfaces.

2.2 Classification

The sheets are classified both according to the height of their corrugations and according to their load bearing capacity.

2.2.1 Geometrical classification

(Classification according to the height of the corrugations)

DEFINITION — The height h of the corrugations is the height measured from the valley of the corrugation up to the crown of the next corrugation (see Figure 1).

This dimension includes one thickness only.



Fig. 1

¹ Asymmetrical section corrugated sheets are covered by ISO Recommendation R 394.

² This Recommendation also applies to autoclaved sheets when the binder is partially replaced by ground silica.

DESIGNATION OF THE CATEGORY

- (1) deep corrugations
height not less than 42 mm
- (2) medium corrugations
height less than 42 mm
and not less than 30 mm
- (3) shallow corrugations
height less than 30 mm
and not less than 15 mm.

2.2.2 Mechanical classification

(Classification according to the load bearing capacity)

DEFINITION — The sheets are classified according to a classifying index C_m which takes into account the minimum unit bending stress value of 160 kgf/cm², that defines the intrinsic quality of the asbestos-cement material (2.4.2), and the nominal bending section modulus W_n corresponding to the theoretical profile (2.4.1.1) and to the nominal thickness (2.4.1.3) of the sheet.

The classifying index C_m represents a minimum acceptable load bearing capacity related to a width of one metre.

DESIGNATION OF THE CLASS

- (1) class 150 C_m : 150 kgf/m
- (2) class 212 C_m : 212 kgf/m
- (3) class 300 C_m : 300 kgf/m
- (4) class 425 C_m : 425 kgf/m.

One lower class may be introduced into this classification; it has to be chosen from the same series of preferred numbers as the classes above.

2.2.3 Choice of the classifications

The national standards may prescribe one or other or both the above classifications on the condition that the minimum unit bending stress value of 160 kgf/cm² provided for in 2.4.2 is maintained.

- (a) In order to facilitate the interchangeability of the sheets and consequently to ensure the tightness of the roofs when matching sheets, a sheet should keep within the category of its geometrical profile irrespective of its minimum load bearing capacity.
- (b) It is not permissible to change the class according to the minimum acceptable load bearing capacity of a sheet as determined by 2.2.2, even if the verification of bearing capacities carried out according to 2.5.2.2 indicates an index corresponding to a higher class than the classifying index C_m for the sheet.

2.3 General appearance and finish

The sheets are elements the cross-section of which consists of approximately sinusoidal corrugations to make the sheet rigid. The surface intended to be exposed to the weather should be finished smooth.

The edges of the sheets should be square, straight and clean.

2.4 Characteristics

2.4.1 Geometrical characteristics

2.4.1.1 PROFILES AND SIZES

The profiles and sizes of the sheets should conform to those in the national standards of the producing country or, failing this, should be as specified in the manufacturers' catalogues.

2.4.1.2 LENGTH, WIDTH AND COVERAGE

These nominal dimensions should conform to those in the national standards of the producing country or, failing this, should be as specified in the manufacturers' catalogues.

2.4.1.3 THICKNESSES

The sheets are of two types

— A, sheets with a constant thickness

— B, sheets with a profile of regularly varying thickness.

The nominal thickness of the sheets of type A and the extreme nominal thicknesses of the sheets of type B should conform to those in the national standards of the producing country or, failing this, should be as specified in the manufacturers' catalogues.

The actual thickness measured according to 2.5.1.1 should at no point be less than 5.5 mm for the sheets of type A and 5.2 mm for the sheets of type B. For the sheets of the category "shallow corrugations" (2.2.1) the actual thickness should be not less than 3.5 and 3.2 mm respectively.

2.4.1.4 TOLERANCES ON THE NOMINAL DIMENSIONS

(a) on the length

Upper deviation: $+ 5$ mm

Lower deviation: $- 10$ mm.

(b) on the width

Upper deviation: $+ 10$ mm

Lower deviation: $- 5$ mm.

(c) on the thickness

Upper deviation: free

Lower deviation: $- 0.5$ mm.

2.4.2 Mechanical characteristics

Tested as provided for in 2.5.2 (compulsory test), the sheets should give a minimum unit bending stress of 160 kgf/cm².

2.4.3 Physical characteristics

2.4.3.1 IMPERMEABILITY

Tested as provided for in 2.5.3 (optional test), traces of moisture may appear on the lower surface of the sheets, but in no instance should there be any formation of drops of water.

2.4.3.2 FROST CRACKING

Tested as provided for in 2.5.4 (optional test), the sheets should not show signs of cracking or surface alteration.

2.5 Tests

The acceptance tests should be carried out at the manufacturer's works on sheets and test pieces cut off the sheets which the manufacturer guarantees to be sufficiently matured.

(a) Compulsory tests

1. Measurement of the thicknesses (method as defined in 2.5.1).
2. Bending test (method as defined in 2.5.2, number of tests as indicated in the extract of the table in Appendix B).

(b) Optional tests at purchaser's request

3. Impermeability test (method as defined in 2.5.3, number of tests as indicated in the extract of the table in Appendix B).
4. Frost cracking test (method as defined in 2.5.4, number of tests as indicated in the extract of the table in Appendix B).

2.5.1 Measurement of the thicknesses

The methods of assessing these measurements and the instruments used should be in accordance with the national standards of the producing country.

2.5.1.1 CHECKING OF THE MINIMUM THICKNESS

The actual thickness measured at any point should be not less than the minimum provided for in 2.4.1.3.

2.5.1.2 MEASUREMENT OF THE THICKNESSES IN THE BROKEN SECTIONS

The thickness is measured in the crown and valley of the corrugations. The actual average thickness is the arithmetical average of the measurements so obtained.³

2.5.2 Bending test

This test serves

- to determine the unit bending stress of the tested sheet,
- to verify the classifying index C_m according to the classification by the load bearing capacity.

The test is carried out on pieces cut off straight sheets with a minimum length of 1.22 m. The width of the test pieces corresponds to the total width of the sheet reduced at the edges by cutting along the axes of the outer valleys. Before testing, the test pieces should be immersed in water for 24 hours.




Fig. 2

The test piece should be placed on two transverse fixed rigid flat parallel supports 5 cm wide, leaving between them a clear span of 1.10 m. It should be loaded at mid-span by means of a self-aligning rigid flat beam 23 cm wide, parallel to the supports and loaded at mid-span.

³ This measurement also applies to sheets of type B. The thickness is not measured in the side of the corrugation, as it is in direct relation with the thicknesses measured in the crown and valley of the corrugations and may be deduced therefrom either by calculations or graphs.

Strips of felt or soft fibre not more than 1 cm thick are interposed between the test piece and the supports and under the beam by which the load is applied.

The speed of application of the load should be regulated so as to realize an increase of the unit stress of about 4 kgf/cm²s up to breaking point. ⁴

2.5.2.1 UNIT BENDING STRESS

The unit bending stress expressed in kilogrammes-force per square centimetre is given by the formula:

$$R_f = \frac{M}{W}$$

where

$$M = \frac{P l}{4}$$

W = bending section modulus in relation to the part of the test piece exposed to tension and determined from the theoretical profile given by the manufacturer and the actual average thicknesses measured at the broken section of the test piece according to 2.5.1.2, expressed in cubic centimetres

P = breaking load, expressed in kilogrammes-force

l = clear span between the supports, expressed in centimetres.

The unit bending stress R_f corresponding to the breaking load should be not less than 160 kgf/cm² (2.4.2).

The manufacturer should place at the disposal of the testing engineer tables or graphs which, in function of the distance between the supports, the thicknesses, the values of the corresponding W and the above mentioned figure R_f , indicate the minimum load to be applied corresponding to breaking point. ⁵

2.5.2.2 CLASSIFYING INDEX

When the sheets are classified according to their load bearing capacity expressed in kilogrammes-force for a width of one metre, the index C which is used to classify them is determined by the conventional formula:

$$C = \frac{P}{b} \text{ kgf/m}$$

where

P = breaking load, expressed in kilogrammes-force

b = width of the test piece, expressed in metres.

The index C determined by the test should be not less than the classifying index C_m of the sheets defined in 2.2.2.

⁴ When national standards provide for a constant speed of application of the load, it should be of about 10 kgf/s up to breaking point.

⁵ Manufacturers are invited to state in their catalogues
(a) the main figures of the various sections and the W value for each corrugation profile,
(b) the minimum load corresponding for each value of W to the application of 2.5.2.1.

2.5.3 Impermeability test

The impermeability should be tested on test pieces cut off the sheets in air with a relative humidity of over 70 per cent. A vertical transparent tube 30 cm long with a bore of 3.5 cm and with the lower end shaped to fit into the valley of a corrugation, is sealed to the middle of a test piece placed horizontally on a transparent container. The tube is filled with water, the level of which is maintained at a height of about 25 cm measured from the valley of the corrugation.

During the 24 hours of the test, traces of moisture may appear on the lower surface but in no instance should there be any formation of drops of water.

2.5.4 Frost cracking test

Test pieces cut off the sheets after immersion for 48 hours in water, are submitted to alternate freezing and de-freezing between temperatures of -20°C and $+20^{\circ}\text{C}$ (with a tolerance of $\pm 3^{\circ}\text{C}$). The size of the test pieces, the number of cycles and the duration of the test at the utmost temperatures should be in accordance with the national standards of the producing country.

The test is considered to be satisfactory if the test pieces after testing do not show signs of cracking or surface alteration.

2.6 Marking

The sheets should be marked legibly and indelibly so as to show:

- the origin of manufacture,
- the date of manufacture.

The method of marking should conform to that in the national standards of the producing country.

3. FITTINGS**3.1 Composition**

The fittings are of similar composition to the sheets (2.1).

3.2 General appearance and finish

The fittings should have straight and clean edges. They may have a lapped joint.

3.3 Characteristics**3.3.1 Geometrical characteristics****3.3.1.1 SHAPES**

The shapes of the fittings should conform to those in the national standards of the producing country or, failing this, should be as specified in the manufacturers' catalogues.

If requested, they should belong to the same type and category as the sheets with which they are to be used.

3.3.1.2 LENGTH, WIDTH AND COVERAGE

These nominal dimensions should conform to those in the national standards of the producing country or, failing this, should be as specified in the manufacturers' catalogues.

3.3.1.3 THICKNESS

The nominal thickness of the fittings should be not less than the corresponding thickness of the sheets with which they are to be used.

3.3.1.4 TOLERANCES ON THE NOMINAL DIMENSIONS*(a) on the length and width*

Upper deviation: + 10 mm

Lower deviation: — 10 mm.

(b) on the thickness

Upper deviation: free

Lower deviation: — 0.5 mm.

3.3.2 Physical characteristics**3.3.2.1 IMPERMEABILITY**

Tested as provided for in 2.5.3 (optional test), traces of moisture may appear on the lower surface of the fittings, but in no instance should there be any formation of drops of water.

3.3.2.2 FROST CRACKING

Tested as provided for in 2.5.4 (optional test), the fittings should not show signs of cracking or surface alteration.

3.4 Marking

The marking of the fittings should correspond to the marking of the sheets (2.6).

4. SAMPLING, INSPECTION AND ACCEPTANCE

Enquiries and orders should specify whether the consignment is to be delivered with or without acceptance tests. Failing this, it is presumed to be with acceptance tests if agreements on the date of the tests or the nature of the optional tests have been made between the manufacturer and the purchaser. Otherwise, the consignment is presumed to be without acceptance tests.

4.1 Inspection of each item of the consignment

4.1.1 The requirements concerning the geometrical classification⁶ (2.2.1), the general appearance and finish (2.3 — 3.2), the geometrical characteristics (2.4.1 — 3.3.1) and the marking (2.6 — 3.4) of the sheets and fittings may be verified on each item of the consignment.

4.1.2 The sheets and fittings which do not satisfy the requirements when submitted to inspection of each item of the consignment (4.1.1) may be rejected.

⁶ For the sheets only.

4.2 Inspection by sampling

4.2.1 The requirements concerning the mechanical classification ⁶ (2.2.2), the mechanical characteristics ⁶ (2.4.2) and the physical characteristics (2.4.3 — 3.3.2) of the sheets and fittings should be verified, if requested, by sampling.

4.2.2 The procedure in Recommendation R 390 applies for the sampling, inspection and acceptance. Each inspection lot should include only items of the same category and of the same class. The maximum and minimum inspection lots are agreed between the manufacturer and the purchaser; failing such an agreement these should be

- for length less or equal to 1.60 m: 8000 and 800 sheets respectively,
- for length exceeding 1.60 m: 3000 and 800 sheets respectively,
and 400 and 100 fittings respectively.

STANDARDSISO.COM : Click to view the full PDF of ISO/R 393:1964

⁶ For the sheets only.

STANDARDSISO.COM : Click to view the full PDF of ISO/R 393:1964