

ISO

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION

ISO RECOMMENDATION R 565

WOVEN WIRE CLOTH AND PERFORATED PLATES
IN TEST SIEVES
NOMINAL SIZES OF APERTURES

1st EDITION
April 1967

COPYRIGHT RESERVED

The copyright of ISO Recommendations and ISO Standards belongs to ISO Member Bodies. Reproduction of these documents, in any country, may be authorized therefore only by the national standards organization of that country, being a member of ISO.

For each individual country the only valid standard is the national standard of that country.

Printed in Switzerland

Also issued in French and Russian. Copies to be obtained through the national standards organizations.

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO/R 565:1967

BRIEF HISTORY

The ISO Recommendation R 565, *Woven Wire Cloth and Perforated Plates in Test Sieves – Nominal Sizes of Apertures*, was drawn up by Technical Committee ISO/TC 24, *Sieves, Sieving and other Sizing Methods*, the Secretariat of which is held by the Deutscher Normenausschuss (DNA).

Work on this question by the Technical Committee began in 1956 and led, in 1964, to the adoption of a Draft ISO Recommendation.

In April 1965, this Draft ISO Recommendation (No.805) was circulated to all the ISO Member Bodies for enquiry. It was approved, subject to a few modifications of an editorial nature, by the following Member Bodies:

Brazil	Ireland	U.A.R.
Canada	Israel	United Kingdom
Chile	Netherlands	U.S.A.
France	New Zealand	U.S.S.R.
Germany	Sweden	Yugoslavia
Hungary	Switzerland	
India	Turkey	

One Member Body opposed the approval of the Draft:

Italy

The Draft ISO Recommendation was then submitted by correspondence to the ISO Council, which decided, in April 1967, to accept it as an ISO RECOMMENDATION.

STANDARDSISO.COM : Click to view the full PDF of ISO/R 565:1967

WOVEN WIRE CLOTH AND PERFORATED PLATES IN TEST SIEVES

NOMINAL SIZES OF APERTURES

1. SCOPE

This ISO Recommendation gives the nominal sizes of apertures for woven wire cloth and perforated plates in test sieves.

2. TYPE OF SIEVING MEDIA IN TEST SIEVES

- 2.1 Woven wire cloth consists of wires woven to form nominally square apertures.
- 2.2 Perforated plates are metal plates with either square or circular holes in regular arrangement.

3. DESIGNATION

- 3.1 Woven wire cloth in test sieves is designated according to nominal size of the square aperture.
- 3.2 Perforated plates in test sieves are designated according to nominal size of the square aperture, or nominal diameter of the round aperture. In addition, the type of hole, *square* or *round*, should be stated.
- 3.3 Sizes below 1 mm are expressed in microns (μm)*; sizes of 1 mm and above, in millimetres (mm).

* 1000 μm = 1 mm

4. NOMINAL SIZES OF APERTURES

4.1 Principal sizes

TABLE 1

Woven wire cloth	Perforated plates	
	Nominal size of square hole	Nominal size of round hole
	mm	mm
125	125	125
90.0	90	90
63.0	63	63
45.0	45	45
31.5	31.5	31.5
22.4	22.4	22.4
16.0	16	16
11.2	11.2	11.2
8.00	8	8
5.6	5.6	5.6
4.00	4	4
2.8		2.8
2.00		2
1.4		1.4
1.00		1
μm		
710		
500		
355		
250		
180		
125		
90		
63		
45		

NOTE. — The nominal sizes listed above are selected from the R 20 series of preferred numbers. *

* ISO Recommendation R 3, *Preferred numbers — Series of preferred numbers.*