
**Destructive tests on welds in metallic
materials — Etchants for macroscopic
and microscopic examination**

*Essais destructifs des soudures sur matériaux métalliques — Réactifs
pour examens macroscopique et microscopique*

STANDARDSISO.COM : Click to view the full PDF of ISO/TR 16060:2003



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO/TR 16060:2003

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 General	1
4 Etchants for carbon steels and low-alloy steels	1
5 Etchants for stainless steels	1
6 Etchants for nickel and nickel alloys	2
7 Etchants for titanium and titanium alloys	2
8 Etchants for copper and copper alloys	2
9 Etchants for aluminium and aluminium alloys	2
10 Designation	2
Annex A (informative) Etchants for carbon steels and low-alloy steels	3
Annex B (informative) Etchants for stainless steels	10
Annex C (informative) Etchants for nickel and nickel alloys	16
Annex D (informative) Etchants for titanium and titanium alloys	18
Annex E (informative) Etchants for copper and copper alloys	20
Annex F (informative) Etchants for aluminium and aluminium alloys	22
Annex G (informative) List of etchants	27

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

In exceptional circumstances, when a technical committee has collected data of a different kind from that which is normally published as an International Standard ("state of the art", for example), it may decide by a simple majority vote of its participating members to publish a Technical Report. A Technical Report is entirely informative in nature and does not have to be reviewed until the data it provides are considered to be no longer valid or useful.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO/TR 16060 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 5, *Testing and inspection of welds*.

STANDARDSISO.COM : Click to view the full PDF of ISO/TR 16060:2003

Destructive tests on welds in metallic materials — Etchants for macroscopic and microscopic examination

1 Scope

This Technical Report gives a non-exhaustive list of etchants that can be used for the macroscopic and microscopic examination of welds in accordance with ISO 17639 for the following groups of materials:

- carbon steels and low-alloy steels;
- stainless steels;
- nickel and nickel alloys;
- titanium and titanium alloys;
- copper and copper alloys;
- aluminium and aluminium alloys.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 17639, *Destructive tests on welds in metallic materials — Macroscopic and microscopic examination of welds*

3 General

Where details of concentration or waters of crystallization of reagents are not defined in the annexes, Table 1 is applicable. These values should be confirmed by the suppliers of each etchant.

4 Etchants for carbon steels and low-alloy steels

The etchants for carbon and low alloyed steels are given in Annex A.

5 Etchants for stainless steels

The etchants for stainless steels are given in Annex B.

6 Etchants for nickel and nickel alloys

The etchants for nickel and nickel alloys are given in Annex C.

7 Etchants for titanium and titanium alloys

The etchants for titanium and titanium alloys are given in Annex D.

8 Etchants for copper and copper alloys

The etchants for copper and copper alloys are given in Annex E.

9 Etchants for aluminium and aluminium alloys

The etchants for aluminium and aluminium alloys are given in Annex F.

10 Designation

Etchants should be designated either by names or by numbers of tables in accordance with Annex G.

Table 1 — Characteristics of components

Components	Characteristics			Remarks
	Specific gravity g/cm ³	Concentration %	Hydrate	
HCl	1,18 1,16	35 to 38 31,5 to 33	—	
HF	1,13	40	—	
HNO ₃	1,42	69	—	
H ₂ SO ₄	1,84	98	—	
H ₂ O ₂	—	6 % W/V ^a	—	Usually 20 volumes (i.e. 20 volume available O ₂)
H ₃ PO ₄	1,70	85	—	
CH ₃ COOH	1,05	99,1	—	glacial
HF ₄	1,23	35	—	
C ₂ H ₂ O ₄	—	—	2	
FeCl ₃	—	—	6	
CuCl ₂	—	—	2	
MgCl ₂	—	—	6	
Fe(NO ₃) ₃	—	—	9	

^a W/V means weight by volume.

Annex A (informative)

Etchants for carbon steels and low-alloy steels

See Tables A.1 to A.13.

Table A.1 — Nital

Type of etchant: Macroscopic and microscopic etchant
Composition in volume and in order of mixing: 99 ml to 95 ml industrial methylated spirits* 1 ml to 5 ml nitric acid (HNO ₃) *Ethyl alcohol (C ₂ H ₅ OH), denatured with methyl alcohol (CH ₃ OH) Also methyl alcohol or isoamyl alcohol [(CH ₃) ₂ CH(CH ₂) ₂ OH]
Safe shelf life: Indefinite
Surface preparation: 600 grit or finer (macroetching ≈ 5 % of nitric acid) 3 μm diamond or finer (microetching ≈ 2 % of nitric acid)
Etching temperature: Ambient
Etching time: A few seconds — check by eye
Additional precautions/requirements: Usual precautions for handling and disposal of acids.
Comments: Can increase strength to 15 % for macroetching on ground surface — reveals ferrite boundaries — differentiates ferrite from martensite. Good general purpose etchant. Amyl alcohol is preferable for galvanized steel.

Table A.2 — Picral (4 %)

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 100 ml ethyl alcohol (C ₂ H ₅ OH) 4 g picric acid [C ₆ H ₂ OH(NO ₂) ₃] [+ wetting agent (sodium dodecyl benzene sulphate) (C ₁₈ H ₂₉ NaSO ₄) if required]
Safe shelf life: Indefinite
Surface preparation: 3 µm diamond or finer
Etching temperature: Ambient
Etching time: A few seconds — check by eye
Additional precautions/requirements: Usual precautions for handling and disposal of acids.
Comments: Little attack prior austenite boundaries — detects carbides — good resolution with fine pearlite, martensite, tempered martensite and bainitic structures.

Table A.3 — Picric acid solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 1 l saturated aqueous picric acid [C ₆ H ₂ OH(NO ₂) ₃] 10 ml wetting agent (sodium dodecyl benzene sulphate) (C ₁₈ H ₂₉ NaSO ₄)
Safe shelf life: Indefinite
Surface preparation: 3 µm diamond or finer
Etching temperature: 55 °C to 60 °C
Etching time: A few seconds — check by eye
Additional precautions/requirements: Usual precautions for handling and disposal of acids.
Comments: Reveals prior grain boundaries and segregation.

Table A.4 — Picral (15 %)

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 100 ml ethyl alcohol* (C ₂ H ₅ OH) 15 g picric acid [C ₆ H ₂ OH(NO ₂) ₃] *Also methyl alcohol (CH ₃ OH)
Safe shelf life: Indefinite
Surface preparation: 2 µm diamond or finer
Etching temperature: Ambient
Etching time: A few seconds to one minute — check by eye
Additional precautions/requirements: Usual precautions for handling and disposal of acids.
Comments: Reveals general structure. The composition given saturates the solution with picric acid.

Table A.5 — Hydrochloric picric acid solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 100 ml ethyl alcohol (C ₂ H ₅ OH) 1 ml hydrochloric acid (HCl) 4 g picric acid [C ₆ H ₂ OH(NO ₂) ₃]
Safe shelf life: Indefinite
Surface preparation: 3 µm diamond or finer
Etching temperature: Ambient
Etching time: 10 s to a few minutes
Additional precautions/requirements: Usual precautions for handling and disposal of acids.
Comments: Microstructural characterization of HAZ, weld and parent metal. Especially effective for very fine structures. Less effective than Nital for the ferrite grain boundaries.

Table A.6 — Ammonium peroxodisulphate solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 100 ml water (H ₂ O) 10 g ammonium peroxodisulphate [(NH ₄) ₂ S ₂ O ₈]
Safe shelf life: Limited
Surface preparation: 6 µm diamond or finer
Etching temperature: Ambient
Etching time: 2 min to 3 min
Additional precautions/requirements: nil
Comments: Reveals extent of HAZ. Microscopic features of multipass welds.

Table A.7 — Alcoholic hydrochloric solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 100 ml ethyl alcohol (C ₂ H ₅ OH) 1 ml to 5 ml hydrochloric acid (HCl)
Safe shelf life: Indefinite
Surface preparation: 3 µm diamond or finer
Etching temperature: 40 °C to 50 °C
Etching time: A few seconds to one minute
Additional precautions/requirements: Usual precautions for handling and disposal of acids. Add HCl to C ₂ H ₅ OH.
Comments: nil

Table A.8 — 120/10/30 etchant

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 120 ml ethyl alcohol (C ₂ H ₅ OH) or methyl alcohol (CH ₃ OH) 10 ml iron (III) chloride (FeCl ₃) (60 % W/V) 30 ml hydrochloric acid (HCl)
Safe shelf life: Indefinite
Surface preparation: 2 µm diamond or finer
Etching temperature: Ambient
Etching time: A few seconds by immersion — check by eye
Additional precautions/requirements: Usual precautions for handling and disposal of acids.
Comments: Good general-purpose etchant.

Table A.9 — Cuprochloric solution 1

Type of etchant: Macroscopic etchant
Composition in volume and in order of mixing: 30 ml water (H ₂ O) 25 ml ethyl alcohol (C ₂ H ₅ OH) 40 ml hydrochloric acid (HCl) 5 g copper (II) chloride (CuCl ₂)
Safe shelf life: 2 h
Surface preparation: 1 000 grit or finer
Etching temperature: Ambient
Etching time: 10 s to 20 s
Additional precautions/requirements: After the etching, the specimen should be washed in order to remove copper deposits. Usual precautions for handling and disposal of acids.
Comments: Reveals cold working strain lines.

Table A.10 — Magneso cuprochloric solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 100 ml ethyl alcohol (C ₂ H ₅ OH) 20 ml water (H ₂ O) 1 ml hydrochloric acid (HCl) 4 g magnesium (II) chloride (MgCl ₂) 1 g copper (II) chloride (CuCl ₂)
Safe shelf life: 2 h
Surface preparation: 3 µm diamond or finer
Etching temperature: Ambient
Etching time: 60 s
Additional precautions/requirements: Salts should be dissolved in the smallest amount of hot water, then diluted with ethyl alcohol. A slight polishing (1 µm) after the etching furnishes the best contrast.
Comments: Reveals phosphorus and related segregations. The copper deposits first of all on those areas poorest in phosphorus.

Table A.11 — Adler's etchant

Type of etchant: Macroscopic etchant
Composition in volume and in order of mixing: 25 ml water (H ₂ O) 3 g ammonium tetra chloro diaquo cuprate (II) [(NH ₄) ₂ CuCl ₄ ·2H ₂ O] 50 ml hydrochloric acid (HCl) 15 g iron (III) chloride (FeCl ₃)
Safe shelf life: Months
Surface preparation: 320 grit or finer
Etching temperature: Ambient
Etching time: 5 s to 10 s
Additional precautions/requirements: Add [(NH ₄) ₂ CuCl ₄ ·2H ₂ O] to H ₂ O (a). Add FeCl ₃ to HCl (b). Mix both then add (b) to (a).
Comments: nil

Table A.12 — Heyn's etchant

Type of etchant: Macroscopic etchant
Composition in volume and in order of mixing: 120 ml water (H ₂ O) 10 g ammonium tetra chloro diaquo cuprate (II) [(NH ₄) ₂ CuCl ₄ ·2H ₂ O]
Safe shelf life: Months
Surface preparation: 240 grit or finer
Etching temperature: Ambient
Etching time: 10 s to 1 min
Additional precautions/requirements: Add [(NH ₄) ₂ CuCl ₄ ·2H ₂ O] to H ₂ O.
Comments: Copper deposit shall be removed.

Table A.13 — Ferric chloride solution

Type of etchant: Macroscopic etchant
Composition in volume and in order of mixing: 70 ml water (H ₂ O) 30 ml iron (III) chloride (FeCl ₃) (60 % W/V)
Safe shelf life: Indefinite.
Surface preparation: 1 000 grit or finer
Etching temperature: Ambient
Etching time: A few seconds
Additional precautions/requirements: Usual precaution for handling and disposal of acids.
Comments: 1) Swab the surface; 2) Rinse with water; 3) Swab again the surface; 4) After etching, water rinse, alcohol rinse, dry.

Annex B (informative)

Etchants for stainless steels

See Tables B.1 to B.12.

Table B.1 — Oxalic acid solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 100 ml water (H ₂ O) 10 g oxalic acid (ethanedioic acid) (C ₂ H ₂ O ₄)
Safe shelf life: Indefinite
Surface preparation: 3 µm diamond or finer
Etching temperature: Ambient
Etching time: A few seconds — check by eye
Additional precautions/requirements: Usual precautions for handling and disposal of acids.
Comments: Electrolytic 2 V to 6 V. Can reveal sensitivity to inter-crystalline corrosion. Reveals general structure. Reveals carbides at the grain boundaries.

Table B.2 — Thiocyanate solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 80 ml water (H ₂ O) 20 ml sulphuric acid (H ₂ SO ₄) 10 g ammonium thiocyanate (NH ₄ SCN)
Safe shelf life: Indefinite
Surface preparation: 3 µm diamond or finer
Etching temperature: Ambient
Etching time: A few seconds — check by eye
Additional precautions/requirements: Usual precautions for handling and disposal of acids.
Comments: Electrolytic 1,5 V to 2,0 V. Good general purpose etchant.

Table B.3 — Acidified ferric chloride solution

Type of etchant: Macroscopic etchant
Composition in volume and in order of mixing: 480 ml water (H ₂ O) 120 ml hydrochloric acid (HCl) 50 g iron (III) chloride (FeCl ₃)
Safe shelf life: Indefinite
Surface preparation: 600 grit or finer
Etching temperature: Ambient
Etching time: A few seconds to one minute — check by eye
Additional precautions/requirements: Usual precautions for handling and disposal of acids.
Comments: Good general purpose macroscopic etchant, for austenitic chromium nickel and other stainless steels.

Table B.4 — Modified Murakami's etchant

Type of etchant: Macroscopic etchant
Composition in volume and in order of mixing: 60 ml water (H ₂ O) 30 g potassium ferricyanide [K ₃ Fe(CN) ₆] 30 g potassium hydroxide (KOH)
Safe shelf life: Fresh solution
Surface preparation: 1 µm diamond or finer
Etching temperature: Temperature of freshly prepared solution (hot)
Etching time: 20 s to 40 s
Additional precautions/requirements: Usual precautions for handling and disposal of caustic solutions.
Comments: Reveals σ phase from δ ferrite and carbides. Austenite matrix is not revealed.

Table B.5 — Cuprochloric solution 2

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 100 ml water(H ₂ O) 100 ml ethyl alcohol (C ₂ H ₅ OH) 100 ml hydrochloric acid (HCl) 5 g copper (II) chloride (CuCl ₂)
Safe shelf life: 2 h
Surface preparation: 1 µm diamond or finer
Etching temperature: Ambient
Etching time: 10 s to a few minutes
Additional precautions/requirements: After etching, the test specimen should be washed in order to remove copper deposits. Usual precautions for handling and disposal of acids.
Comments: Especially for ferritic and martensitic stainless steels, an alternative to electrolytic etching. Less effective for austenitic grain boundaries that can be attacked using longer etching times. Not effective for carbides.

Table B.6 — Chromic acid solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 100 ml water (H ₂ O) 10 g chromium (VI) oxide (CrO ₃)
Safe shelf life: A few days
Surface preparation: 1 µm diamond or finer
Etching temperature: Ambient
Etching time: 10 s to 1 min
Additional precautions/requirements: Usual precautions for handling and disposal of acids.
Comments: Austenitic grain boundaries. Distinguishes σ phase and carbides. Electrolytic etching (3 V) for general purpose etchings. For the analysis of carbides, the etching is carried out in two steps: first with 1 V and afterwards with 3 V.

Table B.7 — Alcoholic hydrochloric solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 100 ml ethyl alcohol (C ₂ H ₅ OH) 1 ml to 5 ml hydrochloric acid (HCl)
Safe shelf life: Indefinite
Surface preparation: 3 µm diamond or finer
Etching temperature: 40 °C to 50 °C
Etching time: A few seconds to one minute
Additional precautions/requirements: Add HCl to C ₂ H ₅ OH. Usual precaution for handling and disposal of acids.
Comments: nil

Table B.8 — Hydrochloric nitric acid solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 39 ml water (H ₂ O) 52 ml hydrochloric acid (HCl) 9 ml nitric acid (HNO ₃), (concentration 65 %)
Safe shelf life: Indefinite
Surface preparation: 3 µm diamond or finer
Etching temperature: Ambient
Etching time: A few seconds to a few minutes
Additional precautions/requirements: Always add HCl and HNO ₃ to H ₂ O. Usual precautions for handling and disposal of acids.
Comments: nil

Table B.9 — Adler's etchant

Type of etchant: Macroscopic etchant
Composition in volume and in order of mixing: 25 ml water (H ₂ O) 3 g ammonium tetra chloro diaquo cuprate (II) [(NH ₄) ₂ CuCl ₄ ·2H ₂ O] 50 ml hydrochloric acid (HCl) 15 g iron (III) chloride (FeCl ₃)
Safe shelf life: Months
Surface preparation: 320 grit or finer.
Etching temperature: Ambient
Etching time: 5 s to 10 s
Additional precautions/requirements: Add [(NH ₄) ₂ CuCl ₄ ·2H ₂ O to H ₂ O] (a). Add FeCl ₃ to HCl (b). Mix both then add (b) to (a).
Comments: nil

Table B.10 — Fluonitric acid solution 1

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 50 ml nitric acid (HNO ₃) 50 ml hydrofluoric acid (HF)
Safe shelf life: Do not store after using.
Surface preparation: 2 µm diamond or finer
Etching temperature: Ambient
Etching time: 5 min to 30 min by immersion
Additional precautions/requirements: CAUTION: When handling HF wear hand and eye protection. In the event of bodily contact, wash off skin immediately and seek medical advice. Use receptacles in plastic. Usual precautions for handling and disposal of acids.
Comments: Reveals general structure.

Table B.11 — Fluonitric acid solution 2

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 100 ml water (H ₂ O) 100 ml nitric acid (HNO ₃) 100 ml hydrofluoric acid (HF)
Safe shelf life: Do not store after using.
Surface preparation: 2 µm diamond or finer
Etching temperature: Ambient
Etching time: 1 min to 15 min by immersion
Additional precautions/requirements: CAUTION: When handling HF wear hand and eye protection. In the event of bodily contact, wash off skin immediately and seek medical advice. Use receptacles in plastic. Usual precautions for handling and disposal of acids.
Comments: Reveals grain boundaries.

Table B.12 — Nitric acid solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 50 ml water (H ₂ O) 50 ml nitric acid (HNO ₃)
Safe shelf life: Indefinite
Surface preparation: 2 µm diamond or finer
Etching temperature: Ambient
Etching time: A few seconds
Additional precautions/requirements: Usual precautions for handling and disposal of acids.
Comments: Electrolytic at 3 V to 6 V. Rinse in the solution to remove the film present on the surface.

Annex C (informative)

Etchants for nickel and nickel alloys

See Tables C.1 to C.4.

Table C.1 — Alcoholic hydrochloric acid solution with hydrogen peroxide

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 65 ml ethyl alcohol (C ₂ H ₅ OH) 35 ml hydrochloric acid (HCl) 4 ml hydrogen peroxide (H ₂ O ₂) (20 volumes)
Safe shelf life: Do not store after using.
Surface preparation: 2 µm diamond or finer
Etching temperature: Ambient
Etching time: A few seconds — check by eye
Additional precautions/requirements: Add H ₂ O ₂ just before using. Usual precautions for handling and disposal of acids.
Comments: Good general-purpose etchant.

Table C.2 — Thiocyanate solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 80 ml water (H ₂ O) 20 ml sulfuric acid (H ₂ SO ₄) 10 g ammonia thiocyanate (NH ₄ SCN)
Safe shelf life: Indefinite
Surface preparation: 3 µm diamond or finer
Etching temperature: Ambient
Etching time: A few seconds — check by eye
Additional precautions/requirements: Usual precautions for handling and disposal of acids.
Comments: Electrolytic 1,5 V to 2,0 V. Good general-purpose etchant.

Table C.3 — Nitric acetic acid solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 30 ml acetone [(CH ₃) ₂ CO] 30 ml nitric acid (HNO ₃) 30 ml acetic acid (CH ₃ COOH)
Safe shelf life: Do not store after using.
Surface preparation: 3 µm diamond or finer
Etching temperature: Ambient
Etching time: few seconds — check by eye
Additional precautions/requirements: Keep cool. Nitrous oxide given off. Usual precautions for handling and disposal of acids.
Comments: Good general-purpose etchant.

Table C.4 — Adler's etchant

Type of etchant: Macroscopic etchant
Composition in volume and in order of mixing: 25 ml water (H ₂ O) 3 g ammonium tetra chloro diaquo cuprate (II) [(NH ₄) ₂ CuCl ₄ ·2H ₂ O] 50 ml hydrochloric acid (HCl) 15 g iron (III) chloride (FeCl ₃)
Safe shelf life: Months
Surface preparation: 320 grit or finer
Etching temperature: Ambient
Etching time: 5 s to 10 s
Additional precautions/requirements: Add [(NH ₄) ₂ CuCl ₄ ·2H ₂ O] to H ₂ O (a). Add FeCl ₃ to HCl (b). Mix both then add (b) to (a).
Comments: nil

Annex D (informative)

Etchants for titanium and titanium alloys

See Tables D.1 and D.2.

Table D.1 — Keller's etchant

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 950 ml water (H ₂ O) 25 ml nitric acid (HNO ₃) 15 ml hydrochloric acid (HCl) 10 ml hydrofluoric acid (HF)
Safe shelf life: Indefinite
Surface preparation: 3 µm diamond or finer
Etching temperature: Ambient
Etching time: A few seconds — check by eye
Additional precautions/requirements: CAUTION: When handling HF wear hand and eye protection. In the event of bodily contact, wash off skin immediately and seek medical advice. Use receptacles in plastic. Usual precautions for handling and disposal of acids.
Comments: Good general-purpose etchant.

Table D.2 — Fluonitric acid solution 3

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 880 ml water (H ₂ O) 100 ml nitric acid (HNO ₃) 20 ml hydrofluoric acid (HF)
Safe shelf life: Indefinite
Surface preparation: 3 µm diamond or finer
Etching temperature: Ambient
Etching time: A few seconds — check by eye
Additional precautions/requirements: CAUTION: When handling HF wear hand and eye protection. In the event of bodily contact, wash off skin immediately and seek medical advice. Use receptacles in plastic. Usual precautions for handling and disposal of acids.
Comments: Good general-purpose etchant.

Annex E (informative)

Etchants for copper and copper alloys

See Tables E.1 to E.3.

Table E.1 — Alcoholic acidified ferric chloride solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 960 ml industrial methylated spirits* 20 ml hydrochloric acid (HCl) 50 g iron (III) chloride (FeCl ₃) *ethyl alcohol (C ₂ H ₅ OH) denatured with methyl alcohol (CH ₃ OH)
Safe shelf life: Indefinite
Surface preparation: 3 µm diamond or finer
Etching temperature: Ambient
Etching time: A few seconds — check by eye
Additional precautions/requirements: Usual precautions for handling and disposal of acids.
Comments: Good general-purpose etchant, especially for high copper content alloys.

Table E.2 — Ammonium peroxodisulfate solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 90 ml water (H ₂ O) 10 mg ammonium peroxodisulfate [(NH ₄) ₂ S ₂ O ₈] 10 ml ammonium hydroxide (ammonia solution) (NH ₃ in H ₂ O) specific gravity 0,880 g/cm ³ .
Safe shelf life: Use fresh. Do not store after using.
Surface preparation: 3 µm diamond or finer
Etching temperature: Ambient
Etching time: A few seconds — check by eye
Additional precautions/requirements: Usual precautions for handling and disposal of caustic solutions.
Comments: Good general-purpose etchant.

Table E.3 — Nitric acid with ammonium and ferric nitrate solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 500 ml water (H ₂ O) 2 ml nitric acid (HNO ₃) 2 g ammonium nitrate (NH ₄ NO ₃) 20 g iron (III) nitrate [Fe(NO ₃) ₃]
Safe shelf life: Indefinite
Surface preparation: 3 µm diamond or finer
Etching temperature: Ambient
Etching time: A few seconds — check by eye
Additional precautions/requirements: Usual precautions for handling and disposal of acids.
Comments: Good general-purpose etchant.

STANDARDSISO.COM : Click to view the full PDF of ISO/TR 16060:2003

Annex F (informative)

Etchants for aluminium and aluminium alloys

See Tables F.1 to F.7.

Table F.1 — Sodium hydroxide solution

Type of etchant: Macroscopic etchant
Composition in volume and in order of mixing: 100 ml water (H ₂ O) 15 g sodium hydroxide (NaOH)
Safe shelf life: Do not store after using.
Surface preparation: 600 grit or finer
Etching temperature: Ambient
Etching time: A few seconds — check by eye
Additional precautions/requirements: Usual precautions for handling and disposal of caustic solutions. Use in a fume cupboard.
Comments: Good general-purpose etchant. Can be used in various dilutions.

Table F.2 — Keller's etchant

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 950 ml water (H ₂ O) 25 ml nitric acid (HNO ₃) 15 ml hydrochloric acid (HCl) 10 ml hydrofluoric acid (HF)
Safe shelf life: Indefinite
Surface preparation: 3 µm diamond or finer
Etching temperature: Ambient
Etching time: A few seconds — check by eye
Additional precautions/requirements: CAUTION: When handling HF wear hand and eye protection. In the event of bodily contact, wash off skin immediately and seek medical advice. Use receptacles in plastic. Usual precautions for handling and disposal of acids.
Comments: Good general-purpose etchant. Warning: grain boundary attack can look like cracks.

Table F.3 — Hydrochloric nitric hydrofluoric acid solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 350 ml water (H ₂ O) 300 ml hydrochloric acid (HCl) 300 ml nitric acid (HNO ₃) 50 ml hydrofluoric acid (HF)
Safe shelf life: Is indicated by a change of colour to greenish brown and sluggish reaction.
Surface preparation: 3 µm diamond or finer
Etching temperature: Ambient
Etching time: 30 s to 60 s after start of reaction.
Additional precautions/requirements: CAUTION: When handling HF wear hand and eye protection. In the event of bodily contact, wash off skin immediately and seek medical advice. Use receptacles in plastic. Usual precautions for handling and disposal of acids.
Comments: Warning: Grain boundary attack can look like cracks.

Table F.4 — Hydrochloric nitric orthophosphoric acid solution

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 480 ml water (H ₂ O) 200 ml hydrochloric acid (HCl) 200 ml nitric acid (HNO ₃) 120 ml orthophosphoric acid (H ₃ PO ₄)
Safe shelf life: Is indicated by a change of colour to greenish brown and sluggish reaction.
Surface preparation: 3 µm diamond or finer
Etching temperature: 30 °C to 40 °C
Etching time: 60 s to 120 s after start of reaction.
Additional precautions/requirements: Usual precautions for handling and disposal of acids.
Comments: Warning: grain boundary attack can look like cracks

Table F.5 — Barker's etchant

Type of etchant: Microscopic etchant
Composition in volume and in order of mixing: 940 ml water (H ₂ O) 60 ml fluorobaric acid (HBF ₄)
Safe shelf life: Normally is stable for an unlimited period only.
Surface preparation: 3 µm diamond of finer
Etching temperature: Ambient
Etching time: 40 s to 60 s
Additional precautions/requirements: See in Clause F.1 the description of the "Barker" procedure.
Comments: Warning: grain boundary attack can look like cracks. For examination of grain and/or fibre structures of aluminium and aluminium alloys, the examination of the "Barker" anodized samples under polarized light proved to be successful and produced the required result