

# NFPA® 703

## Standard for Fire Retardant–Treated Wood and Fire-Retardant Coatings for Building Materials

### 2009 Edition



NFPA, 1 Batterymarch Park, Quincy, MA 02169-7471  
An International Codes and Standards Organization

## **IMPORTANT NOTICES AND DISCLAIMERS CONCERNING NFPA DOCUMENTS**

### **NOTICE AND DISCLAIMER OF LIABILITY CONCERNING THE USE OF NFPA DOCUMENTS**

NFPA codes, standards, recommended practices, and guides, of which the document contained herein is one, are developed through a consensus standards development process approved by the American National Standards Institute. This process brings together volunteers representing varied viewpoints and interests to achieve consensus on fire and other safety issues. While the NFPA administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its codes and standards.

The NFPA disclaims liability for any personal injury, property or other damages of any nature whatsoever, whether special, indirect, consequential or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this document. The NFPA also makes no guaranty or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this document available, the NFPA is not undertaking to render professional or other services for or on behalf of any person or entity. Nor is the NFPA undertaking to perform any duty owed by any person or entity to someone else. Anyone using this document should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances.

The NFPA has no power, nor does it undertake, to police or enforce compliance with the contents of this document. Nor does the NFPA list, certify, test or inspect products, designs, or installations for compliance with this document. Any certification or other statement of compliance with the requirements of this document shall not be attributable to the NFPA and is solely the responsibility of the certifier or maker of the statement.

## **ADDITIONAL NOTICES AND DISCLAIMERS**

### **Updating of NFPA Documents**

Users of NFPA codes, standards, recommended practices, and guides should be aware that these documents may be superseded at any time by the issuance of new editions or may be amended from time to time through the issuance of Tentative Interim Amendments. An official NFPA document at any point in time consists of the current edition of the document together with any Tentative Interim Amendments and any Errata then in effect. In order to determine whether a given document is the current edition and whether it has been amended through the issuance of Tentative Interim Amendments or corrected through the issuance of Errata, consult appropriate NFPA publications such as the National Fire Codes® Subscription Service, visit the NFPA website at [www.nfpa.org](http://www.nfpa.org), or contact the NFPA at the address listed below.

### **Interpretations of NFPA Documents**

A statement, written or oral, that is not processed in accordance with Section 6 of the Regulations Governing Committee Projects shall not be considered the official position of NFPA or any of its Committees and shall not be considered to be, nor be relied upon as, a Formal Interpretation.

### **Patents**

The NFPA does not take any position with respect to the validity of any patent rights asserted in connection with any items which are mentioned in or are the subject of NFPA codes, standards, recommended practices, and guides, and the NFPA disclaims liability for the infringement of any patent resulting from the use of or reliance on these documents. Users of these documents are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, is entirely their own responsibility.

NFPA adheres to applicable policies of the American National Standards Institute with respect to patents. For further information contact the NFPA at the address listed below.

### **Law and Regulations**

Users of these documents should consult applicable federal, state, and local laws and regulations. NFPA does not, by the publication of its codes, standards, recommended practices, and guides, intend to urge action that is not in compliance with applicable laws, and these documents may not be construed as doing so.

### **Copyrights**

This document is copyrighted by the NFPA. It is made available for a wide variety of both public and private uses. These include both use, by reference, in laws and regulations, and use in private self-regulation, standardization, and the promotion of safe practices and methods. By making this document available for use and adoption by public authorities and private users, the NFPA does not waive any rights in copyright to this document.

Use of NFPA documents for regulatory purposes should be accomplished through adoption by reference. The term "adoption by reference" means the citing of title, edition, and publishing information only. Any deletions, additions, and changes desired by the adopting authority should be noted separately in the adopting instrument. In order to assist NFPA in following the uses made of its documents, adopting authorities are requested to notify the NFPA (Attention: Secretary, Standards Council) in writing of such use. For technical assistance and questions concerning adoption of NFPA documents, contact NFPA at the address below.

### **For Further Information**

All questions or other communications relating to NFPA codes, standards, recommended practices, and guides and all requests for information on NFPA procedures governing its codes and standards development process, including information on the procedures for requesting Formal Interpretations, for proposing Tentative Interim Amendments, and for proposing revisions to NFPA documents during regular revision cycles, should be sent to NFPA headquarters, addressed to the attention of the Secretary, Standards Council, NFPA, 1 Batterymarch Park, P.O. Box 9101, Quincy, MA 02269-9101.

For more information about NFPA, visit the NFPA website at [www.nfpa.org](http://www.nfpa.org).

Copyright © 2008 National Fire Protection Association®. All Rights Reserved.

## NFPA® 703

### Standard for

# Fire Retardant-Treated Wood and Fire-Retardant Coatings for Building Materials

## 2009 Edition

This edition of NFPA 703, *Standard for Fire Retardant-Treated Wood and Fire-Retardant Coatings for Building Materials*, was prepared by the Technical Committee on Structures, Construction, and Materials. It was issued by the Standards Council on May 30, 2008, with an effective date of July 18, 2008, and supersedes all previous editions.

This edition of NFPA 703 was approved as an American National Standard on July 18, 2008.

### Origin and Development of NFPA 703

In 1957, the Committee on Flameproofing and Preservative Treatments began to develop a standard for the flameproofing of wood. It soon became clear to the Committee that the fire retardant-coating industry was expanding considerably and that fire-retardant admixtures of plastics and other building materials required coverage in the standard. Thus, in its many subsequent meetings, the Committee reexamined its approach and expanded the standard to cover all fire-retardant treatments.

The standard was tentatively adopted at the 1960 Annual Meeting and was submitted for final adoption at the 1961 Annual Meeting.

The 1979 edition of NFPA 703, *Fire Retardant Impregnated Wood and Fire Retardant Coatings for Building Materials*, superseded the 1961 edition. The change in title was necessary to more adequately cover the subjects included in the text of the standard. The principal changes in the 1979 edition included improved definitions for fire-retardant coatings.

The 1985 edition included the addition of a new chapter that listed referenced publications whose use was mandated within the standard.

In the 1992 edition, the Committee provided clarification in several areas defining fire resistance. The 1995 edition was a reconfirmation with some editorial changes.

The 2000 edition reflected changes in the methods by which treated wood products are evaluated. Other changes were format driven to reflect the *Manual of Style for NFPA Technical Committee Documents*.

In the 2006 edition, technical modifications brought the document into agreement with the 2003/2006 editions of *NFPA 5000, Building Construction and Safety Code*, on the topic of fire retardant-treated wood. Additional changes were made to the format in compliance with the latest edition of the *Manual of Style for NFPA Technical Committee Documents*.

The changes in the 2009 edition are editorial in nature.

## Technical Committee on Structures, Construction, and Materials

**Peter J. Willse**, *Chair*

Swiss Re, Global Asset Protection Services, CT [I]

**Jesse J. Beitel**, Hughes Associates, Inc., MD [SE]

**David S. Collins**, The Preview Group, Inc., OH [SE]  
Rep. American Institute of Architects

**Ralph Dorio**, Insurance Services Office, NJ [I]

**Jeffrey Feid**, State Farm Insurance Company, IL [I]

**Michael A. Gardner**, Gypsum Association, DC [M]

**Mark S. Graham**, National Roofing Contractors Association, IL [IM]

**John C. Harrington**, FM Global, MA [I]

**Alfred J. Hogan**, Winter Haven, FL [E]

Rep. New England Association of Fire Marshals

**Joseph T. Holland**, Hoover Treated Wood Products, FL [M]

**John V. Loscheider**, Loscheider Engineering Company, WA [SE]

Rep. National Council of Structural Engineers Associations

**Bonnie E. Manley**, American Iron and Steel Institute, MA [M]

**Joseph J. Messersmith, Jr.**, Portland Cement Association, VA [M]

**Eugene M. Novak, Jr.**, Commonwealth of Massachusetts, MA [E]

**Sarah A. Rice**, Schirmer Engineering Corporation, OH [I]

**James A. Rossberg**, American Society of Civil Engineers, VA [SE]

**David P. Tyree**, American Forest & Paper Association, CO [M]

**Joseph H. Versteeg**, Versteeg Associates, CT [E]  
Rep. International Fire Marshals Association

### Alternates

**David G. Bueche**, Hoover Treated Wood Products, CO [M]

(Alt. to J. T. Holland)

**Richard J. Davis**, FM Global, MA [I]

(Alt. to J. C. Harrington)

**Dennis L. Pitts**, American Forest & Paper Association, TX [M]

(Alt. to D. P. Tyree)

**Stephen V. Skalko**, Portland Cement Association, GA [M]

(Alt. to J. J. Messersmith, Jr.)

**Robert J. Wills**, American Iron and Steel Institute, AL [M]

(Alt. to B. E. Manley)

**Hossein Davoodi**, NFPA Staff Liaison

*This list represents the membership at the time the Committee was balloted on the final text of this edition. Since that time, changes in the membership may have occurred. A key to classifications is found at the back of the document.*

NOTE: Membership on a committee shall not in and of itself constitute an endorsement of the Association or any document developed by the committee on which the member serves.

**Committee Scope:** This Committee shall have primary responsibility for documents on the protection of human life and property from fire and environmental loads through the selection and design of structural elements and assemblies; construction techniques and methodologies; and on the application of building materials used in the construction of buildings, structures, and related facilities.

### Contents

<p><b>Chapter 1 Administration</b> ..... 703-4</p> <p>1.1 Scope ..... 703-4</p> <p>1.2 Purpose. (Reserved) ..... 703-4</p> <p>1.3 Application. (Reserved) ..... 703-4</p> <p>1.4 Retroactivity ..... 703-4</p> <p>1.5 Equivalency ..... 703-4</p> <p>1.6 Units ..... 703-4</p> <p><b>Chapter 2 Referenced Publications</b> ..... 703-4</p> <p>2.1 General ..... 703-4</p> <p>2.2 NFPA Publications ..... 703-4</p> <p>2.3 Other Publications ..... 703-4</p> <p>2.4 References for Extracts in Mandatory Sections. (Reserved) ..... 703-4</p> <p><b>Chapter 3 Definitions</b> ..... 703-4</p> <p>3.1 General ..... 703-4</p> <p>3.2 NFPA Official Definitions ..... 703-5</p> <p>3.3 General Definitions ..... 703-5</p>	<p><b>Chapter 4 Fire Retardant-Treated Wood</b> ..... 703-5</p> <p>4.1 Application ..... 703-5</p> <p>4.2 Interior Applications ..... 703-5</p> <p>4.3 Exposure to Weather or Damp or Wet Locations ..... 703-5</p> <p>4.4 Moisture Content ..... 703-5</p> <p>4.5 Labeling ..... 703-6</p> <p><b>Chapter 5 Fire-Retardant Coatings for Building Materials</b> ..... 703-6</p> <p>5.1 Application ..... 703-6</p> <p>5.2 General ..... 703-6</p> <p>5.3 Tests ..... 703-6</p> <p>5.4 Maintenance of Protection ..... 703-6</p> <p>5.5 Labeled ..... 703-6</p> <p><b>Annex A Explanatory Material</b> ..... 703-6</p> <p><b>Annex B Informational References</b> ..... 703-7</p> <p><b>Index</b> ..... 703-8</p>
--	---

## NFPA 703

### Standard for

# Fire Retardant-Treated Wood and Fire-Retardant Coatings for Building Materials

### 2009 Edition

**IMPORTANT NOTE:** This NFPA document is made available for use subject to important notices and legal disclaimers. These notices and disclaimers appear in all publications containing this document and may be found under the heading "Important Notices and Disclaimers Concerning NFPA Documents." They can also be obtained on request from NFPA or viewed at [www.nfpa.org/disclaimers](http://www.nfpa.org/disclaimers).

NOTICE: An asterisk (\*) following the number or letter designating a paragraph indicates that explanatory material on the paragraph can be found in Annex A.

Changes other than editorial are indicated by a vertical rule beside the paragraph, table, or figure in which the change occurred. These rules are included as an aid to the user in identifying changes from the previous edition. Where one or more complete paragraphs have been deleted, the deletion is indicated by a bullet (•) between the paragraphs that remain.

Information on referenced publications can be found in Chapter 2 and Annex B.

## Chapter 1 Administration

**1.1\* Scope.** This standard provides criteria for defining and identifying fire retardant-treated wood and fire retardant-coated building materials.

**1.2 Purpose. (Reserved)**

**1.3 Application. (Reserved)**

**1.4 Retroactivity.** Unless otherwise specified, the provisions of this standard shall not apply to facilities, equipment, structures, or installations that existed or were approved for construction or installation prior to the effective date of the standard. Where specified, the provisions of this standard shall be retroactive.

**1.5 Equivalency.**

**1.5.1** Nothing in this standard is intended to prevent the use of systems, methods, or devices of equivalent or superior quality, strength, fire resistance, effectiveness, durability, and safety over those prescribed by this standard.

**1.5.2** Technical documentation shall be submitted to the authority having jurisdiction to demonstrate equivalency. The system, method, or device shall be approved for the intended purpose by the authority having jurisdiction.

**1.6 Units.**

**1.6.1 SI Units.** Metric units in this standard are in accordance with the modernized metric system known as the International System of Units (SI).

**1.6.2 Primary and Equivalent Values.** If a value for a measurement as given in this standard is followed by an equivalent value

in other units, the first stated value shall be regarded as the requirement. A given equivalent value might be approximate.

## Chapter 2 Referenced Publications

**2.1 General.** The documents or portions thereof listed in this chapter are referenced within this standard and shall be considered part of the requirements of this document.

**2.2 NFPA Publications.** National Fire Protection Association, 1 Batterymarch Park, Quincy, MA 02169-7471.

NFPA 255, *Standard Method of Test of Surface Burning Characteristics of Building Materials*, 2006 edition.

**2.3 Other Publications.**

**2.3.1 ASTM Publications.** ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959.

ASTM D 2898, *Standard Test Methods for Accelerated Weathering of Fire-Retardant-Treated Wood for Fire Testing*, 1994 (2004).

ASTM D 3201, *Standard Test Method for Hygroscopic Properties of Fire-Retardant Wood and Wood-Base Products*, 1994 (2003).

ASTM D 5516, *Standard Test Method for Evaluating the Flexural Properties of Fire-Retardant Treated Softwood Plywood Exposed to Elevated Temperatures*, 2003.

ASTM D 5664, *Standard Test Method for Evaluating the Effects of Fire-Retardant Treatments and Elevated Temperatures on Strength Properties of Fire-Retardant Treated Lumber*, 2002.

ASTM D 6305, *Standard Practice for Calculating Bending Strength Design Adjustment Factors for Fire-Retardant Treated Plywood Roof Sheathing*, 2002 e1.

ASTM D 6841, *Standard Practice for Calculating Design Value Treatment Adjustment Factors for Fire-Retardant-Treated Lumber*, 2003.

ASTM E 84, *Standard Test Method for Surface Burning Characteristics of Building Materials*, 2004.

**2.3.2 UL Publications.** Underwriters Laboratories, Inc., 333 Pfingsten Road, Northbrook, IL 60062-2096.

ANSI/UL 723, *Standard for Test for Surface Burning Characteristics of Building Materials*, 2003, Revised 2005.

**2.3.3 Other Publications.**

*Merriam-Webster's Collegiate Dictionary*, 11th edition, Merriam-Webster, Inc., Springfield, MA, 2003.

**2.4 References for Extracts in Mandatory Sections. (Reserved)**

## Chapter 3 Definitions

**3.1 General.** The definitions contained in this chapter shall apply to the terms used in this standard. Where terms are not defined in this chapter or within another chapter, they shall be defined using their ordinarily accepted meanings within the context in which they are used. *Merriam-Webster's Collegiate Dictionary*, 11th edition, shall be the source for the ordinarily accepted meaning.

### 3.2 NFPA Official Definitions.

**3.2.1\* Approved.** Acceptable to the authority having jurisdiction.

**3.2.2\* Authority Having Jurisdiction (AHJ).** An organization, office, or individual responsible for enforcing the requirements of a code or standard, or for approving equipment, materials, an installation, or a procedure.

**3.2.3 Labeled.** Equipment or materials to which has been attached a label, symbol, or other identifying mark of an organization that is acceptable to the authority having jurisdiction and concerned with product evaluation, that maintains periodic inspection of production of labeled equipment or materials, and by whose labeling the manufacturer indicates compliance with appropriate standards or performance in a specified manner.

**3.2.4\* Listed.** Equipment, materials, or services included in a list published by an organization that is acceptable to the authority having jurisdiction and concerned with evaluation of products or services, that maintains periodic inspection of production of listed equipment or materials or periodic evaluation of services, and whose listing states that either the equipment, material, or service meets appropriate designated standards or has been tested and found suitable for a specified purpose.

**3.2.5 Shall.** Indicates a mandatory requirement.

**3.2.6 Should.** Indicates a recommendation or that which is advised but not required.

**3.2.7 Standard.** A document, the main text of which contains only mandatory provisions using the word “shall” to indicate requirements and which is in a form generally suitable for mandatory reference by another standard or code or for adoption into law. Nonmandatory provisions shall be located in an appendix or annex, footnote, or fine-print note and are not to be considered a part of the requirements of a standard.

### 3.3 General Definitions.

**3.3.1 Fire-Retardant Coating.** A coating that reduces the flame spread of Douglas fir, and all other tested combustible surfaces to which it is applied, by at least 50 percent or to a flame spread classification value of 75 or less, whichever is the lesser value, and has a smoke developed rating not exceeding 200 when tested in accordance with NFPA 255, ASTM E 84, or UL 723.

**3.3.1.1 Class A Fire-Retardant Coating.** A coating that reduces the flame spread to 25 or less, and that has a smoke developed rating not exceeding 200 where applied to the applicable substrate, building material, or species of wood when tested in accordance with NFPA 255, ASTM E 84, or UL 723.

**3.3.1.2 Class B Fire-Retardant Coating.** A coating that reduces the flame spread to greater than 25 but not more than 75, and that has a smoke developed rating not exceeding 200 where applied to the applicable substrate, building material, or species of wood when tested in accordance with NFPA 255, ASTM E 84, or UL 723.

**3.3.2 Fire Retardant-Treated Wood.** A wood product impregnated with chemical by a pressure process or other means during manufacture, which is tested in accordance with NFPA 255, ASTM E 84, or UL 723, has a listed flame spread of

25 or less, and shows no evidence of significant progressive combustion when the test is continued for an additional 20-minute period; nor does the flame front progress more than 10.5 ft (3.2 m) beyond the centerline of the burners at any time during the test.

## Chapter 4 Fire Retardant-Treated Wood

**4.1 Application.** These requirements shall apply to fire retardant-treated wood.

**4.2 Interior Applications.** Interior fire retardant-treated wood shall have a moisture content of not over 28 percent when tested in accordance with the procedures of ASTM D 3201 at 92 percent relative humidity. Interior fire retardant-treated wood shall be tested in accordance with 4.2.1 or 4.2.2.

**4.2.1 Wood Structural Panels.** Adjustment to design values for wood structural panels shall be in accordance with the following:

- (1) The effect of the treatment, the method of redrying after treatment, and the exposure to high temperatures and high humidities on the flexure properties of fire retardant-treated softwood plywood shall be determined in accordance with ASTM D 5516.
- (2) The test data developed by ASTM D 5516 shall be used to develop adjustment factors or maximum loads and spans, or both, for untreated plywood design values in accordance with ASTM D 6305.
- (3) Each manufacturer shall publish the allowable maximum loads and spans for service as floor and roof sheathing for their treatment.

**4.2.2 Lumber.** Adjustment to design values for lumber shall be in accordance with the following:

- (1) For each species of wood treated, the effect of the treatment, the method of redrying after treatment, and the exposure to high temperatures and high humidities on the allowable design properties of fire retardant-treated lumber shall be determined in accordance with ASTM D 5664.
- (2) The test data developed by ASTM D 5664 shall be used to develop modification factors for use at or near room temperature and at elevated temperatures and humidity in accordance with ASTM D 6841.
- (3) Each manufacturer shall publish the modification factors for service at ambient temperatures of up to 100°F (37.8°C) and for service as roof framing.
- (4) The roof framing modification factors shall take into consideration the climatological location.

**4.3 Exposure to Weather or Damp or Wet Locations.** Where fire retardant-treated wood is exposed to weather or damp or wet locations, it shall be identified as “exterior” to indicate that there is no increase in the listed flame spread index when subjected to ASTM D 2898. (See 3.3.2, *Fire Retardant-Treated Wood*.)

### 4.4 Moisture Content.

**4.4.1** Fire retardant-treated wood shall have a moisture content of 19 percent or less for lumber and 15 percent or less for wood structural panels before use.

**4.4.2** For fire retardant-treated wood dried after treatment, the temperatures shall not exceed the temperatures used in drying the lumber and plywood submitted for the testing described in 4.2.1 or 4.2.2.

**4.4.3** Fire retardant-treated wood that is air-dried after treatment (ADAT) shall be protected from the weather.

**4.5 Labeling.** Fire retardant-treated lumber and wood structural panels shall be labeled and listed with the following information:

- (1) Identification mark of an approved agency that lists materials in accordance with Chapter 3 (*See 3.2.4, Listed.*)
- (2) Identification of the treating manufacturer
- (3) Name of the fire-retardant treatment
- (4) Species of wood treated
- (5) End use of the product
- (6) Flame spread and smoke developed rating
- (7) Method of drying after treatment
- (8) Verification of conformance with appropriate standards in accordance with Sections 4.2 through 4.4
- (9) The words “No increase in the listed classification when subjected to the Standard Rain Test (ASTM D 2898),” for fire retardant-treated wood exposed to weather or to damp or wet locations

## Chapter 5 Fire-Retardant Coatings for Building Materials

**5.1\* Application.** These requirements shall apply to fire-retardant coatings such as paints and other surface coatings used to reduce certain burning characteristics of building materials.

### 5.2 General.

**5.2.1\*** Fire-retardant coatings shall remain stable and adhere to the material under all atmospheric conditions to which the material is exposed.

**5.2.2** A fire-retardant coating shall not be used for unprotected outdoor installations unless labeled for such installations.

**5.2.3** The classification of fire-retardant coatings shall apply only when the coating is applied at the rates of coverage and to the applicable substrate, building material, or species of wood indicated on the test report when the coating is applied in accordance with the manufacturer’s directions supplied with the container.

**5.2.4** Fire-retardant coatings shall be applied in accordance with the manufacturer’s directions.

**5.2.5** The application shall be certified by the applicator as being in conformance with the manufacturer’s directions for application.

**5.2.6** A fire-retardant coating shall not be coated over with any material unless both the fire-retardant coating and the overcoat have been tested as a system and are found to meet the requirements of a fire-retardant coating.

### 5.3 Tests.

**5.3.1\*** Fire-retardant coatings shall be tested by NFPA 255, ASTM E 84, or UL 723.

**5.3.2** Where fire-retardant coatings are to be subjected to sustained humidity of 80 percent or more or exposure to the weather, certification by a testing laboratory shall be required to indicate that there is no increase in listed classification when subjected to the “Standard Rain Test” described in ASTM D 2898.

**5.4 Maintenance of Protection.** Fire-retardant coatings shall possess the desired degree of permanency and shall be maintained to retain the effectiveness of the treatment under the service conditions encountered in actual use.

### 5.5 Labeled.

**5.5.1** The fire retardant-coating material shall be listed and labeled to indicate conformance with the requirements in Sections 5.2 through 5.4.

**5.5.2** The manufacturers’ instructions for application shall be affixed to each container of the fire retardant-coating material.

## Annex A Explanatory Material

*Annex A is not a part of the requirements of this NFPA document but is included for informational purposes only. This annex contains explanatory material, numbered to correspond with the applicable text paragraphs.*

**A.1.1** Fire resistance ratings measured on an hourly basis are not covered in this standard. To establish such ratings, tests should be made in accordance with NFPA 251.

**A.3.2.1 Approved.** The National Fire Protection Association does not approve, inspect, or certify any installations, procedures, equipment, or materials; nor does it approve or evaluate testing laboratories. In determining the acceptability of installations, procedures, equipment, or materials, the authority having jurisdiction may base acceptance on compliance with NFPA or other appropriate standards. In the absence of such standards, said authority may require evidence of proper installation, procedure, or use. The authority having jurisdiction may also refer to the listings or labeling practices of an organization that is concerned with product evaluations and is thus in a position to determine compliance with appropriate standards for the current production of listed items.

**A.3.2.2 Authority Having Jurisdiction (AHJ).** The phrase “authority having jurisdiction,” or its acronym AHJ, is used in NFPA documents in a broad manner, since jurisdictions and approval agencies vary, as do their responsibilities. Where public safety is primary, the authority having jurisdiction may be a federal, state, local, or other regional department or individual such as a fire chief; fire marshal; chief of a fire prevention bureau, labor department, or health department; building official; electrical inspector; or others having statutory authority. For insurance purposes, an insurance inspection department, rating bureau, or other insurance company representative may be the authority having jurisdiction. In many circumstances, the property owner or his or her designated agent assumes the role of the authority having jurisdiction; at government installations, the commanding officer or departmental official may be the authority having jurisdiction.

**A.3.2.4 Listed.** The means for identifying listed equipment may vary for each organization concerned with product evaluation; some organizations do not recognize equipment as listed unless it is also labeled. The authority having jurisdiction should utilize the system employed by the listing organization to identify a listed product.

**A.5.1** This section does not address the use of fire-retardant coatings as a thermal barrier.

**A.5.2.1** Certain coatings might not be suitable for high-humidity occupancies or for other occupancies where combustible dust or oily residue deposits might accumulate, affecting the ability of the coating to adhere to the substrate material.

**A.5.3.1** The flame spread rating is expressed numerically on a scale for which the zero point is fixed by the performance of inorganic-reinforced cement board and the 100 point (approximately) is fixed by the performance of red oak flooring.

## Annex B Informational References

**B.1 Referenced Publications.** The documents or portions thereof listed in this annex are referenced within the informational sections of this standard and are not part of the requirements of this document unless also listed in Chapter 2 for other reasons.

**B.1.1 NFPA Publications.** National Fire Protection Association, 1 Batterymarch Park, Quincy, MA 02169-7471.

NFPA 251, *Standard Methods of Tests of Fire Resistance of Building Construction and Materials*, 2006 edition.

**B.1.2 Other Publications. (Reserved)**

**B.2 Informational References. (Reserved)**

**B.3 References for Extracts in Informational Sections. (Reserved)**

## Index

Copyright © 2008 National Fire Protection Association. All Rights Reserved.

The copyright in this index is separate and distinct from the copyright in the document that it indexes. The licensing provisions set forth for the document are not applicable to this index. This index may not be reproduced in whole or in part by any means without the express written permission of NFPA.

<b>-A-</b>	
Approved (definition) .....	3.2.1, A.3.2.1
Authority having jurisdiction (definition) .....	3.2.2, A.3.2.2
<b>-D-</b>	
Definitions .....	Chap. 3
<b>-E-</b>	
Equivalency to standard .....	1.5
<b>-F-</b>	
Fire-retardant coatings .....	Chap. 5
Class A (definition) .....	3.3.1.1
Class B (definition) .....	3.3.1.2
Definition .....	3.3.1
Labeling and listing .....	5.5
Maintenance of protection .....	5.4
Tests .....	5.3, A.5.3.1
Fire retardant-treated wood .....	Chap. 4; <i>see also</i> Lumber, fire retardant-treated; Wood structural panels, fire retardant-treated
Definition .....	3.3.2
Interior applications .....	4.2
Labeling/identification .....	4.3, 4.5
Moisture content .....	4.2, 4.4
Weather or damp or wet locations, exposure to .....	4.3
Floors, fire retardant-treated wood used for .....	4.2.1(3)
<b>-I-</b>	
Identification .....	
Fire retardant-treated wood .....	4.5
For exterior use .....	4.3
<b>-L-</b>	
Labeled .....	
Definition .....	3.2.3
Fire retardant-coating material .....	5.5
Fire retardant-treated wood .....	4.5
<b>Listed</b>	
Definition .....	3.2.4, A.3.2.4
Fire retardant-coating material .....	5.5
Fire retardant-treated wood .....	4.5
Lumber, fire retardant-treated .....	4.2.2
Labeling .....	4.5
Moisture content .....	4.4
<b>-M-</b>	
Measurement, units of .....	1.6
<b>-R-</b>	
References .....	Chap. 2, Annex B
Retroactivity of standard .....	1.4
Roofs, fire retardant-treated wood used for .....	4.2.1(3), 4.2.2(4)
<b>-S-</b>	
Scope of standard .....	1.1, A.1.1
Shall (definition) .....	3.2.5
Should (definition) .....	3.2.6
SI units .....	1.6.1
Standard (definition) .....	3.2.7
<b>-T-</b>	
Tests .....	
Fire-retardant coatings for building materials .....	5.3
Fire retardant-treated wood .....	4.2
<b>-U-</b>	
Units of measurement .....	1.6
<b>-W-</b>	
Wood structural panels, fire retardant-treated .....	4.2.1
Labeling .....	4.5
Moisture content .....	4.4

## *Sequence of Events Leading to Issuance of an NFPA Committee Document*

### **Step 1: Call for Proposals**

- Proposed new Document or new edition of an existing Document is entered into one of two yearly revision cycles, and a Call for Proposals is published.

### **Step 2: Report on Proposals (ROP)**

- Committee meets to act on Proposals, to develop its own Proposals, and to prepare its Report.
- Committee votes by written ballot on Proposals. If two-thirds approve, Report goes forward. Lacking two-thirds approval, Report returns to Committee.
- Report on Proposals (ROP) is published for public review and comment.

### **Step 3: Report on Comments (ROC)**

- Committee meets to act on Public Comments to develop its own Comments, and to prepare its report.
- Committee votes by written ballot on Comments. If two-thirds approve, Report goes forward. Lacking two-thirds approval, Report returns to Committee.
- Report on Comments (ROC) is published for public review.

### **Step 4: Technical Report Session**

- “*Notices of intent to make a motion*” are filed, are reviewed, and valid motions are certified for presentation at the Technical Report Session. (“Consent Documents” that have no certified motions bypass the Technical Report Session and proceed to the Standards Council for issuance.)
- NFPA membership meets each June at the Annual Meeting Technical Report Session and acts on Technical Committee Reports (ROP and ROC) for Documents with “certified amending motions.”
- Committee(s) vote on any amendments to Report approved at NFPA Annual Membership Meeting.

### **Step 5: Standards Council Issuance**

- Notification of intent to file an appeal to the Standards Council on Association action must be filed within 20 days of the NFPA Annual Membership Meeting.
- Standards Council decides, based on all evidence, whether or not to issue Document or to take other action, including hearing any appeals.

## *Committee Membership Classifications*

The following classifications apply to Technical Committee members and represent their principal interest in the activity of the committee.

- M *Manufacturer*: A representative of a maker or marketer of a product, assembly, or system, or portion thereof, that is affected by the standard.
- U *User*: A representative of an entity that is subject to the provisions of the standard or that voluntarily uses the standard.
- I/M *Installer/Maintainer*: A representative of an entity that is in the business of installing or maintaining a product, assembly, or system affected by the standard.
- L *Labor*: A labor representative or employee concerned with safety in the workplace.
- R/T *Applied Research/Testing Laboratory*: A representative of an independent testing laboratory or independent applied research organization that promulgates and/or enforces standards.
- E *Enforcing Authority*: A representative of an agency or an organization that promulgates and/or enforces standards.
- I *Insurance*: A representative of an insurance company, broker, agent, bureau, or inspection agency.
- C *Consumer*: A person who is, or represents, the ultimate purchaser of a product, system, or service affected by the standard, but who is not included in the *User* classification.
- SE *Special Expert*: A person not representing any of the previous classifications, but who has a special expertise in the scope of the standard or portion thereof.

#### NOTES;

1. “Standard” connotes code, standard, recommended practice, or guide.
2. A representative includes an employee.
3. While these classifications will be used by the Standards Council to achieve a balance for Technical Committees, the Standards Council may determine that new classifications of members or unique interests need representation in order to foster the best possible committee deliberations on any project. In this connection, the Standards Council may make appointments as it deems appropriate in the public interest, such as the classification of “Utilities” in the National Electrical Code Committee.
4. Representatives of subsidiaries of any group are generally considered to have the same classification as the parent organization.