

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space

400 COMMONWEALTH DRIVE, WARRENDALE, PA 15096

**AEROSPACE
INFORMATION
REPORT**

AIR4160

Issued 2-10-89

Submitted for recognition as an American National Standard

ALTERNATIVES TO CADMIUM PLATING

1. PURPOSE:

- 1.1 The purpose of this information report is to summarize and document data regarding possible alternatives to the use of cadmium plating on hardware typical of the aerospace hose and fitting industry.

2. SCOPE:

- 2.1 To document and provide access to information obtained by an industry survey.

3. INTRODUCTION:

- 3.1 Due to the unique properties of cadmium, there does not appear to be a substitute material that provides the same advantages and corrosion protection. However, a number of alternative surface treatments are available. Each has relative merit as compared to cadmium.
- 3.2 The data found in Table I are intended as a guide and do not necessarily include all possible surface treatments or processes. Each treatment is compared to cadmium and rated according to the criteria below:

Ratings:

- A = Equal to or more desirable than cadmium
B = Slightly less desirable than cadmium (specific material selections and applications should be investigated)
C = Significantly less desirable than cadmium
D = Property is not applicable

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

4. ZINC:

- 4.1 There is evidence that zinc coatings at 150°F and higher reverse their roll in the galvanic circuit and become cathodic. That is, instead of being sacrificial, zinc becomes noble and the steel corrodes. Attached are references on the phenomenon.

Reversal of zinc - steel galvanic couple at moderate high temperatures:

LaQue and Copson, Corrosion Resistance of Metals and Alloys,
Second Edition ACS Monograph Series No. 158,
(Reinhold Publishing Company, 1965), p 230.

Uhlig Corrosion Handbook,
Sponsored by the Electrochemical Society,
(John Wiley and Sons Inc., 1948), p 814.

"Plating and Surface Finishing",
Journal of American Electroplaters and Surface Finishers Society,
(April 1987) Column: "Finishers Think Tank", p 10.

- 4.2 The use of zinc coatings, particularly at elevated temperatures, may cause corrosion. Users of this information document are cautioned to consider the environment temperature when considering this material.

PREPARED BY SAE COMMITTEE G-3,
AEROSPACE FITTINGS, HOSE AND TUBING ASSEMBLIES

TABLE I - Comparison Chart

Property	(Pure) Zinc	(Pure) Aluminum	MIL-C-81751 Aluminum Ceramic	Electroless Nickel 0.0003 to 0.0005 Thick	Tin-Zinc Alloy
Corrosion Resistant Marine Environment	C	A	A	C	B
Corrosion Resistant Industrial Environment	A	A	A	B	A
Galvanic Protection of Steel	A	A	A	D	A
Dimensional Control	A	A	A	A	A
Lubricants 0.0003-0.0005 thick (torque tension)	C	C	A	C	A
Lubricant (Heavy Load)	B	C	C	A	B
Compatibility with Aluminum	B	A	A	C	B
Temperature Resistance	A	A	A	A	A
Reliability (Threads, etc.)	A	A	A	A	B
Solderability	B	C	C	A	A
Process Hydrogen Embrittlement	A	A	A	A	A
Adhesive Bonding	B	A	B	A	B
Painting	A	A	A	A	B
Contact Resistance	B	A	C	B	B
Freon Cleaning Compatibility	D	A	A	A	D