



AEROSPACE MATERIAL SPECIFICATION	AMS1383™	REV. B
	Issued 1985-04 Revised 1994-05 Reaffirmed 2007-02 Stabilized 2020-07 Superseding AMS1383A	
Oxide Conditioner, Alkaline Permanganate Aircraft Turbine Engine Components		

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

AMS1383B has been declared "STABILIZED" by SAE AMS Committee J Aircraft Maintenance Chemicals and Materials and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAENORM.COM : Click to view the full PDF of AMS1383B

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2020 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS1383B>

1. SCOPE:

1.1 Form:

This specification covers an alkaline permanganate oxide conditioner in the form of a water-soluble powder or a liquid for dilution with water.

1.2 Application:

This product has been used typically for conditioning of oxidation products on aircraft turbine engine components fabricated from steels, nickel alloys, and cobalt alloys by immersion in a solution of the cleaner at elevated temperature, but usage is not limited to such applications.

1.3 Classification:

Conditioners conforming to this specification are classified as follows:

Type 1 - Water-soluble powder

Type 2 - Liquid

1.3.1 Type 1 shall be supplied unless Type 2 is ordered.

1.4 Safety - Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

1.4.1 Precautions: Conditioner may contain chemicals which, if improperly used, could be hazardous to the health and safety of operators. Protective clothing including eye shields, suitable gloves, and apron should be worn when preparing and using conditioner. Tanks shall be prepared and operated under conditions of adequate fume extraction and with due regard to the safety recommendations of the manufacturer of the conditioner together with local workshop safety regulations.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2825 Material Safety Data Sheets
ARP1755 Effect of Cleaning Agents on Aircraft Engine Materials, Stock Loss Test Method

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM D 1568 Sampling and Chemical Analysis of Alkylbenzene Sulfonates
ASTM D 2667 Biodegradability of Alkylbenzene Sulfonates

2.3 U.S. Government Publications:

Available from DODSSP Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-2073-1 DOD Materiel, Procedures for Development and Application of Packaging Requirements

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall be optional with the manufacturer. When prepared in accordance with manufacturer's instructions, the compound shall form a liquid product, with no solid sediment at room temperature, and shall meet the requirements of 3.2. Solution make up and control procedures shall be in accordance with manufacturer's instructions and purchaser's requirements.

3.2 Properties:

Conditioner shall conform to the following requirements; tests shall be performed in accordance with specified test methods on the product supplied at the maximum concentration and temperature recommended by the manufacturer.

- 3.2.1 Stock Loss: Test panels of alloys or panels with electrodeposited coatings shall not incur stock loss exceeding 0.000025 inch (0.635 μm) per surface and plasma deposited coatings shall not incur stock loss exceeding 0.0001 inch (2.5 μm) when tested in accordance with ARP1755, Category 5. Where required in ARP1755, stock loss figures shall be reported. Vendor may indicate where conditioner is not recommended for particular alloys or surface coatings.
- 3.2.2 Pitting and Intergranular Attack: Test panels and bars used for the stock loss test of 3.2.1 shall exhibit no surface attack, when examined at 50X magnification under oblique surface lighting conditions.
- 3.2.3 Biodegradability: Vendor shall supply evidence that surfactants used in the conditioner are at least 90% biodegradable, determined either in accordance with ASTM D 2667 where relevant to surfactant type or by alternative methods appropriate to surfactant type acceptable to purchaser.
 - 3.2.3.1 Evidence of surfactant biodegradability does not guarantee that the conditioner may be discharged in either concentrated or diluted form into public waterways or sewerage systems; manufacturers shall give advice on the means for disposal.
- 3.2.4 Storage Stability: Conditioner stored at 25 °C \pm 5 (77 °F \pm 9) for one year shall show no visual evidence of deterioration and shall meet all other technical requirements.
- 3.2.5 Performance: Conditioner, prepared and used in accordance with manufacturer's instructions, shall condition oxides on parts to make them readily removable. Conditioner which meets all other technical requirements shall be tested for conditioning performance in an approved engine overhaul facility for not less than six months, during which time at least ten turbofan or turbojet engines, or equivalent, shall be processed with satisfactory results before approval for service use is granted by the applicable engine manufacturer.

3.3 Quality:

The conditioner, as received by purchaser, if a liquid, shall be clear, homogeneous, and free from solid particles and separation and free from foreign materials detrimental to usage of the conditioner and, if in powder form, shall be free flowing, free from lumping caused by moisture absorption, and from foreign materials detrimental to its usage.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the conditioner shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the conditioner conforms to the requirements of this specification.

4.2 Classification of Tests:

Tests for all technical requirements except storage stability (3.2.4) are preproduction tests and shall be performed prior to or on the initial shipment of conditioner to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing:

Shall be in accordance with ASTM D 1568. A lot shall be all conditioner produced in a single production run from the same batches of raw materials under the same fixed conditions and presented for vendor's inspection at one time. A lot shall not exceed 6,000 gallons (22,700 L) if a liquid or 10,000 pounds (4536 kg) if a powder.

4.4 Approval:

4.4.1 Conditioner shall be approved by purchaser before conditioner for production use is supplied, unless such approval be waived by purchaser. Results of tests on production conditioner shall be essentially equivalent to those on the approved sample conditioner.

4.4.1.1 A new or revised conditioner may be conditionally approved pending completion of the storage stability test of 3.2.4. Full approval will be granted following testing for the other technical requirements after completion of storage stability testing.

4.4.2 Vendor shall use ingredients, manufacturing procedures, and methods of inspection on production conditioner which are essentially the same as those used on the approved sample conditioner. If necessary to make any change in ingredients or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in ingredients and/or processing and, when requested, sample conditioner. Production conditioner made by the revised procedure shall not be shipped prior to receipt of reapproval.