

**AEROSPACE
MATERIAL
SPECIFICATION**

AMS 1525B

Superseding AMS 1525A

Issued 7-15-77

Revised 4-1-85

CLEANER FOR AIRCRAFT EXTERIOR METALLIC SURFACES
Wipe Solvent, Cold Operations

1. SCOPE:

1.1 Form: This specification covers a wipe-solvent cleaner in the form of a liquid.

1.2 Application: Primarily for use at ambient temperature as a cleaner for exterior metallic surfaces of aircraft. This cleaner shall not be used on plastics or aircraft windows due to crazing properties.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications and Aerospace Recommended Practices shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 2825 - Material Safety Data Sheets

AMS 4049 - Aluminum Alloy Sheet and Plate, Alclad, 5.6Zn - 2.5Mg - 1.6Cu - 0.26Cr (Alclad 7075; -T6 Sheet -T651 Plate)

2.1.2 Aerospace Recommended Practices:

ARP 1512 - Corrosion of Aluminum Alloys by Aircraft Maintenance Chemicals, Sandwich Test

REAFFIRMED

10-91

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

AMS 1525B

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM D56 - Flash Point by Tag Closed Tester
- ASTM D891 - Specific Gravity of Industrial Aromatic Hydrocarbons and Related Materials
- ASTM D1078 - Distillation Range of Volatile Organic Liquids
- ASTM D1353 - Nonvolatile Matter in Volatile Solvents for Use in Paint, Varnish, Lacquer, and Related Products
- ASTM D1568 - Sampling and Chemical Analysis of Alkylbenzene Sulfonates
- ASTM F483 - Total Immersion Corrosion Test for Aircraft Maintenance Chemicals
- ASTM F485 - Effects of Cleaners on Unpainted Aircraft Surfaces
- ASTM F503 - Preparing Aircraft Cleaning Compounds, Liquid Type, for Storage Stability Testing

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Specifications:

- TT-M-261 - Methyl Ethyl Ketone, Technical
- TT-E-776 - Ethylene Glycol Monobutyl Ether (For Use in Organic Coatings)

2.3.2 Military Specifications:

- MIL-D-6998 - Dichloromethane, Technical

2.3.3 Military Standards:

- MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Composition: The cleaner shall be a uniform mixture of the following materials in the percentages by volume shown:

Ø

Dichloromethane (MIL-D-6998, Grade B)	69 + 1
Methyl Ethyl Ketone (TT-M-261)	29 + 1
Ethylene Glycol Monobutyl Ether (TT-E-776)	2 + 0.5

3.1.1 Cleaner shall not be deleterious to aircraft structural alloys.

3.2 Properties: The cleaner shall conform to the following requirements; tests shall be performed in accordance with specified test methods on the cleaner supplied in concentrated form:

3.2.1 Flash Point: Shall be not lower than 43°C (110°F), determined in accordance with ASTM D56.

3.2.2 Residue: There shall be no visible residue or stains on aluminum alloy panels after the final water rinse, determined in accordance with 3.2.2.1.

3.2.2.1 Two 2 x 6 in. (50 x 150 mm) panels of AMS 4049 aluminum alloy shall be cleaned with acetone. The specimens shall be immersed in a sufficient quantity of the cleaner to cover approximately one-half of the panel. After the cleaner has been applied, the panels shall be placed at approximately 45 deg from the horizontal in an oven maintained at $38^{\circ}\text{C} \pm 1$ ($100^{\circ}\text{F} \pm 2$) for 30 min. ± 1 . At the end of the 30 min., the panels shall be removed from the oven, rinsed with room-temperature distilled water, and allowed to dry. The treated and untreated areas of the panel shall be visually examined and compared for the presence of residue and stains.

3.2.3 Corrosion of Metal Surfaces:

3.2.3.1 Sandwich Corrosion: Specimens of AMS 4049 aluminum alloy, after test, shall show a rating not worse than 1, determined in accordance with ARP 1512.

3.2.3.2 Total Immersion Corrosion: Cleaner shall neither produce evidence of corrosion of the panels nor cause a weight change greater than 0.3 (mg/cm^2)/24 hr for any single panel of AMS 4049 aluminum alloy, determined in accordance with ASTM F483.

3.2.4 Temperature Stability: Cleaner shall not show chemical or physical deterioration, including evidence of discoloration, layering, or other change denoting loss of stability after exposure to $2^{\circ}\text{C} \pm 3$ ($35^{\circ}\text{F} \pm 5$) for 120 hr ± 1 .

3.2.5 Color: The product shall be water white.

3.2.6 Effect on Unpainted Surfaces: Cleaner, tested in accordance with ASTM F485, shall neither produce streaking of unpainted AMS 4049 aluminum alloy test panels nor leave any stains requiring polishing to remove.

3.2.7 Storage Stability: Cleaner shall be stable in storage for not less than 12 months at room temperature. Cleaner shall remain free of lumps and skin formation and shall remain homogeneous. Samples prepared as in 3.2.7.1 shall show no evidence of layering, separation, settling, or crystallization after being subjected to five freeze-thaw cycles in accordance with 3.2.7.2. Cleaner shall not deliquesce or otherwise deteriorate when stored in shipping container or use package for not less than 12 months, determined in accordance with ASTM F503.

3.2.7.1 Two 6-oz (177-mL) samples of the product shall be placed in 8-oz (237-mL) clear glass bottles, sealed, and, from that time until test is completed, shall be handled so as to minimize movement of the sample.

AMS 1525B

3.2.7.2 Samples shall be exposed for not less than 12 hr at $-23^{\circ}\text{C} + 1$ ($-10^{\circ}\text{F} + 2$). At the end of the 12 hr, sample shall be removed to a room-temperature environment and allowed to thaw completely.

3.2.8 Specific Gravity: Shall be 1.1204 - 1.2376 at 23°C (73°F), determined in accordance with ASTM D891.

3.2.9 Distillation Range: Shall be as follows, determined in accordance with ASTM D1078:

Initial Boiling Point	-	40°C	(104°F)	min
10%	-	47°C	(117°F)	min
20%	-	48°C	(118°F)	min
30%	-	50°C	(122°F)	min
40%	-	52°C	(126°F)	min
50%	-	55°C	(131°F)	min
60%	-	59°C	(138°F)	min
70%	-	65°C	(149°F)	min
80%	-	71°C	(160°F)	min
90%	-	81°C	(178°F)	min
Dry Point	-	166°C	(331°F)	max

3.2.10 Nonvolatile Matter: Shall not exceed 0.002%, determined in accordance with ASTM D1353.

3.2.11 Performance: Cleaner, when used in accordance with manufacturer's recommendations, shall remove normally accumulated soils from exterior metallic surfaces of aircraft without leaving any visible residue on any surface tested.

3.3 Quality: The cleaner, as received by purchaser, shall be clear, homogeneous, and free from solid particles and separation and from foreign materials detrimental to usage of the cleaner.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the cleaner shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the cleaner conforms to the requirements of this specification.

4.2 Classification of Inspection:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for flash point (3.2.1), residue (3.2.2), color (3.2.5), specific gravity (3.2.8), distillation range (3.2.9), nonvolatile matter (3.2.10), and quality (3.3) are classified as acceptance tests and shall be performed on each lot.

- 4.2.2 Periodic Tests: Tests to determine conformance to requirements for composition (3.1), corrosion of metal surfaces (3.2.3), temperature stability (3.2.4), effect on unpainted surfaces (3.2.6), and performance (3.2.11) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.
- 4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed on the initial shipment of cleaner to a purchaser, when a change in material or processing, or both, requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.
- 4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.
- 4.3 Sampling: Shall be in accordance with ASTM D1568, unless otherwise specified by purchaser; a lot shall be all cleaner produced in a single production run from the same batches of raw materials under the same fixed conditions and presented for vendor's inspection at one time.
- 4.4 Approval:
- 4.4.1 Sample cleaner shall be approved by purchaser before cleaner for production use is supplied, unless such approval be waived by purchaser. Results of tests on production cleaner shall be essentially equivalent to those on the approved sample.
- 4.4.2 Vendor shall use ingredients, manufacturing procedures, and methods of inspection on production cleaner which are essentially the same as those used on the approved sample cleaner. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in material or processing, or both, and, when requested, sample cleaner. Production cleaner made by the revised procedure shall not be shipped prior to receipt of reapproval.
- 4.5 Reports: Unless waived by purchaser, the vendor of the cleaner shall furnish with each shipment a report showing the results of tests to determine conformance to the acceptance test requirements and, when performed, to the periodic test requirements and stating that the cleaner conforms to the other technical requirements of this specification. This report shall include the purchase order number, AMS 1525B, manufacturer's identification, lot number, and quantity.
- 4.5.1 A material safety data sheet conforming to AMS 2825 or equivalent shall be supplied to each purchaser prior to, or concurrent with, the report of preproduction tests results or, if preproduction testing be waived by