

Issued 1945-05
Reaffirmed 2000-10
Revised 2010-11
Superseding AMS2243H

Tolerances
Corrosion and Heat-Resistant Steel Tubing

RATIONALE

AMS2243J revises tolerances (Tables 1, 2, and 3) and results from a Five Year Review and update of this specification.

1. SCOPE

This specification covers manufacturing tolerances applicable to seamless and welded tubing of corrosion and heat-resistant steel ordered to inch dimensions. These tolerances apply to all conditions and are based on individual measurements, unless otherwise noted. Tubing may be specified by two dimensions only (OD and wall thickness, ID and wall thickness, or OD and ID).

2. DIAMETER

2.1 Tubing Other than Pressure Tubing; Welded (See 2.1.1) or Seamless (See 2.1.2)

Shall be as shown in Table 1.

TABLE 1

| Specified OD or ID Inches | Tolerance, Inch Including Ovality (See 2.3) Plus and Minus | |
|------------------------------|--|-------|
| | Plus | Minus |
| Up to 0.5, excl | 0.003 | 0.003 |
| 0.5 to 1.5, excl | 0.003 | 0.003 |
| 1.5 to 3.5, excl | 0.004 | 0.004 |
| 3.5 to 5.5, excl | 0.005 | 0.005 |
| 5.5 and over | 0.010 | 0.010 |

2.1.1 Welded Tubing

Shall be bead-reduced or shall be cold finished by tube-reducing, cold-drawing, machining, or grinding.

2.1.2 Seamless Tubing

Shall be cold-finished by tube-reducing, cold-drawing, machining, or grinding.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions. Copyright © 2010 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER:
Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS2243J>**

2.2 Pressure Tubing (See 6.1.5); Cold Drawn or Cold Reduced (Seamless or Welded)

Shall be as shown in Table 2.

TABLE 2

| Specified OD or ID Inches | OD or ID Tolerance, Inch Including Ovality (See 2.3) Plus and Minus | |
|---------------------------|---|-------|
| | Up to 0.5, incl | 0.003 |
| Over 0.5 to 1.0, excl | 0.003 | |
| 1.0 to 1.5, excl | 0.003 | |
| 1.5 to 2.0, excl | 0.004 | |
| 2.0 to 2.5, excl | 0.004 | |
| 2.5 to 3.5, excl | 0.004 | |
| 3.5 to 5.5, excl | 0.005 | |
| 5.5 to 8.0, excl | 0.010 | |
| 8.0 to 8.625, incl | 0.020 | |

2.2.1 Half Tolerances

When half tolerances are specified, the tolerances of Table 2 shall be plus only; the minus side of the tolerance range shall not be applicable.

2.3 Ovality, All Tubing

All of the tolerances shown in Tables 1 and 2 include ovality except on light-walled tubing where the specified wall thickness is 3% or less of the specified OD. On such light-walled tubing, there is an additional ovality tolerance (in addition to the tabular tolerances) equal to $\pm 0.5\%$ of the specified OD (or ID); however, the average diameter shall be within the tabular tolerances.

3. WALL THICKNESS

3.1 Tubing Other than Pressure Tubing; Welded or Seamless

Shall be as shown in Table 3.

TABLE 3

| Specified OD or ID Inches | Wall Thickness Tolerance, % Plus or Minus | |
|------------------------------|--|----------------|
| | For Wall Thickness, Inch, Shown Under 0.250 | 0.250 and Over |
| Up to 0.5, excl | 10 | 10 |
| 0.5 to 1.5, excl | 10 | 10 |
| 1.5 to 3.5, excl | 12.5 | 10 |
| 3.5 to 5.5, excl | 12.5 | 10 |
| 5.5 and Over | 12.5 | 10 |

3.2 Pressure Tubing (See 6.1.5); Seamless or Welded

Shall be $\pm 10\%$ for all specified diameters.

3.2.1 Half Tolerances

When half tolerances are specified, tolerance shall be +10%, only. The minus side of the tolerance range shall not be applicable