



<b>AEROSPACE MATERIAL SPECIFICATION</b>	<b>AMS2245™</b>	<b>REV. C</b>
	Issued 1973-12 Reaffirmed 2013-04 Revised 2021-09  Superseding AMS2245B	
<b>Tolerances Titanium and Titanium Alloy Extruded Bars, Rods, and Shapes</b>		

RATIONALE

AMS2245C results from a Five-Year Review and editorial update of this specification. Addition of References (Section 2) has renumbered following paragraphs.

1. SCOPE

This specification covers established manufacturing tolerances applicable to titanium and titanium alloy extruded bars, rods, and shapes. These tolerances apply to all conditions, unless otherwise noted. The term "excl" applies only to the higher figure of the specified range.

1.1 Extrusions shall be specified in either inch/pound units or SI units. When inch/pound units are used, the tolerances shown for SI units are not applicable. When SI are used, the tolerances shown for inch/pound units are not applicable.

2. REFERENCES

There are no referenced publications specified herein.

3. DIAMETER OR THICKNESS

Shall be as shown in Table 1.

**Table 1A - Tolerance, diameter, inch/pound units**

Specified Diameter or Distance Between Parallel Sides Inches	Tolerance, Inches Plus and Minus (see 12.2)
Up to 0.500, excl	0.020
0.500 to 1.000, excl	0.030
1.000 to 2.000, excl	0.040
2.000 to 3.000, excl	0.050
3.000 to 5.000, excl	0.060
5.000 and over	0.125

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2021 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:**   Tel:   877-606-7323 (inside USA and Canada)  
   Tel:   +1 724-776-4970 (outside USA)  
   Fax:   724-776-0790  
   Email: CustomerService@sae.org  
**SAE WEB ADDRESS:**                   http://www.sae.org

**For more information on this standard, visit**  
<https://www.sae.org/standards/content/AMS2245C/>

**Table 1B - Tolerance, diameter, SI units**

Specified Diameter or Distance Between Parallel Sides Millimeters	Tolerance, Millimeters Plus and Minus (see 12.2)
Up to 12.50, excl	0.50
12.50 to 25.00, excl	0.75
25.00 to 50.00, excl	1.00
50.00 to 75.00, excl	1.25
75.00 to 125.00, excl	1.50
125.00 and over	3.20

## 4. CORNER AND FILLET RADII

## 4.1 Bars and Shapes (see Figure 1)

Shall be as shown in Table 2.

**Table 2A - Tolerance, corner and fillet radii, inch/pound units**

Specified Radius Inches	Tolerance, Inches, Plus and Minus	
	Difference Between Specified Radius and Corner Radius (A)	Difference Between Specified Radius and Fillet Radius (B)
All	0.031	0.062

**Table 2B - Tolerance, corner and fillet radii, SI units**

Specified Radius Millimeters	Tolerance, Millimeters, Plus and Minus	
	Difference Between Specified Radius and Corner Radius (A)	Difference Between Specified Radius and Fillet Radius (B)
All	0.80	1.60

## 5. ANGULARITY (SEE 12.3)

## 5.1 Shapes (see Figure 2)

Shall be as shown in Table 3.

**Table 3 - Tolerance on angularity**

Minimum Specified Leg or Metal Thickness Inches	Tolerance (Allowable Deviation from Specified Angle) Degrees, Plus and Minus (Ratio: Leg or Surface Length Shall Not Exceed 14 Times the Leg or Metal Thickness)
	All

## 6. TRANSVERSE FLATNESS

## 6.1 Bars and Shapes (see Figure 3)

Shall be as shown in Table 4.

**Table 4A - Transverse flatness tolerance, inch/pound units**

Surface Width (W) Inches	Tolerance (Allowable Deviation from Flat) Inches
Up to 1.000, excl	0.010
1.000 and over	0.010 x W
In any 1 inch of width	0.010

**Table 4B - Transverse flatness tolerance, SI units**

Surface Width (W) Millimeters	Tolerance (Allowable Deviation from Flat) Millimeters
Up to 25.00, excl	0.25
25.00 and over	0.25 x W
In any 25.00 mm of width	0.010

## 7. STRAIGHTNESS (SEE FIGURE 4)

Shall be as shown in Table 5.

**Table 5A - Straightness tolerance, inch/pound units**

Specified Diameter (Rod) Specified Width (Bar) Circumscribing Circle Diameter (see 12.5)	Tolerance, Inches (see 12.4)	
	In Any Foot or Less of Length	In Total Length of Piece
Inches	0.025	0.025 x length, feet
All	0.025	0.025 x length, feet

**Table 5B - Straightness tolerance, SI units**

Specified Diameter (Rod) Specified Width (Bar) Circumscribing Circle Diameter (see 12.5)	Tolerance, Inches (see 12.4)	
	In Any 300 mm or Less of Length	In Total Length of Piece
Millimeters	0.65	0.65 per 300 mm of length
All	0.65	0.65 per 300 mm of length

## 8. TWIST (SEE 12.6)

## 8.1 Bars and Shapes (see Figure 5)

Shall be as shown in Table 6.

**Table 6A - Tolerance on twist, inch/pound units**

Specified Width (Bars) Circumscribing Circle Diameter (see 12.5)	Tolerance, Degrees		
	Minimum Thickness Inches	In Any Foot or Less of Length	In Total Length of Piece
Inches	All	1	1 x length feet; 3 maximum
All	All	1	1 x length feet; 3 maximum

**Table 6B - Tolerance on twist, SI units**

Specified Width (Bars) Circumscribing Circle Diameter (see 12.5) Millimeters	Tolerance, Degrees		
	Minimum Thickness Millimeters	In Any 300 mm or Less of Length	In Total Length of Piece
All	All	1	1 per 300 mm of length; 3 maximum

## 9. LENGTH

Tolerance on length shall be as shown in Table 7.

**Table 7A - Tolerance on length, inch/pound units**

Circumscribing Circle Diameter (Shapes); Specified Diameter (Rod); Specified Width (Bar) Inches (see 12.5)	Tolerance, Inch, Plus Only Length Ranges, Feet		
	Up to 10, incl	Over 10 to 20, incl	Over 20
Up to 3.000, excl	1/4	5/16	3/8
3.000 to 5.000, excl	5/16	7/16	1/2
5.000 to 9.000, excl	3/8	1/2	5/8

**Table 7B - Tolerance on length, SI units**

Circumscribing Circle Diameter (Shapes); Specified Diameter (Rod); Specified Width (Bar) Millimeters (see 12.5)	Tolerance, Millimeters, Plus Only Length Ranges, Meters		
	Up to 3.0, incl	Over 3.0 to 6.0, incl	Over 6.0
Up to 75.00, excl	6.2	7.8	9.4
75.00 to 125.00, excl	7.8	10.9	12.5
125.00 to 225.00, excl	9.4	12.5	15.6

## 10. SQUARENESS OF CUT ENDS

Ends shall not deviate from square by more than 3 degrees.

## 11. SURFACE ROUGHNESS

Shall be as shown in Table 8.

**Table 8A - Surface imperfections, inch/pound units**

Specified Section Thickness Inches	Depth of Imperfection Inches, Maximum (see 12.7, 12.8)
Up to 0.250, incl	0.008
Over 0.250 to 0.500, incl	0.010
Over 0.500	0.015

**Table 8B - Surface imperfections, SI units**

Specified Section Thickness Millimeters	Depth of Imperfection Millimeters, Maximum (see 12.7, 12.8)
Up to 6.25, incl	0.20
Over 6.25 to 12.50, incl	0.25
Over 12.50	0.38

## 12. NOTES

### 12.1 Revision Indicator

A change bar (I) located in the left margin is for the convenience of the user in locating areas where technical revisions, not editorial changes, have been made to the previous issue of this document. An (R) symbol to the left of the document title indicates a complete revision of the document, including technical revisions. Change bars and (R) are not used in original publications, nor in documents that contain editorial changes only.

12.2 Allowable deviation from specified dimension when diameter of circumscribing circle is less than 7 inches when inch/pound units are used, or 175 mm when SI units are used.

12.3 Angles are measured with protractors or with gauges. As illustrated in sketch 1, a four point contact system is used, two contact points being as close to the angle vertex as practical, and the others near the ends of the respective surfaces forming the angle. Between these points of measurement, surface flatness is the controlling tolerance.



Sketch 1

12.4 When weight of piece on flat surface minimizes deviation.

12.5 The circumscribing circle diameter is the smallest circle that will completely enclose the cross-section of the extruded product.

12.6 Twist is normally measured by placing the extruded section on a flat surface and measuring the maximum distance at any point along its length between the bottom surface of the section and the flat surface. From this measurement, the deviation from true straightness of the section is subtracted. The remainder is the twist. To convert the standard twist tolerance to an equivalent linear value, the tangent of the standard tolerance is multiplied by the width of the surface of the section that is on the flat surface.

12.7 The depth of local defects, such as gouges, dents, die lines, laps, and handling marks shall be included within the minimum dimensions permitted by the tolerances of Table 1.