



AEROSPACE MATERIAL SPECIFICATION

AMS2262

REV. G

Issued 1948-05
Revised 2002-03
Reaffirmed 2013-10

Superseding AMS2262F

Tolerances
Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate

RATIONALE

This document has been reaffirmed to comply with the SAE five year review policy.

1. SCOPE:

This specification covers established manufacturing tolerances applicable to sheet, strip, and plate of nickel, nickel alloys, and cobalt alloys ordered to inch/pound dimensions. These tolerances apply to all conditions, unless otherwise noted. The term "excl" is used to apply only to the higher figure of a specified range.

1.1 Where the terms "nickel", "nickel-copper", "nickel-chromium", "nickel-molybdenum", "nickel-molybdenum-chromium", and "cobalt" are used without qualification, they refer to both non-heat-treatable and heat-treatable alloys as applicable, unless otherwise noted.

1.2 MAM 2262 is the metric version of this AMS.

2. THICKNESS:

Thickness for sheet and strip is measured at any place on widths under 1 inch, at any place 3/8 inch and over from an edge on widths 1 inch and over, and for plate at least 3/8 inch but not more than 3 inches from an edge.

2.1 Sheet:

2.1.1 Nickel, Nickel-Chromium, and Nickel-Copper Alloys: For thickness 0.018 inch and under, tolerances apply only to widths of 36 inches and under in lengths 96 inches and under. Cold rolled tolerances do not apply to precipitation-hardenable nickel-chromium alloys over 44 inches wide.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2013 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

SAE values your input. To provide feedback on this Technical Report, please visit <http://www.sae.org/technical/standards/AMS2262G>

TABLE 1

Specified Thickness Inch	Thickness Tolerance, Inch, Plus and Minus Cold Rolled Widths of 48 Inches and Under	Thickness Tolerance, Inch, Plus and Minus Cold Rolled Widths of Over 48 Inches to 60, incl	Thickness Tolerance, Inch, Plus and Minus Hot Rolled Widths of 48 Inches and Under	Thickness Tolerance, Inch, Plus and Minus Hot Rolled Widths of Over 48 Inches to 60, incl
0.010 to 0.018, incl	0.002	--	--	--
Over 0.018 to 0.025, incl	0.002	0.003	0.003	0.004
Over 0.025 to 0.034, incl	0.003	0.004	0.004	0.005
Over 0.034 to 0.056, incl	0.004	0.005	0.005	0.006
Over 0.056 to 0.070, incl	0.005	0.006	0.006	0.007
Over 0.070 to 0.078, incl	0.006	0.007	0.007	0.008
Over 0.078 to 0.093, incl	0.007	0.008	0.008	0.009
Over 0.093 to 0.109, incl	0.007	0.009	0.009	0.010
Over 0.109 to 0.125, incl	0.008	0.010	0.010	0.012
Over 0.125 to 0.140, incl	0.008	0.010	0.012	0.014
Over 0.140 to 0.171, incl	0.009	0.012	0.014	0.016
Over 0.171 to 0.187, incl	0.010	0.013	0.015	0.017

2.1.2 Nickel-Molybdenum, Nickel-Molybdenum-Chromium, and Cobalt Alloys (Widths 48 inches and Under): For specified thicknesses over 0.187 inch, plate tolerances of Table 5 apply.

TABLE 2

Specified Thickness Inch	Thickness Tolerances, Inch Plus	Thickness Tolerances, Inch, Minus
0.010 to 0.018, incl	0.002	0.002
Over 0.018 to 0.025, incl	0.003	0.003
Over 0.025 to 0.034, incl	0.004	0.004
Over 0.034 to 0.056, incl	0.005	0.005
Over 0.056 to 0.070, incl	0.006	0.006
Over 0.070 to 0.078, incl	0.007	0.007
Over 0.078 to 0.093, incl	0.008	0.008
Over 0.093 to 0.109, incl	0.009	0.009
Over 0.109 to 0.125, incl	0.010	0.010
Over 0.125 to 0.140, incl	0.013	0.010
Over 0.140 to 0.171, incl	0.016	0.010
Over 0.171 to 0.187, incl	0.018	0.010

2.2 Cold-Rolled Strip:

- 2.2.1 All Alloys: Table 3 does not apply to precipitation-hardenable nickel-chromium and nickel-molybdenum-chromium alloys for specified thicknesses over 0.025 inch or to any alloy in widths over 12 inches.

TABLE 3

Specified Thickness (T) Inch	Thickness Tolerance, Inch Plus and Minus All Widths
Up to 0.006, excl	0.10T
0.006 to 0.015, incl	0.001
Over 0.015 to 0.050, incl	0.0015
Over 0.050 to 0.093, incl	0.0025
Over 0.093 to 0.125, incl	0.004

2.3 Hot-Rolled Plate:

Minus tolerance shall be 0.010 inch for all widths and all thicknesses in all alloys; plus tolerances shall be as shown in 2.3.1 and 2.3.2.

- 2.3.1 Nickel, Nickel-Chromium, and Nickel-Copper Alloys: Tolerances shown in Table 4 are only approximate for precipitation-hardenable nickel-chromium alloys; failure to meet these tolerances shall not be cause for rejection of such alloy product.

TABLE 4

Specified Thickness (T) Inches	Thickness Tolerance, Inch, Plus Only For Widths Up to	Thickness Tolerance, Inch, Plus Only For Widths 48 to	Thickness Tolerance, Inch, Plus Only For Widths 60 to	Thickness Tolerance, Inch, Plus Only For Widths 72 to	Thickness Tolerance, Inch, Plus Only For Widths 84 to	Thickness Tolerance, Inch, Plus Only For Widths 96 to
	48 Inches, excl	60 Inches, excl	72 Inches, excl	84 Inches, excl	96 Inches, incl	
0.1875 to 0.3125, excl	0.113T	0.132T	0.150T	0.169T	0.184T	
0.3125 to 0.375, excl	0.094T	0.113T	0.132T	0.150T	0.169T	
0.375 to 0.4375, excl	0.088T	0.094T	0.113T	0.132T	0.150T	
0.4375 to 0.500, excl	0.075T	0.088T	0.094T	0.113T	0.132T	
0.500 to 0.625, excl	0.063T	0.075T	0.088T	0.094T	0.113T	
0.625 to 0.750, excl	0.057T	0.069T	0.075T	0.088T	0.094T	
0.750 to 1.000, excl	0.050T	0.057T	0.069T	0.075T	0.088T	
1.000 and over	0.050T	0.050T	0.057T	0.069T	0.075T	

- 2.3.2 Nickel-Molybdenum, Nickel-Molybdenum-Chromium, and Cobalt Alloys (Widths 48 Inches and Under): Tolerances shown in Table 5 are only approximate for precipitation-hardenable alloys; failure to meet these tolerances shall not be cause for rejection of such product.

TABLE 5

Specified Thickness (T) Inches	Thickness Tolerance, Inch, Plus Only For Width Ranges Shown, Inches Up to 48, excl	Thickness Tolerance, Inch, Plus Only For Width Ranges Shown, Inches 48 to 60, excl	Thickness Tolerance, Inch, Plus Only For Width Ranges Shown, Inches 60 to 72, excl	Thickness Tolerance, Inch, Plus Only For Width Ranges Shown, Inches 72 to 84, excl	Thickness Tolerance, Inch, Plus Only For Width Ranges Shown, Inches 84 to 96, incl
0.1875 to 0.3125, excl	0.132T	0.150T	0.169T	0.184T	0.199T
0.3125 to 0.375, excl	0.113T	0.132T	0.150T	0.169T	0.184T
0.375 to 0.4375, excl	0.094T	0.113T	0.132T	0.150T	0.169T
0.4375 to 0.500, excl	0.088T	0.094T	0.113T	0.132T	0.150T
0.500 to 0.625, excl	0.075T	0.088T	0.094T	0.113T	0.132T
0.625 to 0.750, excl	0.069T	0.075T	0.088T	0.094T	0.113T
0.750 to 1.000, excl	0.057T	0.069T	0.075T	0.088T	0.094T
1.000 and over	0.050T	0.057T	0.069T	0.075T	0.088T

3. WIDTH:

3.1 Sheet (All Alloys, Widths 60 Inches and Under):

Shall not vary in width more than +1/8 inch, -0.

3.2 Cold-Rolled Strip:

3.2.1 All Alloys:

TABLE 6

Specified Thickness Inch	Specified Width Inches	Width Tolerance, Inch Plus and Minus
Up to 0.009, incl	12 and under	0.005
Over 0.009 to 0.024, incl	12 and under	0.007
Over 0.024 to 0.075, incl	14 and under	0.007
Over 0.075 to 0.100, incl	14 and under	0.009
Over 0.100 to 0.125, incl	14 and under	0.012

3.3 Hot-Rolled Plate:

3.3.1 Nickel, Nickel-Chromium, Nickel-Copper, Nickel-Molybdenum, Nickel-Molybdenum-Chromium, and Cobalt Alloys:

3.3.1.1 Sheared Plate 240 Inches and Under in Length: Minus tolerance shall be 0.125 inch for all widths and all thicknesses; plus tolerance shall be as shown in Table 7. The minimum available width of sheared plate is 24 inches.

TABLE 7

Specified Thickness Inches	Width Tolerance, Inch, Plus Only Width Ranges, Inches Up to	Width Tolerance, Inch, Plus Only Width Ranges, Inches Over 30 to	Width Tolerance, Inch, Plus Only Width Ranges, Inches Over 72 to
	30, incl	72, incl	96, incl
0.1875 to 0.3125, excl	0.1875	0.250	0.375
0.3125 to 0.500, excl	0.250	0.375	0.375
0.500 to 0.750, excl	0.375	0.375	0.500
0.750 to 1.000, excl	0.500	0.500	0.625
1.000 to 1.250, excl	0.625	0.625	0.750

3.3.1.2 Sheared Plate Over 240 Inches in Length: Minus tolerance shall be 0.1875 inch for all widths and all thicknesses; plus tolerance shall be 0.0625 inch greater than those of Table 7.

3.3.1.3 Abrasive-Cut Plate: Standard width tolerances for abrasive-cut plate shall be ± 0.125 inch for specified thicknesses 1.250 inches and under and +0.1875 inch, -0.125 inch for specified thicknesses over 1.250 to 2.750 inches, inclusive.

3.3.2 Tolerances for width of powder or inert-arc cut plate and for diameter of machined, powder, or inert-arc cut circular plate shall be as agreed upon by purchaser and vendor.

4. LENGTH:

4.1 Sheet and Strip:

Definite lengths shall vary not more than +1/8 inch, -0 from the length ordered.

4.2 Hot-Rolled Plate:

4.2.1 Nickel, Nickel-Chromium, Nickel-Copper, Nickel-Molybdenum, Nickel-Molybdenum-Chromium, and Cobalt Alloys:

4.2.1.1 Sheared Plate: Minus tolerance shall be 0.125 inch for all lengths and all thicknesses; plus tolerances shall be as shown in Table 8.

TABLE 8

Specified Thickness Inches	Length Tolerance, Inch, Plus Only For Lengths of 24 to 60 Inches, incl	Length Tolerance, Inch, Plus Only For Lengths of Over 60 to 96 Inches, incl	Length Tolerance, Inch, Plus Only For Lengths of Over 96 to 120 Inches, incl	Length Tolerance, Inch, Plus Only For Lengths of Over 120 to 240 Inches, incl	Length Tolerance, Inch, Plus Only For Lengths of Over 240 Inches
	0.1875 to 0.3125, excl	0.1875	0.250	0.375	0.500
0.3125 to 0.500, excl	0.375	0.500	0.500	0.500	0.625
0.500 to 0.750, excl	0.500	0.500	0.625	0.625	0.750
0.750 to 1.000, excl	0.625	0.625	0.625	0.750	0.875
1.000 to 1.250, excl	0.750	0.750	0.750	0.875	1

4.2.1.2 Abrasive-Cut Plate: Standard length tolerances for abrasive-cut plate shall be ± 0.125 inch for specified thicknesses 1.250 inches and under and $+0.1875$ inch, -0.125 inch for specified thicknesses over 1.250 to 2.750 inches, inclusive.

4.2.2 Tolerances for length of powder or inert-arc cut plate shall be as agreed upon by purchaser and vendor.

5. STRAIGHTNESS:

Sheet and flat strip shall be of such straightness that the maximum edgewise curvature (depth of arc) shall be not greater than 0.050 inch in any foot of length.

6. FLATNESS:

6.1 Sheet and Flat Strip:

Shall be commercially flat unless cold worked after final heat treatment or when ordered for spinning or deep drawing.