

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 2403B

Issued 11-1-48

Revised 6-15-53

NICKEL PLATING

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for moderate corrosion and oxidations resistance.
3. TECHNICAL REQUIREMENTS:
 - 3.1 Surfaces of parts to be plated shall be smooth and substantially free from blemishes, pits, tool marks, and other irregularities.
 - 3.2 Unless otherwise specified, parts having hardness higher than Rockwell C 40 and which have been ground after heat treatment shall be suitably stress-relieved before cleaning for plating. Temperatures to which parts are heated shall be such that maximum stress-relief is obtained without reducing hardness of parts below drawing limits.
 - 3.3 Before placing parts in plating solutions, they shall have chemically clean surfaces, prepared with minimum abrasion, erosion, or pitting.
 - 3.4 Tight electrical connections shall be made and maintained for satisfactory plating.
 - 3.5 Plating shall be performed by electrodeposition of nickel from a chloride or sulfate-chloride solution containing no organic addition agents. Unless otherwise specified, nickel shall be deposited directly on the basis metal without a prior flash coating of other metal, except in the case of parts made of aluminum or aluminum alloys. A preliminary chemical coating, immersion plate and/or metal flash is permissible on aluminum and aluminum alloys.
 - 3.6 After plating, washing and drying, steel parts shall be treated as follows, unless otherwise permitted, to remove hydrogen embrittlement due to cleaning and plating.
 - 3.6.1 Parts, including roll threaded parts, cold worked after being heat treated by hardening and tempering, shall be heated to $375\text{ F} \pm 10$ in air, preferably in a circulating air furnace, and held at temperature for not less than 3 hours.
 - 3.6.2 Springs and all other parts, excluding parts covered by 3.6.3, having hardness of Rockwell C 33 or over shall be heated to $375\text{ F} \pm 10$ in air, preferably in a circulating air furnace, and held at temperature for not less than 3 hours.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."