



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 2404B

Superseding AMS 2404A

Issued 9-15-57
Revised 1-15-77

ELECTROLESS NICKEL PLATING

1. SCOPE:

- 1.1 Purpose: This specification covers the engineering requirements for electroless deposition of nickel on various materials and the properties of the deposit.
- 1.2 Application: Primarily to provide hard, ductile, wear-resistant, and corrosion-resistant surfaces for operation up to 1000°F (540°C) and to provide uniform build-up on complex shapes.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B117 - Salt Spray (Fog) Testing

ASTM B487 - Measurement of Metal and Oxide Coating Thicknesses by Microscopical Examination of a Cross Section

ASTM E290 - Semi-Guided Bend Test for Ductility of Metallic Materials

- 2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Preparation:

- 3.1.1 Welding and brazing shall be completed before parts or assemblies are plated, unless surfaces are plated to aid in joining by brazing.
- 3.1.2 Surfaces of metal parts to be plated shall be smooth and substantially free from blemishes, pits, tool marks, and other irregularities.
- 3.1.3 Surfaces of nonmetallic parts shall show no marks other than those necessary to provide a freshly abraded surface.

SAE Technical Board rules provide that: "All technical reports, including standards approved in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

3.1.4 Parts having hardness higher than 40 HRC and which have been machined or ground after heat treatment shall be suitably stress-relieved before cleaning for plating. Temperatures to which parts are heated shall be such that maximum stress-relief is obtained without reducing hardness of parts below drawing limits.

3.1.5 Parts shall have chemically clean surfaces prepared with minimum abrasion, erosion, or pitting prior to immersion in the plating solution.

3.2 Procedure:

3.2.1 Plating shall be performed by chemical deposition of an amorphous, high-nickel, low-phosphorus metallic compound on a catalytic or catalyzed surface from a chemical nickel bath. The nickel-phosphorus plate shall be deposited directly on the basis metal without a prior flash coating of other metal, unless otherwise specified.

∅ 3.2.2 The plated parts shall be removed from the plating solution, thoroughly rinsed, and dried.

3.3 Post Treatment:

3.3.1 After plating, rinsing, and drying, parts shall be heat treated as in 3.3.1.1, 3.3.1.2, or 3.3.1.3 unless they are to be post treated as in 3.3.2 or unless otherwise permitted to remove hydrogen embrittlement; heating shall be in air, preferably in a circulating-air furnace.

3.3.1.1 Parts, including roll-threaded parts, cold worked after being heat treated by hardening and tempering, springs, and other parts having hardness of 33 HRC or over, shall be heated to $375^{\circ}\text{F} \pm 15$ ($190^{\circ}\text{C} \pm 8$) and held at heat for not less than 3 hours.

3.3.1.2 Parts and assemblies, including carburized parts, which will decrease in hardness or be otherwise deleteriously affected by heating to $375^{\circ}\text{F} \pm 15$ (190°C) shall be heated to $275^{\circ}\text{F} \pm 15$ ($135^{\circ}\text{C} \pm 8$) and held at heat for not less than 5 hours.

3.3.1.3 Parts requiring special handling shall be treated as agreed upon by purchaser and vendor.

3.3.2 When specified on the drawing, parts, after plating, rinsing, and drying, shall be heated for 30 - 60 min., preferably in an inert atmosphere, at $750^{\circ}\text{F} \pm 15$ ($400^{\circ}\text{C} \pm 8$) except that parts made of aluminum or aluminum alloy shall be heated at $450^{\circ}\text{F} \pm 15$ ($232^{\circ}\text{C} \pm 8$) for not less than 4 hours.

3.4 Properties:

3.4.1 Thickness: Shall be as specified on the drawing, determined on representative parts or test panels by ∅ micrometer method, by microscopical method in accordance with ASTM B487, or other method agreed upon by purchaser and vendor.

3.4.2 Adhesion: Specimens shall show no separation of plating from the basis metal, when examined at ∅ magnification up to 6X, after being bent rapidly at room temperature, in accordance with ASTM E290, through an angle of 180 deg (3.14 rad) around a diameter equal to the nominal thickness of the specimen. Formation of cracks which do not result in flaking or blistering of the plating is acceptable.

3.4.2.1 As a referee test, plating shall show no blisters or cracks on representative steel parts or test panels after being heated in air, preferably in a circulating-air furnace, at $700^{\circ}\text{F} \pm 15$ ($370^{\circ}\text{C} \pm 8$) for 23 hr ± 1 followed by heating at $1000^{\circ}\text{F} \pm 15$ ($540^{\circ}\text{C} \pm 8$) for 60 min. ± 5 .

3.4.3 Corrosion Resistance: Steel parts or representative test panels having specified minimum plating ∅ thickness of 0.001 in. (0.03 mm) or more, shall, after plating and embrittlement-relieving, show no visual evidence of corrosion of the basis metal after being subjected for not less than 48 hr to continuous salt corrosion test conducted in accordance with ASTM B117.

3.5 Quality: Plated surfaces shall be smooth, continuous, and uniform in appearance and shall be free
∅ from frosty areas, pinholes, blisters, and other imperfections detrimental to performance of parts.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The processing vendor shall supply all samples and shall be responsible
∅ for performing all required tests. Results of such tests shall be reported to the purchaser as re-
quired by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems neces-
sary to ensure that processing conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to thickness (3.4.1) and quality (3.5) require-
∅ ments are classified as acceptance tests.

4.2.2 Periodic Tests: Tests to determine conformance to adhesion (3.4.2) and corrosion resistance (3.4.3)
∅ requirements and of cleaning and plating solutions to ensure that the deposited metal will conform to
the requirements of this specification are classified as periodic tests.

4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specifi-
∅ cation are classified as preproduction tests.

4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction
∅ test material shall be submitted to the cognizant agency as directed by the procuring activity,
the contracting officer, or the request for procurement.

∅ 4.3 Sampling: Shall be not less than the following:

∅ 4.3.1 Acceptance Tests:

∅ 4.3.1.1 Thickness: Three parts for each consecutive 8 hr of operation of the same set of solutions,
except as specified in 4.3.3.

∅ 4.3.1.2 Quality: As agreed upon by purchaser and vendor.

∅ 4.3.2 Periodic Tests and Preproduction Tests: As agreed upon by purchaser and vendor.

4.3.3 When plated parts are of such configuration or size as to be not readily adaptable to the specified
∅ tests, separate test specimens cleaned, plated, and post treated with the parts represented
may be used. For adhesion tests, such specimens shall be panels of annealed low-carbon steel ap-
proximately 0.032 x 1 x 4 in. or 1 x 25 x 100 mm and for thickness and quality tests shall be panels
of the same size and type or shall be bars approximately 0.5 in. or 10 mm in diameter and 4 in. or
100 mm long. For corrosion resistance tests, specimens shall be panels 0.062 - 0.125 in. or 1.5 -
3 mm in nominal thickness and not less than 4 in. or 100 mm long by 3 in. or 75 mm wide.

4.4 Approval:

4.4.1 Plated parts shall be approved by purchaser before parts for production use are supplied, unless such
∅ approval be waived. Results of tests on production parts shall be essentially equivalent to those on
the approved sample parts.

4.4.2 Vendor shall use manufacturing procedures, processes, and methods of inspection on production parts
∅ which are essentially the same as those used on the approved sample parts. If any change is neces-
sary in type of equipment or in established composition limits and operating conditions of process
solutions, vendor shall submit for reapproval of the process a statement of the proposed changes in
processing and, when requested, sample plated parts, test panels, or both. Production parts plated
by the revised procedure shall not be shipped prior to receipt of reapproval.