

# AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
29 West 39th Street  
New York City

AMS 2410 B

Issued 8-1-45

Revised 3-1-55

## SILVER PLATING Nickel Strike - High Bake

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily to provide a bearing surface and/or to prevent galling or seizing of metal surfaces of parts made of corrosion resistant steels or parts made of materials not deleteriously affected by high baking temperatures.
3. PREPARATION:
  - 3.1 Unless otherwise specified, roughness of surfaces to be plated shall not exceed 80 microinches, rms, prior to cleaning.
  - 3.2 Parts shall be chemically clean when immersed in plating solutions.
  - 3.3 Electrical contacts shall be made in such manner as will ensure that no chemical or immersion deposition will occur.
4. PROCEDURE:
  - 4.1 Unless otherwise specified, plating of parts shall be conducted in the following sequence, except that the nickel strike may be omitted in plating copper base alloys; process shall be approved by purchaser.
    1. Nickel Strike
    2. Silver Strike
    3. Silver Plate
  - 4.2 Unless otherwise specified, all parts shall be heated to 940-960 F after plating and held at heat for not less than 20 min. and not more than 1 hr; temperature of the parts shall not be over 400 F for more than 7 hr, and above 400 F the heating and cooling medium shall be a neutral or reducing atmosphere or a neutral or non-oxidizing molten salt bath. If such heating would lower hardness below drawing limits or otherwise deleteriously affect the parts, heating shall be at the highest practicable temperature which will maintain specified properties.
5. THICKNESS:
  - 5.1 Where "silver flash" is specified, plate thickness shall be approximately 0.0001 inch.
  - 5.2 Thickness of plate other than flash shall be as specified on drawing. If machining of plated metal is required, plate thickness as deposited shall be sufficient to allow machining of all areas of plated surfaces to the dimensions specified on the drawing.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."