

AERONAUTICAL MATERIAL SPECIFICATIONS

AMS 2416B

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 8-15-55
Revised 1-15-58

NICKEL-CADMIUM PLATING, DIFFUSED

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily to prevent corrosion of carbon and low alloy steel parts which may operate at temperatures up to 900 F. This process is not suitable for use on parts of complex shape where minimum nickel plate thickness requirements cannot be met and on parts whose hardness would be reduced below drawing requirements by heating at 640 F.
3. PREPARATION:
 - 3.1 All brazing or welding shall be completed before parts or assemblies are plated.
 - 3.2 Unless otherwise specified, parts having hardness higher than Rockwell C 40 and which have been ground after heat treatment shall be suitably stress relieved before cleaning for plating. Temperatures to which parts are heated shall be such that maximum stress relief is obtained without reducing hardness of parts below drawing limits.
 - 3.3 Before placing parts in plating solutions, they shall have chemically clean surfaces, prepared with minimum abrasion, erosion, or pitting.
4. PROCEDURE:
 - 4.1 Nickel Plating: Unless otherwise specified, consists of electrodeposition of nickel from a chloride, sulfate-chloride, or sulfamate solution containing no addition agents which might have a detrimental effect on the properties of the plate or the basis metal; stress reducing agents shall not be used unless specifically authorized by the purchaser.
 - 4.1.1 After being nickel plated, parts shall be rinsed, neutralized in alkali, and transferred directly to the cadmium plating solution, except that parts to be used for determining thickness of the nickel plate shall be neutralized in alkali, rinsed, and dried after nickel plating, and then cadmium plated as soon as possible after nickel plate thickness determination by non-destructive methods.
 - 4.2 Cadmium Plating: Consists of electrodeposition of cadmium from a cadmium cyanide solution. The cadmium shall be deposited directly on the nickel plate. Parts shall then be rinsed. Extreme care shall be exercised to avoid deposition of cadmium on any area not previously covered by nickel.
 - 4.2.1 Parts which have been used for determination of nickel plate thickness by non-destructive methods shall be cleaned and the nickel reactivated prior to cadmium plating.

Including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no attempt to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents.

Section 7C of the SAE Technical Board rules provides that: "All technical reports are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no attempt to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 4.3 Chromate Treatment: After rinsing following cadmium plating, and without drying, parts may be treated by an approved chromate process which will prevent finger-printing and staining. Parts shall then be rinsed.
- 4.3.1 If parts are not chromate treated, they shall be marked with a dye which will change color during the diffusion treatment.
- 4.4 Heating: After rinsing following marking with dye, or following chromate treatment when used, parts shall be dried and then shall be heated to $630\text{ F} \pm 10$ in air, preferably in a circulating air furnace, held at heat for not less than 30 min., and cooled in air.
5. TECHNICAL REQUIREMENTS:
- 5.1 Thickness:
- 5.1.1 Nickel Plate: Shall be 0.0002 - 0.0004 in. thick on significant surfaces of parts and not less than 0.00005 in. thick on surfaces of parts on which a controlled deposit cannot be maintained, such as holes, grooves, recesses, etc. Unless otherwise specified, uncontrolled plate thickness areas are defined as those areas not touched by a 0.75 in. diameter sphere. Thickness of nickel plate shall be determined on representative parts from each batch or on separate specimens representing parts and plated simultaneously with them, by microscopic method, micrometer measurement, magnetic test, drop test, or electro-strip method, before parts are cadmium plated.
- 5.1.2 Cadmium Plate: Shall be approximately 0.0001 - 0.0002 in. thick. Routine determination of cadmium plate thickness will not be required; the process of plating shall be controlled to produce the specified thickness.
- 5.2 Bonding:
- 5.2.1 Nickel Plate: Shall be firmly and continuously bonded to the basis metal and shall be smooth, uniform in appearance on areas of equivalent hardness and surface finish, and free from frosty areas, pin holes, nodules, blisters, and other harmful imperfections.
- 5.2.2 Cadmium Plate: Shall be firmly and continuously bonded to the nickel plate, and shall be smooth, uniform in appearance, not coarsely crystalline, and free from pin holes, porosity, blisters, nodules, pits, and other harmful imperfections.
- 5.3 Color and Appearance: Finished plate after heating as in 4.4 shall have dull matte finish, shall be free from balling when examined under magnification up to 10X, and shall be smooth to the touch. Color of chromate treated parts may vary from olive drab to black. Color of dye marking shall be characteristic of the dye used.
- 5.4 Heat Resistance: Plate on parts, or on specimens representing parts and processed through the complete cleaning and plating cycle with the parts represented, shall be capable of being heated in air, preferably in a circulating air furnace, at $700\text{ F} \pm 10$ for 23 hr followed by heating at $1000\text{ F} \pm 10$ for 1 hr without blistering or cracking on significant surfaces. Appearance of a loose powdery film which can readily be wiped off will not be cause for rejection.