

Plating, Nickel-Cadmium
Diffused

RATIONALE

AMS2416L results from a Five Year Review and update of this specification.

NOTICE

ORDERING INFORMATION: The following information shall be provided to the plating processor by the purchaser.

1) Purchase order shall specify not less than the following:

- AMS2416L
- Plating thickness desired. See 3.3.1.
- Basis metal to be plated
- Tensile strength or hardness of the basis metal
- Pre-plate stress relief to be performed by plating processor (time and temperature) if different from 3.1.1
- Special features, geometry or processing present on parts that requires special attention by the plating processor
- Minimum thickness on internal surfaces, if required. See 3.3.1.1.
- Optional: Periodic testing frequency (4.2.2) and sample quantity (4.3.3)
- Quantity of pieces to be plated

2) Parts manufacturing operations such as heat treating, forming, joining and media finishing can affect the condition of the substrate for plating, or if performed after plating, could adversely affect the plated part. The sequencing of these types of operations should be specified by the cognizant engineering organization or purchaser and is not controlled by this specification.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user." SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions. Copyright © 2010 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS2416L>**

SAE WEB ADDRESS:

1. SCOPE

1.1 Purpose

This specification covers the requirements for an electrodeposit of cadmium diffused into an electrodeposit of nickel on carbon, low-alloy, and corrosion-resistant steels.

1.2 Application

This coating has been used typically to prevent corrosion of carbon, low-alloy, and corrosion resistant steel parts that may operate in service up to 900 °F (482 °C), but usage is not limited to such applications. This process is not suitable for use on parts of complex shape where minimum nickel plate thickness requirements cannot be met and on parts whose hardness or strength would be reduced below drawing or specification requirements by heating to 640 °F (338 °C).

1.3 Safety - Hazardous Materials

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

1.4 Warning

This document includes cadmium as a plating material. The use of cadmium has been restricted and/or banned for use in many countries due to environmental and health concerns. The user should consult with local officials on applicable health and environmental regulations regarding its use.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2750 Pyrometry

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B 117 Operating Salt Spray (Fog) Testing Apparatus

ASTM B 487 Measurement of Metal and Oxide Coating Thicknesses by Microscopical Examination of a Cross Section.

ASTM B 499 Measurement of Coating Thicknesses by the Magnetic Method; Nonmagnetic Coatings on Magnetic Basis Metals

ASTM B 504 Measurement of Thickness of Metallic Coatings by the Coulometric Method

ASTM B 567 Measurement of Coating Thickness by Beta Backscatter Method

ASTM B 568 Measurement of Coating Thickness by X-ray Spectrometry

ASTM B 636 Measurement of Internal Stress of Plated Metallic Coatings With the Spiral Contractometer

ASTM E 376 Measuring of Coating Thickness by Magnetic-Field or Eddy-Current (Electromagnetic) Test Methods

3. TECHNICAL REQUIREMENTS

3.1 Preparation

3.1.1 Stress Relief Treatment

All steel parts having hardness 40 HRC or above and that are machined, ground, cold formed or cold straightened shall be cleaned to remove surface contamination and thermally stress relieved before plating for relief of residual tensile stresses. Temperatures to which parts are heated shall be such that maximum stress relief is obtained without reducing hardness of parts below drawing limits, but, unless otherwise specified, not less than 275 °F (135 °C) for not less than 5 hours for parts having hardness of 55 HRC or higher, or not less than 375 °F (191 °C) for not less than 4 hours for other parts. Residual tensile stresses have been found to be damaging during electrofinishing.

3.1.1.1 For parts, excluding nitrided parts, having a hardness of 55 HRC and above, including carburized and induction hardened parts, stress relieve at 275 °F ± 25 (135 °C ± 14) for a minimum of 5 hours.

3.1.1.2 For parts having a hardness less than 55 HRC, stress relieve at 375 °F ± 25 (191 °C ± 14) for a minimum of 4 hours. Nitrided parts fall into this category. Higher temperatures shall be used only when specified or approved by the cognizant engineering organization.

3.1.1.3 For peened parts, if stress relief temperatures above 375 °F (191 °C) are elected, the stress relief shall be performed prior to peening or the cognizant engineering organization shall be consulted and shall approve the stress relief temperature.

3.1.2 The plating shall be applied over a surface free from water breaks. The cleaning procedure shall not produce pitting or intergranular attack of the basis metal and shall preserve dimensional requirements.

3.1.3 Except for barrel plating, electrical contact points shall be as follows. For parts which are to be plated all over, locations shall be acceptable to the cognizant engineering organization. For parts which are not to be plated all over, locations shall be in areas on which plating is not required.

3.2 Procedure

3.2.1 Nickel Plating

Nickel shall be electrodeposited from a sulfamate solution, or other plating bath acceptable to the cognizant engineering organization, containing no substances that might have a detrimental effect on the properties of the plate or the basis metal; stress-reducing agents shall not be used unless authorized by the cognizant engineering organization. The nickel plate shall be deposited directly on the basis metal. A preliminary strike or flash of nickel especially on corrosion-resistant steels or similarly passive materials is permissible. A strike or flash of any metal other than nickel is prohibited. Spotting-in is not permitted.

3.2.1.1 After being nickel plated, parts shall be thoroughly rinsed and transferred directly to the cadmium plating solution. Parts to be used for determining thickness of the nickel plate shall be rinsed after neutralization in alkaline solution and dried. Parts shall be reactivated and cadmium plated as soon as possible after determination of nickel plate thickness.

3.2.1.2 Specimens to be used for determining stress in the nickel plate shall be processed in the same manner as specified for parts to be used for determining nickel plate thickness.

3.2.2 Cadmium Plating

Cadmium shall be electrodeposited from a suitable cadmium plating solution. The cadmium shall be deposited directly on the nickel plate. CAUTION: Cadmium shall not be deposited on any area not covered by nickel plate. Parts, after plating to desired thickness, shall be thoroughly rinsed and, if not subjected to conversion coating as in 3.2.3, dried.

3.2.3 Conversion Coating

After rinsing following cadmium plating and without drying, parts shall be conversion coated unless otherwise specified. Processor shall prevent fingerprints and stains. Parts shall be thoroughly rinsed and dried after conversion coating. Parts that are not treated with a conversion coating shall be marked with a suitable dye that will change color during the diffusion treatment.

3.2.4 Diffusion Treatment

Parts, after conversion coating or dyeing, shall be heated in a circulating-air furnace conforming to AMS2750 for steel tempering furnaces and having a uniformity of ± 10 °F (± 6 °C). The set temperature shall be 630 °F (332 °C). Parts shall be held at heat for not less than 30 minutes, and cooled in air. For steel parts having a hardness greater than 40 HRC, this diffusion treatment shall start within 4 hours of completion of plating.

3.3 Properties

The diffused nickel-cadmium plate shall conform to the following requirements.

3.3.1 Thickness

3.3.1.1 Nickel plate shall, except as specified in 3.3.1.1.1, be 0.0002 to 0.0004 inch (5 to 10 μm) thick on significant surfaces of parts and not less than 0.0005 inch (1.3 μm) thick on surfaces of parts on which a controlled deposit cannot be maintained, such as holes, grooves, recesses, etc; nickel plate thickness greater than 0.0004 inch (10 μm) will be permissible in high current density areas. Uncontrolled plate thickness areas are defined as those areas that cannot be touched by a 0.75-inch (19-mm) diameter sphere except for the threaded portion of externally threaded fasteners, for which thickness shall be not less than 0.0001 inch (2.5 μm). Thickness of nickel plate shall be determined, prior to cadmium plating, in accordance with ASTM B 487, ASTM B 499, ASTM B 504, ASTM B 567, ASTM B 568, ASTM E 376, or other method acceptable to the cognizant engineering organization on representative parts or on test panels processed and plated simultaneously with the parts. See 4.3.4.2.

3.3.1.1.1 If nickel plate thickness greater than 0.0002 to 0.0004 inch (5 to 10 μm) is desired, such thickness may be specified by this specification number followed by a dash and a number indicating the minimum nickel plate thickness in ten-thousandths of an inch (2.5 μm); a tolerance of +0.0002 inch (+5 μm) will be permitted when the minimum thickness is 0.0003 inch (7.6 μm) and +0.0003 inch (+7.6 μm) will be permitted when the minimum thickness is 0.0004 inch (10 μm) or more. Thus, AMS2416/3 indicates nickel plate thickness of 0.0003 to 0.0005 inch (7.6 to 12.5 μm) and AMS2416/5 indicates nickel plate thickness of 0.0005 to 0.0008 inch (12.7 to 20 μm).

3.3.1.2 Cadmium Plate

Before the diffusion treatment of 3.2.4, thickness shall be 0.0001 to 0.0003 inch (2.5 to 7.6 μm).

3.3.2 Heat Resistance

Representative parts or specimens as in 4.3.4.1 shall show no cracks or blisters in the plate after being heated in air, preferably in a circulating-air furnace, as specified in 3.3.2.1 and 3.3.2.2. The presence of weakly adhering oxide scale is acceptable.

3.3.2.1 Heat to 700 °F \pm 10 (371 °C \pm 6), hold at heat for 23 hours \pm 0.5, transfer without intentional cooling to a furnace at 1000 °F \pm 10 (538 °C \pm 6), hold at heat for 60 minutes \pm 5, and cool to room temperature.

3.3.2.2 Heat to 700 °F \pm 10 (371 °C \pm 6), hold at heat for 2 hours \pm 0.25, transfer without intentional cooling to a furnace at 1000 °F \pm 10 (538 °C \pm 6), hold at heat for 2 hours \pm 0.25, and cool to room temperature.

3.3.3 Corrosion Resistance

Parts, other than externally threaded fasteners, or test specimens as in 4.3.4.1 shall show no visual evidence of corrosion of the basis metal, determined by exposure for 96 hours to salt spray corrosion test conducted in accordance with ASTM B 117. This requirement applies to parts or specimens both after diffusion heating as in 3.2.4 and after heat resistance test of 3.3.2.1.

3.3.3.1 For externally threaded fasteners, unless otherwise permitted by the cognizant engineering organization, representative parts shall show no visual evidence of corrosion of the basis metal, determined by exposure for 96 hours to salt spray corrosion test conducted in accordance with ASTM B 117. This requirement applies to parts after diffusion heating as in 3.2.4.

3.3.4 Nickel plate stress shall be in the range of 5000 psi (34 MPa) in compression to 15 000 psi (103 MPa) in tension, determined in accordance with ASTM B 636 on specimens having nickel plate thickness of 0.0003 inch (7.6 μ m) or greater. See 3.2.1.2.

3.4 Quality

3.4.1 Nickel plate shall be firmly and continuously bonded to the basis metal and shall be free of delamination within the plating, smooth, uniform in appearance on areas of equivalent hardness and surface finish, and free from frosty areas, pin holes, nodules, blisters, and other imperfections detrimental to performance of the plate.

3.4.2 Cadmium plate shall be firmly and continuously bonded to the nickel plate and shall be uniform in appearance and free from pin holes, porosity, blisters, nodules, pits, and other imperfections detrimental to performance of the plate.

3.4.3 Diffused nickel-cadmium plate shall have a smooth, dull, matte finish, shall be free from balling, when examined under magnification up to 10X, and shall be smooth to the touch. Color of conversion-coated parts may vary. Color need not be uniform on any one part but mottled, blotched, or sharply streaked areas are not acceptable. Color of dye marking shall be characteristic of the dye used.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The processor shall supply all specimens for processor's tests and shall be responsible for the performance of all required tests. Where parts are to be tested, such parts shall be supplied by purchaser. The cognizant engineering organization reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that processing conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Thickness of nickel plate (3.3.1.1) and quality (3.4) are acceptance tests and shall be performed on parts, or specimens representing parts when permitted herein from each lot. See 4.3.4.1.

4.2.2 Periodic Tests

Thickness of cadmium plate (3.3.1.2), heat resistance (3.3.2.1), corrosion resistance (3.3.3), and nickel plate stress (3.3.4) are periodic tests and shall be performed in any quarter that parts are processed. Tests of cleaning and plating solutions are periodic tests and shall be performed at a frequency established by the processor unless frequency of testing is specified by the cognizant engineering organization. See 4.4.3 and 8.3.

4.2.3 Preproduction Tests

All property verification tests (3.3) are preproduction tests and shall be performed prior to or on the initial shipment of plated parts to a purchaser and when the cognizant engineering organization requires confirmatory testing.

4.3 Sampling for Testing

4.3.1 Sampling for acceptance testing shall be not less than the following: a lot shall be all parts of the same part number plated to the same specified thickness range, in the set of solutions processed in a continuous operation or within a 24-hour period, and presented for processor's inspection at one time.

4.3.2 Acceptance Tests

Test samples shall be selected randomly from all parts in the lot. Unless the cognizant engineering organization provides a sampling plan, the minimum number of samples shall be as shown in Table 1.

TABLE 1 - SAMPLING FOR ACCEPTANCE TESTS

Number of Parts in Lot	Quality and Thickness
Up to 6	All
7 to 15	7
16 to 40	10
41 to 110	15
111 to 300	25
301 to 500	35
501 to 700	50
701 to 1200	75
over 1200	125

4.3.3 Periodic Tests

Sample size shall be two for corrosion resistance. Sample quantity for other periodic tests shall be at the discretion of the processor unless otherwise specified by the cognizant engineering organization or herein.

4.3.4 Sample Configuration

4.3.4.1 Separate test specimens may be used under any one of the following circumstances: The plated parts are of such configuration or size as to be not readily adaptable to specified tests, nondestructive testing is not practical on actual parts, or it is not economically acceptable to perform destructive tests on actual parts. Except as specified below, acceptance test specimens shall be made of the same generic class of alloy as the parts, established in accordance with AS2390, distributed within the lot, cleaned, plated, and post treated with the parts.

4.3.4.2 For thickness tests, specimens shall be nominally 1/32 x 4 x 1 inch (0.8 x 102 x 25 mm) or bars approximately 0.5 inch (13 mm) in diameter and 4 inches (102 mm) long.

4.3.4.3 For corrosion tests, specimens shall be annealed carbon or low-alloy steel panels 0.062 to 0.125 inch (1.57 to 3.18 mm) in nominal thickness and not less than 4 inches (102 mm) long by 3 inches (76 mm) wide, except that, when parts being plated are externally threaded fasteners, actual parts shall be used unless otherwise permitted by the cognizant engineering organization.

4.4 Approval

4.4.1 The process and control factors, a preproduction sample plated part, or both, whichever is specified, shall be approved by the cognizant engineering organization before production parts are supplied.

4.4.2 If the processor makes a significant change to any material, process, or control factor from that which was used for process approval was based, all preproduction tests shall be performed and the results submitted to the cognizant engineering organization for process reapproval unless the change is approved by the cognizant engineering organization. A significant change is one that, in the judgment of the cognizant engineering organization, could affect the properties or performance of the parts.

4.4.3 Control factors shall include, but not be limited to, the following:

- Surface preparation and cleaning procedures
- Surface activation procedures
- Plating bath composition and composition control limits
- Plating bath temperature limits and controls
- Current/voltage limits and controls
- Post treatment time and temperature
- Post-treatment bath composition and limits
- Method for testing plating thickness
- Periodic test plan for cleaning and processing solutions. See 8.3.

4.5 Reports

The processor of plated parts shall furnish with each shipment a report stating that the parts have been processed and tested in accordance with specified requirements and that they conform to the acceptance test requirements. This report shall include the purchase order number, lot number, AMS2416L, part number, and quantity.