

# AEROSPACE MATERIAL SPECIFICATION

**SAE** AMS-2431/3

REV  
A

Issued 1988-04-01  
Revised 1991-01-01

Superseding AMS-2431/3

Submitted for recognition as an American National Standard

## PEENING MEDIA Conditioned Carbon Steel Cut Wire Shot

1. **SCOPE:** This specification, in conjunction with the general requirements covered in AMS-2431, establishes the requirements for conditioned carbon steel cut wire shot to be used for peening of metal parts.

2. **APPLICABLE DOCUMENTS:** See AMS-2431.

3. **TECHNICAL REQUIREMENTS:**

3.1 Conditioned carbon steel cut wire shot shall conform to AMS-2431 and the requirements specified herein.

3.2 **Composition:** Shall conform to the following percentages by weight:

	min	max
Carbon	0.45	0.75
Manganese	0.60	1.20
Silicon	0.10	0.30
Phosphorus	--	0.045
Sulfur	--	0.050

3.2.1 **Hardness:** Not less than 95% of the readings, using a microhardness tester, shall be at or above the minimum value for the shot size as specified in Table I. The hardness testing shall be performed after the shot has been conditioned for shape.

3.2.2 **Wire Quality:** Shot shall be manufactured from wire that is free from shear cracks and laps and shall not contain excessive seams or burrs.

3.2.3 **Weight:** Fifty pieces shall conform to requirements of Table 1.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

3.2.4 Contamination: Shot shall be clean and free of dirt, grit, or grease.

3.3 Workmanship:

3.3.1 Shape: Shall be predominantly spherical, as a result of conditioning, with no sharp edges allowed.

3.3.2 Conditioning: Shall be accomplished by impacting the cut wire against a hardened steel plate until a predominantly round condition has been accomplished.

3.4 Size: Shall conform to the requirements of Table 1.

3.5 Test Methods and Procedures:

3.5.1 Composition: Shall be determined in accordance with ASTM E 751.

3.5.2 Hardness: Shall be determined in accordance with ASTM E 384.

3.5.3 Size: The size of shot shall be determined by the use of wire with a mean diameter as specified in Table 1.

4. QUALITY ASSURANCE PROVISIONS: See AMS-2431 and the following:

4.1 Sampling and Testing: Two inspection lots of 800 grams each shall be selected from separate containers chosen at random. Each sample shall be split to the following test quantities by the use of a sample splitter:

4.1.1 Composition: Not less than two samples from each inspection lot.

4.1.2 Hardness: Twenty microhardness readings shall be made from each sample with no more than 1 impression from any single shot.

4.1.2.1 Samples for microhardness testing shall be prepared by encapsulating a single layer of shot in a plastic mount and polishing down to nominal half spheres.

4.1.3 Weight: Two 60 gram samples for weight determination.

4.1.4 Shape: A sample shall consist of approximately 100 pieces taken at random from each inspection lot and a visual count, using 20X magnification, shall be taken to determine the percentage of partially conditioned shot.

5. PREPARATION FOR DELIVERY: See AMS-2431 and the following:

5.1 Packaging: Steel shot shall be packaged, in units of 50 pounds (23 kg), in plastic lined bags or boxes.

6. ACKNOWLEDGMENT: See AMS-2431.

7. REJECTIONS: See AMS-2431.