

# AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
29 West 39th Street  
New York City

## AMS 2450<sub>B</sub>

Issued 1-1-42

Revised 10-1-51

### SPRAYED METAL FINISH Aluminum

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for air-cooled cylinder assemblies, but may be used on other parts where applicable.
3. PREPARATION:
  - 3.1 Completely remove all oil and grease by the vapor degreasing method, or by other similar methods of equal cleaning power.
  - 3.2 Blast with No. 18 (0.039-in.), No. 20 (0.033-in.) or No. 25 (0.028-in.) refractory grit, or with No. 30 (0.023-in.), No. 35 (0.020-in.) or No. 40 (0.017-in.) hard, angular silica or flint sand, which shall be free from oil, grease, dust, moisture, and other foreign substances. The above designations are standard sieve numbers and sieve openings (in inches) in accordance with ASTM E11-39.
  - 3.3 No. 35 (0.020-in.) steel grit may be used for blasting steel but shall not be used on aluminum alloys.
  - 3.4 If compressed air is used as the blasting force, it shall be essentially free from oil and water.
  - 3.5 Extreme care shall be exercised that products of corrosion and foreign materials are thoroughly removed by the blasting and the surface roughened to attain a good bond for the sprayed aluminum. Remove all dust and particles after blasting by blowing with high pressure clean dry air.
  - 3.6 Blasted surfaces shall be kept absolutely clean and handled only with protected hands.
4. PROCEDURE:
  - 4.1 Sprayed metal coating shall be applied as soon as possible after the surfaces have been blasted.
  - 4.2 The aluminum shall be applied with an approved metal spray gun in such a manner as to insure complete coverage of the entire surface without depositing an unnecessarily heavy coating.
  - 4.3 All surfaces exposed after the parts are assembled shall be sprayed, unless otherwise noted, with metallic aluminum conforming to the latest issue of AMS 4180.
5. QUALITY: Sprayed coating shall be of fine texture, close-grained, as dense as possible, and free from unatomized particles of metal.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."