

Plating, Brush, Non-Cyanide Silver  
General Purpose

RATIONALE

AMS 2451/8A is a Five Year Review and update of this specification.

1. SCOPE

1.1 Purpose

This specification covers the requirements for brush plating of noncyanide silver by electrodeposition.

1.2 Application

This process has been used typically to lower electrical contact resistance, prevent galling or seizing of surfaces of parts to improve corrosion resistance of steel parts and to repair silver deposits but usage is not limited to such applications.

1.3 Safety - Hazardous Materials

See AMS 2451.

2. APPLICABLE DOCUMENTS

See AMS 2451.

3. TECHNICAL REQUIREMENTS

See AMS 2451.

3.1 Procedure

3.1.1 Silver shall be electrodeposited from a noncyanide silver brush plating solution in accordance with processing instructions from the solution manufacturer.

3.1.2 A preliminary strike or bonding layer of nickel and copper, palladium or gold may be used.

3.2 Properties

3.2.1 Thickness

Where silver flash is specified, plate thickness shall be approximately 0.0001 inch (2.5 µm).

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
**SAE WEB ADDRESS:** http://www.sae.org

**SAE values your input. To provide feedback  
on this Technical Report, please visit  
<http://www.sae.org/technical/standards/AMS2451/8A>**