

ANODIC TREATMENT OF TITANIUM AND TITANIUM ALLOYS

1. SCOPE:

1.1 **Purpose:** This specification establishes the engineering requirements for producing an electrolytic conversion (anodic) coating on titanium and titanium alloys and the properties of the coating.

1.2 **Application:** Type 1 is used primarily as a lubricating and antigalling coating for elevated-temperature forming of titanium and titanium alloys. Type 2 is used primarily for protection against galling and galvanic corrosion, for improved wear resistance, and for pretreatment in the application of dry film lubrication.

1.3 **Classification:** Coatings are classified by end-product application, as follows:

Type 1 - As a coating for elevated-temperature forming.

Type 2 - As an antigalling coating without additional lubrication or as a pretreatment for dry film lubricants. Such coatings also are compatible with hypergolic propellants such as hydrazine-unsymmetrical dimethylhydrazine and nitrogen tetroxide (See 8.2), and are electrically semiconductive.

1.3.1 Type 2 shall be furnished unless type 1 is specified.

1.4 **Safety - Hazardous Materials:** While the materials, methods, applications and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 3084 - Solid Film Lubricant, Space Application, Minimal Outgassing

AMS 4911 - Titanium Alloy Sheet, Strip, and Plate, 6Al - 4V, Annealed

AMS 4928 - Titanium Alloy Bars, Forgings, and Rings 6Al - 4V, Annealed,
120,000 psi (827 MPa) Yield Strength

2.2 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103.

ASTM B 117 - Salt Spray (Fog) Testing

ASTM D 2714 - Calibration and Operation of the Alpha Model LFW-1 Friction
and Wear Testing Machine

2.3 U.S. Government Publications: Available from Commanding Officer, Naval
Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Specifications:

MIL-L-8937 - Lubricant, Solid Film, Heat Cured, Corrosion Inhibiting

MIL-P-26539 - Propellant, Nitrogen Tetroxide

MIL-P-27402 - Propellant, Hydrazine-Uns-Dimethylhydrazine
(50% N₂H₄ - 50% UDMH)

MIL-L-81329 - Lubricant, Solid Film, Extreme Environment

2.3.2 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Solutions:

3.1.1 Electrolyte: Shall be an alkaline solution with pH of 13 or higher.

3.2 Equipment:

3.2.1 Tanks: Shall be of unlined steel.

3.2.2 Fixtures: Wire, hooks, clamps, and racks used to suspend parts shall be of titanium or titanium alloys. Protection at the air/liquid interface is not required.

3.3 Preparation:

- 3.3.1 Cleaning: Parts shall be thoroughly cleaned to ensure that all surfaces are free from grease, oil, soap, alkali, or other contaminants which would cause unacceptable coatings. The use of halogenated solvents is prohibited.
- 3.3.2 Racking: Direct current (DC) processing shall be used. Parts shall be suspended on one electrode with the tank serving as the other electrode.
- 3.3.2.1 Racks and clamps shall have any anodic film removed from contact areas before being reused.
- 3.3.3 Attachment and Contact: Parts shall be firmly attached to the racks. Contact areas shall be kept as small as possible and, when practicable, shall be on surfaces not required to be coated. When parts are to be coated all over, contacts shall be located in areas indicated on the drawing. Parts shall, insofar as practicable, be hung so as to avoid gas entrapment during processing.

3.4 Procedure:

- 3.4.1 Processing: The cleaned and racked parts shall be immersed in the electrolyte. The parts shall be the anode and the tank shall serve as the cathode. Direct current shall be applied with the voltage being raised manually or automatically to maintain the required current density during processing. Completion of the process is indicated by total decay of the amperage (zero amperage).
- 3.4.1.1 Complex parts should be agitated while totally immersed in the electrolyte in order to minimize entrapment of air in pockets and blind holes and should be repositioned periodically to bring the electrolyte into contact with uncoated areas and to prevent attack at the electrolyte/air interface of such pockets and blind holes.
- 3.4.2 Rinsing and Drying: After anodizing, parts shall be rinsed thoroughly in cold, running tap water; rinsed in clean, hot water; and dried.

3.5 Properties: Coating shall conform to the following requirements:

3.5.1 Coating Thickness:

- 3.5.1.1 Type 1: Shall be such that the dimensional increase will be 0.0002 - 0.0004 inch (5 - 10 μm) per surface, determined by measuring at the same locations with micrometers accurate to 0.0001 inch (2.5 μm) before and after anodizing, and dividing by two if opposite surfaces are anodized.
- 3.5.1.2 Type 2: Shall be such that there is no measurable dimensional change.

- 3.5.2 Corrosion Resistance: When specified, anodized parts or test specimens as in 4.3.1.1 shall withstand exposure for 336 hours to salt spray test conducted in accordance with ASTM B 117 without showing corrosion on significant surfaces or more than a few scattered corrosion pits visible without magnification on other surfaces.
- 3.5.3 Wear Resistance (Type 2): Test rings and blocks made of AMS 4928 titanium alloy anodized in accordance with this specification and coated with 0.0003 - 0.0005 inch (7.6 - 12.7 μm) of AMS 3084, MIL-L-8937, or MIL-L-81329 solid film lubricant shall have an average life of 75,000 oscillatory cycles, determined in accordance with 4.5.1.
- 3.5.4 Propellant Compatibility: When specified, Type 2 anodic coating shall not react, dissolve, disperse, change propellant color, or show any other evidence of deterioration during and after 30 days exposure to MIL-P-27402 hydrazine-unsymmetrical dimethylhydrazine and MIL-P-26539 nitrogen tetroxide, determined in accordance with 4.5.2 (See 8.2). Persistent gas escape or continuous streaming of bubbles from the anodic coating which results in a pressure increase exceeding 50 psi (345 kPa), when immersed in non-agitated propellant, shall be evidence of incompatibility.
- 3.6 Quality: Anodic coating, as received by purchaser, shall be continuous, smooth, adherent to basis metal, uniform in texture and appearance, and free from burned or powdery areas, loose films, discontinuities, such as breaks or scratches, except at contact points, or other damage or imperfections detrimental to performance of the coating.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection: The coating vendor shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.6. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the coating conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests for coating thickness (3.5.1.1) of Type 1, corrosion resistance (3.5.2) when specified, and quality (3.6) are acceptance tests and shall be performed on each lot.
- 4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the first-article shipment of coated parts to a purchaser, when a change in material and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.
- 4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring agency, contracting officer, or request for procurement.

- 4.3 Sampling and Testing: Shall be as follows; the number of specimens to be sampled shall be the minimum number of specimens tested. A lot shall be all parts made of the same material, processed in the same set of solutions under the same conditions, in not longer than eight consecutive hours and presented for vendor's inspection at one time:
- 4.3.1 For Acceptance Tests: Sufficient anodized parts shall be selected at random from each lot or representative test specimens shall be prepared to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than two.
- 4.3.1.1 Corrosion resistance test specimens, when required, shall be AMS 4911 titanium alloy sheet 0.020 - 0.063 inch (0.51 - 1.60 mm) thick, and approximately 3 inches (76 mm) wide by 6 inches (152 mm) long. Separate specimens, if used, shall be processed with the work they represent.
- 4.3.2 For Preproduction Tests: As agreed upon by purchaser and vendor.
- 4.4 Approval:
- 4.4.1 Sample coated parts shall be approved by purchaser before parts for production use are supplied, unless such approval be waived by purchaser. Results of tests on production parts shall be essentially equivalent to those on the approved sample parts.
- 4.4.2 Vendor shall use manufacturing procedures, processes, and methods of inspection on production parts which are essentially the same as those used on the approved sample parts. If necessary to make any change in type of equipment or in established composition limits and operating conditions of process solutions, vendor shall submit for reapproval of the process a statement of the proposed changes in processing and, when requested, sample coated parts, and/or test specimens. Production parts coated by the revised procedure shall not be shipped prior to receipt of reapproval.
- 4.5 Test Methods:
- 4.5.1 Wear Resistance:
- 4.5.1.1 Equipment: A block-on-ring test machine calibrated and operated in accordance with ASTM D 2714.
- 4.5.1.2 Procedure: Mount an anodized and dry-film-lubricated AMS 4928 test ring on the block-on-ring test machine according to manufacturer's instructions. Place sufficient weight on the bale rod to achieve 630 pounds normal force (2802 N) when load is applied. Start machine. After one minute, gently apply load to the lever system. Terminate the test when the coefficient of friction equals 0.20. Repeat the room temperature test twice using new anodized and lubricated test blocks and rings in each test.