

SURFACE TREATMENT OF POLYTETRAFLUOROETHYLENE

Bonding Preparation

1. SCOPE:

1.1 Purpose: This specification covers the engineering requirements for preparing surfaces of polytetrafluoroethylene for bonding and the properties resulting from the treatment.

1.2 Application: Primarily for rendering surfaces of parts capable of supporting a high strength adhesive bond. The bonding preparation can affect the electrical properties of the polytetrafluoroethylene and this should be considered before using it for treatment of electronic components.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification, to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 3690 - Adhesive Compound, Epoxy, Room Temperature Curing

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D897 - Tensile Properties of Adhesive Bonds

ASTM D1002 - Strength Properties of Adhesives in Shear by Tension Loading
(Metal-to-Metal)

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

AMS 2491C

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Material: The surface treating agent shall be a solution of sodium or other alkali metal in anhydrous liquid ammonia or tetrahydrofuran-naphthalene or other suitable solvent.

3.1.1 Safety Precaution: Sodium metal reacts violently with water. Tetrahydrofuran solvent is highly flammable. Therefore, it is recommended that persons handling these materials be experienced or trained in their use.

3.2 Preparation: Parts to be treated shall be cleaned of all dirt, grease, oil, and other contamination. Cleaned parts shall be thoroughly dried prior to surface treatment.

3.3 Procedure: The clean, dry parts shall be exposed to the surface treating agent until all surfaces to be bonded display a uniform color.

3.4 Post-Treatment: The treated parts shall be cleaned and thoroughly dried. A suitable cleaning technique is to immerse parts in acetone, then water, followed by a final rinse with clean, anhydrous acetone.

3.4.1 Treated parts not to be bonded immediately shall be packaged in heat-sealed polyethylene bags in a manner which will prevent exposure to ultraviolet light and surface contamination.

3.5 Properties: Treated parts shall conform to the following requirements:

3.5.1 Color: Treated surfaces of parts shall have a uniform, dull, dark brown-to-black color.

3.5.2 Tensile and Shear Strengths: Representative specimens of surface-treated polytetrafluoroethylene which have been bonded to the applicable aluminum specimens with an epoxy adhesive compound conforming to AMS 3690 shall have the following properties:

3.5.2.1 Tensile Strength: Shall be not lower than 1000 psi (7 MPa) at 70° - 75°F (20° - 25°C), determined in accordance with ASTM D897 on specimens prepared by bonding a treated polytetrafluoroethylene disc approximately 0.030 in. (0.75 mm) thick between the two halves of a standard aluminum alloy tensile test specimen.

- 3.5.2.2 Shear Strength: Shall be not lower than 1000 psi (7 MPa) at 70° - 75°F (20° - 25°C), determined in accordance with ASTM D1002 on specimens prepared by bonding a treated polytetrafluoroethylene strip not greater than 0.030 in. (0.75 mm) in thickness between standard aluminum alloy lap shear plates.
- 3.6 Quality: Surfaces of treated parts shall be uniform in texture and appearance. There shall be no bare or definite lighter colored areas.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection: The processing vendor shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the processing conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests to determine conformance to requirements for color ∅ uniformity (3.5.1), shear strength (3.5.2.2), and quality (3.6) are classified as acceptance tests and shall be performed to represent each lot.
- 4.2.2 Periodic Tests: Tests to determine conformance to requirements for tensile strength (3.5.2.1) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.
- 4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and ∅ shall be performed prior to or on the initial shipment of treated parts to a purchaser, when a change in material and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.
- 4.2.3.1 For direct U. S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.
- 4.3 Sampling: Shall be as agreed upon by purchaser and vendor.

AMS 2491C

4.4 Approval:

4.4.1 Parts treated in accordance with this specification shall be approved by purchaser before parts for production use are supplied, unless such approval be waived by purchaser. Results of tests on production parts shall be essentially equivalent to those on the approved sample.

4.4.2 Vendor shall use ingredients, manufacturing procedures, and methods of inspection on production parts which are essentially the same as those used on the approved sample parts. If necessary to make any change in ingredients or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in material or processing and, when requested, sample processed parts, test specimens, or both. Production parts treated by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Reports: The vendor of treated parts shall furnish with each shipment three copies of a report showing the results of tests to determine conformance to the acceptance test requirements and, when performed, to the periodic test requirements and stating that the processed parts conform to the other technical requirements of this specification. This report shall include the purchase order number, AMS 2491C, manufacturer's identification, lot number, part number, and quantity.

4.6 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the processed parts may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the parts represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Treated parts shall be handled and packaged in such a manner as will ensure that the required physical characteristics and properties of the treated parts are preserved.

5.2 Packages of treated parts shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the parts to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.

5.3 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-794, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.1 and 5.2 will be acceptable if it meets the requirements of Level C.