

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 2503A

Issued 10-15-46
Revised 10-1-51

BLACK FINISHING Low Baking

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for parts which do not exceed a temperature of 350 F.
3. PREPARATION: Before parts are painted they shall be prepared in accordance with the following requirements.
 - 3.1 Aluminum and Aluminum Alloys: Both wrought and cast parts shall be treated in accordance with AMS 2470 immediately before the first priming coat.
 - 3.1.1 Aluminum Assemblies: Aluminum alloy parts, which with other materials constitute assemblies, shall be anodized in accordance with AMS 2470 before assembling with the other materials. Assemblies with other metals may be anodized if the other metals are insulated.
 - 3.2 Magnesium Alloys: Both wrought and cast parts shall be treated in accordance with AMS 2475 immediately before the first priming coat. No machining of external surfaces shall be done after this treatment.
 - 3.3 Steel: Cadmium plated parts shall be thoroughly neutralized, before priming, in accordance with AMS 2400. Unplated parts shall be cleaned to remove all oil, dirt, and rust, then treated in accordance with AMS 2480 immediately prior to the first priming coat.
4. PROCEDURE:
 - 4.1 Priming Coat: A coat of zinc chromate primer conforming to AMS 3110 shall be applied to all metallic materials requiring enameling, immediately after the treatment required in Section 3, except that anodized rivets shall not be primed as details.
 - 4.1.1 When there are intervening operations between the first prime and the finish coats, such as assembling or additional machining, the parts shall be thoroughly cleaned by spraying with clean naphtha, or other solvent of low volatility, and then given another coat of zinc chromate primer before the first coat of enamel is applied.
 - 4.2 Baking: Each coat of primer shall be baked at 250-300 F, unless a lower temperature is approved for specific parts.
 - 4.3 Enamel Coat: Three coats of black enamel conforming to AMS 3120 shall be applied on magnesium alloys for applications other than engines, and two coats on all other metals. Two coats shall be applied on magnesium alloys to be used on engines. Each coat of enamel shall be thoroughly baked at a temperature not exceeding 300 F, or preliminary coats may be air-dried dust free, and final coat baked firm and hard at a temperature not exceeding 300 F.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will issue no license of patents, patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."