

AEROSPACE MATERIAL SPECIFICATIONS

AMS 2515A

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 1-15-61
Revised 1-15-63

POLYTETRAFLUOROETHYLENE RESIN COATING Low Build, 700 - 750 F (370 - 400 C) Fusion

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily as a coating on metal parts to produce a fused polytetrafluoroethylene resin surface providing dry lubrication, high heat stability, and good corrosion protection. Applicable primarily to parts which operate at temperatures not higher than 525 F (275 C) for limited periods or 475 F (245 C) for extended periods. The preheating temperature for steels and the fusing temperature may result in some softening of metals which have been cold worked or have been given final heat treatment at temperatures lower than these temperatures.
3. MATERIAL: The coating material shall be a dispersion of polytetrafluoroethylene resin solids in a water medium and shall be unpigmented unless colored material is specified.
 - 3.1 When multiple coatings are applied as in 4.3 and 4.4 to a maximum total dry film thickness of 6.0 mils, each coat shall be free from cracks after fusing at 700 - 750 F (371.1 - 398.9 C) when examined under 40x magnification.
4. PROCEDURE:
 - 4.1 Surface Preparation: Surfaces to be coated shall be degreased and then shall be chemically cleaned or lightly abrasive blasted, cleaned to remove abrasive particles, and air dried.
 - 4.2 Preheating: Immediately prior to coating, metals other than aluminum, magnesium, and copper shall be preheated to 750 F + 10 (398.9 C + 5.6) to produce a light oxide film and remove any organic contamination and then air cooled.
 - 4.3 Coating:
 - 4.3.1 Primer: A primer resin coat of 0.2 - 0.4 mil dry film thickness shall be applied to the oxidized metal surfaces and fused in accordance with 4.4.
 - 4.3.2 Finish: The finish resin coating material shall be applied to the primed surfaces in increments not greater than 1.0 mil as required to yield a total dry film thickness not greater than 6.0 mils. Each coat shall be fused before application of the succeeding coat. For best corrosion properties, coated surfaces shall be sanded and cleaned between coats.
 - 4.3.3 The coating thickness shall be as specified on the drawing.

including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no obligation to conform to or be guided by any technical report. In formulating and adopting technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the reports are responsible for protecting themselves against liability for infringement of patents.

Section 8.3 of the SAE Technical Board rules provides that: "All technical reports are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no obligation to conform to or be guided by any technical report. In formulating and adopting technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the reports are responsible for protecting themselves against liability for infringement of patents."

- 4.4 Fusing: The resin coating shall be air dried to a dry, non-glossy appearance or forced-heat dried at 180 - 200 F (82.2 - 93.3 C) for 5 - 10 minutes. The dried coating shall be fused at 700 - 750 F (371.1 - 398.9 C) until fusing is complete.
- ∅ Fusing is complete when the milk-white (for unpigmented material) air-dried film changes to a clear fused film. Fusing time will vary depending on the mass of metal being coated. For maximum coating toughness, the fused coating shall be quenched in cold water after the final fusing cycle. Adequate ventilation shall be provided in furnace areas to prevent inhalation of toxic fumes.
- 4.5 Repair of Damaged Areas: Damaged areas shall be sanded to a feather edge. If basis metal is exposed, a new primer application shall be used. As many 1 mil coats as required to build the film to its original thickness shall be applied. Each coat shall be fused before application of the subsequent coat. Care shall be taken to remove any overspray of primer from the original top coat and to
- ∅ apply the resin coating well beyond the perimeter of the damaged area. After air drying, repaired areas shall be fused by means of an open flame. In fusing, heating to a temperature above that at which the coating changes to a clear fused film shall be avoided; bright glowing spots in the film are evidence of overheating and decomposition of the resin. Flame fusing shall be performed only under a hood or forced draft ventilation.
5. TECHNICAL REQUIREMENTS:
- 5.1 Adhesion: A representative coated 0.250 in. diameter rod, processed with each lot of parts, shall show no evidence of chalking, blistering, or loss of adhesion of coating when cycled in accordance with the latest issue of MIL-STD-202, Method 102, Condition C, except that the cycling temperature range shall be -80 F (-62.2 C) to +500 F (+260 C).
- 5.2 Coefficient of Friction: The coating shall have a coefficient of friction not higher than 0.1 when tested with a Timken Tester at a temperature of 77 F (25 C), a speed of 25 fpm, and a load of 10 pounds.
- 5.3 Corrosion Resistance: A representative part or test panel processed to a dry film thickness of 3.0 - 4.0 mils shall withstand 168 hr exposure to salt spray
- ∅ without evidence of deterioration of the coating or corrosion of the basis metal; salt spray test shall be conducted in accordance with the issue of ASTM B117 listed in the latest issue of AMS 2350.
- 5.4 Water Vapor Resistance: A panel of low carbon steel, AMS 5040, or equivalent,
- ∅ processed to a dry film thickness of 4.5 - 6.0 mils shall show no blisters in the film and no incipient rusting of the basis metal when exposed to boiling water vapor for 5 hours.
- 5.4.1 The specimen shall be placed horizontally, with coated side down, across the
- ∅ top of a 400 ml beaker maintained approximately half full of gently boiling water.
6. QUALITY: The coating shall be smooth, uniform, and free from craters, pin holes, sags, runs, bubbles, heavy edges, foreign materials, and other imperfections detrimental to performance of parts.