

SAE-AMS2643

## ADOPTION NOTICE

SAE-AMS2643, "Titanium Alloys, Chemical Etch Inspection Procedure, Structural Examination," was adopted on October 3, 1994, for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: ASC/ENOS, 2664 Skyline Drive., Wright-Patterson AFB, OH 45433-7800. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

## Custodians:

Army - MR  
Navy - AS  
Air Force - 11

Adopting Activity

Air Force - 11

AREA NDTI

DISTRIBUTION STATEMENT A. Approved for public release;  
distribution is unlimited.

AMS 2643A

Issued 11-15-72  
Revised 4-1-88

Superseding AMS 2643

**SAE** The Engineering Society  
For Advancing Mobility  
Land Sea Air and Space®

400 COMMONWEALTH DRIVE, WARRENDALE, PA 15096

**AEROSPACE  
MATERIAL  
SPECIFICATION**

Submitted for recognition as an American National Standard

STRUCTURAL EXAMINATION OF TITANIUM ALLOYS  
Chemical Etch Inspection Procedure

## THIS REVISION CONTAINS ONLY EDITORIAL CHANGES

1. SCOPE:1.1 Purpose: This specification covers a procedure for revealing the macrostructure and microstructure of titanium alloys.1.2 Application: Primarily for detecting defects and segregation in titanium alloys. This procedure should not be used on finished parts.2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

2.2 ANSI Publications: Available from American National Standards Institute, Inc., 1430 Broadway, New York, NY 10018.

ANSI B46.1 - Surface Texture

3. TECHNICAL REQUIREMENTS:3.1 Macrostructure:3.1.1 Specimens:

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

3.1.1.1 Bars, Extrusions, Plates, and Stock for Forging or Extruding: Specimens shall be transverse cross-sections not less than 0.5 in. (12 mm) thick cut from the product to be tested and then cut in half longitudinally to permit examination of both transverse and longitudinal surfaces. Specimens from stock for forging or extruding shall be heated to  $50\text{ F} + 25$  ( $30\text{ C} + 15$ ) deg below the beta transus as determined for the heat, held at heat for 60 min. + 5, and cooled at a rate equivalent to air cool or faster. Specimens shall be machined to have surface texture of 70 microin. ( $1.8\ \mu\text{m}$ ) AA or finer, determined in accordance with ANSI B46.1.

3.1.1.2 Forgings: When dimensions permit, forgings shall be rough-machined to clean up and to ensure freedom from alpha case. A minimum of 0.030 in. (0.75 mm) of material shall be left on the surfaces of the forgings between final etching and finish machined configuration to ensure freedom from intergranular attack and hydrogen pickup on finished parts. If forgings are to be inspected by ultrasonic inspection procedures, the configuration used for such inspection is acceptable. Optimum surface texture shall be 130 microin. ( $3.3\ \mu\text{m}$ ) AA or finer, determined in accordance with ANSI B46.1.

3.1.2 Procedure:

3.1.2.1 Specimens shall be cleaned free from dirt, grease, oil, and other foreign materials.

3.1.2.2 Specimens shall be rinsed with clean tap water.

3.1.2.3 Specimens shall be etched in an aqueous acid solution maintained at room temperature for sufficient time to develop a well-defined macrostructure. The following solution or an alternate agreed upon by purchaser and vendor shall be used:

15%  $\pm$  2 by volume, technical grade nitric acid, 42° Baume'  
10%  $\pm$  1.5 by volume, hydrofluoric acid (48%)  
Balance water

3.1.2.3.1 The etching rate of the solution shall be maintained to remove 0.002 - 0.004 in. (0.05 - 0.10 mm) of metal in a 5 min. period. The etching rate shall be determined periodically.

3.1.2.4 Remove specimen from etch solution and immediately wash in clean water for several minutes.

3.1.2.5 Finish rinsing with pressurized tap water to remove smut.

3.1.2.6 Drain water from specimens by blowing dry with clean air.

- 3.1.2.7 Visually inspect the specimen at 1X using a light intensity not lower than 200 ft-candles (2150 lx) for macrostructure and defects such as segregation, laps, folds, cracks, inclusions, and heavy non-cleanup areas.
- 3.2 Microstructure: If examination of the macrostructure indicates the need for further evaluation, the microstructure shall be developed as follows:
- 3.2.1 Specimens: The specimens on which macrostructure was developed shall be cut through the areas of concern and, where practical, shall also be cut for examination of other planes.
- 3.2.2 Procedure:
- 3.2.2.1 Polish and etch the specimens to be examined using metallographic techniques which will clearly reveal the microstructure to be evaluated (See 8.4).
- 3.2.2.2 Examine the specimens to determine the microstructure and the nature of indications found in the macrostructure.
4. QUALITY ASSURANCE PROVISIONS: Not applicable.
5. PREPARATION FOR DELIVERY: Not applicable.
6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
7. REJECTIONS: Not applicable.
8. NOTES:
- 8.1 This revision contains only editorial changes from the previous issue of this specification, and, therefore, no phi ( $\emptyset$ ) symbols indicating technical changes are required.
- 8.2 Equipment:
- 8.2.1 The tank for the solution of 3.1.2.3 must be lined with polyvinyl chloride or comparable lining material.