

# AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
29 West 39th Street  
New York City

## AMS 2671

Issued 12-1-51

Revised

### COPPER FURNACE BRAZING Corrosion and Heat Resistant Steels and Alloys

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. APPLICATION: For joining corrosion and heat resistant steels and alloys. Not recommended for use on parts which will operate at over 1000 F or where high strength joints are required at temperatures over 700 F.
3. PROCESS REQUIREMENTS:
  - 3.1 Surface Condition: The surfaces to be joined shall be clean prior to assembly.
  - 3.2 Fluxing: Flux shall not be used unless permission be obtained from purchaser before brazing.
  - 3.3 Assembly: The parts to be joined shall be assembled so that, if practical, there is metal to metal contact between mating surfaces and relative movement of the components does not occur during the brazing operation so that the parts will be in proper alignment after brazing.
  - 3.4 Brazing Material: The brazing material shall be copper conforming to AMS 4701, or to AMS 4500 and of oxygen-free type. When permitted by purchaser, a suitable copper paste may be used. Sufficient copper shall be placed within or in close proximity to the joint.
  - 3.5 Joining: Heating shall be performed in a furnace with a suitable protective atmosphere at a temperature between 2000 F and 2250 F. Parts shall be heated until the copper melts and the joint is formed. Further heating shall be held to a minimum. The protective atmosphere in the furnace shall be of such a character that the steel will not be scaled, carburized, excessively decarburized, or excessively nitrided.
  - 3.6 Cooling: After brazing, assemblies shall be cooled in such a manner as to prevent cracks and minimize internal stress, distortion, scaling and decarburization. Cooling from the brazing temperature to below the scaling temperature shall be done in a suitable protective atmosphere. If hardening is to be executed in conjunction with brazing, cooling procedures may be revised accordingly.
  - 3.7 Flux Removal: After brazing and cooling, flux if used, shall be removed from the parts by a method not injurious to the specified surface finish.
  - 3.8 Heat Treatment: Where hardness is specified for the brazed assembly and heat treatment is required, such heat treatment shall follow the brazing operation.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."