

**AEROSPACE
MATERIAL
SPECIFICATION**

Submitted for recognition as an American National Standard

SAE AMS 3108D

Issued 7-1-48
Revised 10-1-86

Superseding AMS 3108C

PRIMER, OCHER
Phenolic

1. SCOPE:

1.1 Type: This specification covers an ocher-pigmented primer.

1.2 Application: Primarily as a prime coating on metal surfaces before enameling, usually with AMS 3122 enamel.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D56 - Flash Point by Tag Closed Tester

ASTM D185 - Coarse Particles in Pigments, Pastes, and Paints

ASTM D445 - Kinematic Viscosity of Transparent and Opaque Liquids
(and the Calculation of Dynamic Viscosity)

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.3.1 Federal Specifications:

PPP-P-1892 - Paint, Varnish, Lacquer, and Related Materials, Packaging, Packing, and Marking of

3. TECHNICAL REQUIREMENTS:3.1 Composition (by weight):3.1.1 Primer:

	min	max
Nonvolatile	60%	--
Volatile	--	40%

3.1.2 Nonvolatile:

	min	max
Resin	48 -	50%
Pigment	50 -	52%

3.1.2.1 Resin: Shall be a thermosetting phenolic type with softening agents added. It shall be free from rosin, rosin derivatives, oils, and cellulose derivatives.

3.1.2.2 Pigment: Shall be a natural ocher.

3.1.3 Volatile: The composition of the volatile component shall be optional with the manufacturer and shall meet applicable air pollution control regulations.

3.2 Properties: Primer shall conform to the following requirements:

3.2.1 Product Properties:

3.2.1.1 Color: Shall be yellow-tan, characteristic of ocher.

3.2.1.2 Coarse Particles: Not more than 0.1% by weight of primer shall be retained on a No. 325 (45 μ m) screen, determined in accordance with ASTM D185.

3.2.1.3 Flash Point: Shall be not lower than 16°C (60°F), determined in accordance with ASTM D56.

3.2.1.4 Viscosity: Shall be 9 - 13 poises (0.9 - 1.3 Pa·s) at 25°C (77°F), not less than 24 hr after manufacture, determined in accordance with ASTM D445.

3.2.1.5 Skinning and Livering: Shall be absent in a 1/4-filled, closed container after standing for not less than one week at room temperature.

3.2.2 Film Properties: Primer, reduced to viscosity of 20 - 23 sec in Ford No. 4 cup with alcohol-base thinner of type approved by purchaser, shall have properties as specified in 3.2.2.1 through 3.2.2.4, determined on films applied by brushing, dipping, or spraying on sandblasted, low-carbon steel panels; except for determination of leveling properties, films shall be air-dried for not less than 20 min. and baked for 1 hr \pm 0.1 at 160° - 165°C (320° - 330°F).

3.2.2.1 Leveling: Primer shall be a freely working product with leveling properties acceptable to purchaser.

3.2.2.2 Drying: Films, applied as in 3.2.2, shall dry firm and hard and shall be free from streaks, blisters, silking, and other surface irregularities.

3.2.2.3 Adhesion: Films, applied as in 3.2.2, shall withstand, without peeling, bending at 0°C (32°F) through an angle of 180 deg around a diameter equal to 20 times the nominal thickness of the panel. Cracking of the film on the bent portion of the panel will be permissible.

3.2.2.4 Phenol Resistance: Films, applied as in 3.2.2, shall show no wrinkling or removal after being partly immersed in C.P. phenol at 150°C + 3 (300°F + 5) for 5 min. \pm 0.2. Discoloration or slight surface softening of the film will be permissible.

3.3 Quality: Primer, as received by purchaser, shall be of uniform consistency and free from bubbles, grit, rough particles, floating or caked pigments, and ingredients of respiratory toxicity under normal conditions of use. Component ingredients shall be intimately mixed and processed as required to produce primer which is stable and not subject to abnormal change with age in sealed containers.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of primer shall supply all samples \emptyset for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the primer conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), color (3.2.1.1), flash point (3.2.1.3), viscosity (3.2.1.4), leveling (3.2.2.1), drying (3.2.2.2), and adhesion (3.2.2.3) are classified as acceptance tests and shall be performed on each lot.

4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the initial shipment of primer to a purchaser, when a change in material, processing, or both requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be as follows:

4.3.1 For Acceptance Tests: Sufficient primer shall be taken at random from each lot to permit making the following number of tests; a lot shall be all primer made from the same batches of ingredients in a continuous series of operations and presented for vendor's inspection at one time.

Requirement	Reference Paragraph	Number of Tests
Composition	3.1	1
Color	3.2.1.1	1
Flash Point	3.2.1.3	1
Viscosity	3.2.1.4	1
Leveling	3.2.2.1	2 (See 4.3.1.1)
Drying	3.2.2.2	2 (See 4.3.1.1)
Adhesion	3.2.2.3	2

4.3.1.1 These requirements are to be determined on the panels prepared for the adhesion test.

4.3.1.2 When a statistical sampling plan and acceptance quality level (AQL) have been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.5 shall state that such plan was used.

4.3.2 For Preproduction Tests: As agreed upon by purchaser and vendor.

4.4 Approval:

4.4.1 Primer shall be approved by purchaser before primer for production use is supplied, unless such approval be waived by purchaser. Results of tests on production primer shall be essentially equivalent to those on the approved sample.

4.4.2 Vendor shall use the same ingredients, manufacturing procedures and processes, and methods of inspection on production primer which are essentially the same as those used on the approved sample primer. If necessary to make any change in ingredients or in manufacturing procedures or processing, vendor shall submit for reapproval a statement of the proposed changes in material, processing, or both and, when requested, sample primer. Production primer made by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Reports: The vendor of primer shall furnish with each shipment a report showing the results of tests to determine conformance to the acceptance test requirements and stating that the primer conforms to the other technical requirements of this specification. This report shall include the purchase order number, AMS 3108D, formula number, lot number, and quantity.