

# AERONAUTICAL MATERIAL SPECIFICATION

## AMS 3120A

Society of Automotive Engineers, Inc.  
29 West 39th Street  
New York City

Issued 6-13-40

Revised 5-1-48

### ENAMEL, BLACK BAKING Glyceryl Phthalate

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. TYPE: Gloss baking black.
3. APPLICATION: As an exterior protective coating for metal surfaces.
4. COMPOSITION:
  - 4.1 Product (by weight):

Resin	36 - 44%
Pigment	2 - 6%
Volatile	60% max
  - 4.2 Resin: Shall be of glyceryl phthalate type, modified, if necessary, with small amounts of other resins, and shall contain not less than 31% phthalic anhydride equivalent. It shall be free from rosin and rosin derivatives.
  - 4.3 Pigment: Shall consist of carbon black, with addition of iron blue if necessary, in proportions required to produce an enamel meeting the requirements of paragraph 5.7.2.
5. TECHNICAL REQUIREMENTS:
  - 5.1 General: Enamel shall be of uniform consistency, and free from bubbles, toxic ingredients, grit, rough particles and floating or caked pigments. Component ingredients shall be intimately mixed, and processed as required to produce a product which is stable and not subject to abnormal change with age in sealed containers.
  - 5.2 Coarse Particles: Not more than 0.1% by weight of the enamel shall be retained on a No. 325 screen.
  - 5.3 Moisture Content: Shall not exceed 0.1% by weight.
  - 5.4 Flash Point (Tag Closed Tester): Shall be not lower than 70 F.
  - 5.5 Viscosity: Shall be 300 - 700 centipoises absolute at 77 F not less than 24 hours after manufacture.
  - 5.6 Skinning and Livering: Shall be absent in a 1/4-filled closed container after standing one week.
  - 5.7 Film Properties: Enamel reduced with toluene to viscosity of 100 - 125 centipoises shall have properties as specified in paragraphs 5.7.1 through 5.7.9 below when determined on panels of anodized AMS 4037 aluminum alloy, except that color and gloss requirements apply to tests conducted on glass panels:

Section 1 of the SAE Technical Board rules provides that: "All technical reports, including standards, specifications, and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any standard or recommended practice, and no commitment to continue to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

- 5.7.1 Leveling: When applied by brushing or spraying, enamel shall be a freely working product with leveling properties acceptable to purchaser.
- 5.7.2 Color and Gloss: A coat, baked for 30 minutes at  $300\text{ F} \pm 5$ , shall closely match the color and gloss of the standard panel specified by purchaser.
- 5.7.3 Air-Drying: A coat shall air-dry to touch in not more than 4 hours.
- 5.7.4 Baking: A coat shall dry firm and hard in not more than 30 minutes, when baked at  $300\text{ F} \pm 5$ , and in not more than 1-1/2 hours, when baked at  $250\text{ F} \pm 5$ . Film, upon drying, shall be free from streaks, blisters, silking, and other surface irregularities.
- 5.7.5 Baking Properties: A coat, air-dried 15 minutes and baked at  $300\text{ F} \pm 5$  for 4 hours, shall be hard, tough, smooth and free from all defects such as checking, wrinkling or dulling. Baked film shall show no appreciable discoloration.
- 5.7.6 Flexibility and Adhesion: A coat applied to a panel and baked as in 5.7.5 shall show no cracking or peeling when rapidly bent at  $32\text{ F}$  through an angle of 180 degrees around a diameter equal to six times the thickness of the panel and shall adhere tenaciously to bent portion of the panel. Film shall show fine feathered edges on drawing knife blade over it on bent portions.
- 5.7.7 Heat Resistance: A coat, air-dried 15 minutes, baked 30 minutes at  $300\text{ F} \pm 5$  and then heated 24 hours at  $500\text{ F} \pm 10$  shall show no cracks, checks, blisters, or other defects. Dulling or change in color shall not be considered a defect.
- 5.7.8 Water Resistance (Hot): A coat, air-dried 15 minutes and baked at  $300\text{ F} \pm 5$  for 2 hours, shall withstand immersion in boiling water for 10 minutes. When observed 5 minutes after removal, film shall show no checking, no blistering, no appreciable whitening and not more than very slight dulling, and when observed 15 minutes after removal, shall show no whitening. After 3 hours air-drying, film on immersed end shall be equal in hardness, toughness and adhesion to film which was not immersed, as determined by drawing knife blade over respective ends of panel; film shall also be equal in gloss to film which was not immersed.
- 5.7.9 Fuel Resistance: A coat, air-dried 15 minutes and baked at  $300\text{ F} \pm 5$  for 30 minutes, shall withstand immersion in ASTM Reference Fuel No. 1 at room temperature for 4 hours. Film, 24 hours after removal from fuel, shall be equal in hardness, toughness and adhesion to film on a panel which has not been subjected to fuel, as determined by drawing knife blade over respective panels; film shall also be equal in gloss to film which was not subjected to fuel.
6. REPORTS: Unless otherwise specified, the vendor shall furnish with each shipment three copies of a notarized report of the composition and the quantitative results of tests conducted on the batch of enamel from which the order was filled. This report shall include the purchase order number, material specification number, formula number and/or batch number, and quantity.
7. IDENTIFICATION: Each container shall be marked to show this specification number and title, vendor's identification, formula number and/or batch number, date of manufacture, quantity, and any directions for use or precautions for storage.