



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 3126A

Superseding AMS 3126

Issued 5-15-71

Revised 4-15-78

ALUMINUM COATING MATERIAL, CORROSION AND HEAT RESISTANT Thermosetting, Inorganic Binder

1. SCOPE:

- 1.1 Type: This specification covers a corrosion and heat resistant aluminum coating material supplied as a liquid of suitable consistency for coating parts after being thoroughly mixed.
- 1.2 Application: Primarily for coating ferrous parts to be exposed to temperatures below 650° C (1200° F).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A109 - Steel, Carbon, Cold Rolled Strip
ASTM B117 - Salt Spray (Fog) Testing
ASTM C430 - Fineness of Hydraulic Cement by No. 325 Sieve
ASTM D471 - Rubber Property - Effect of Liquids
ASTM D1084 - Viscosity of Adhesives
ASTM D1475 - Density of Paint, Varnish, Lacquer, and Related Products

- 2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Specifications:

PPP-P-1892 - Paint, Varnish, Lacquer, and Related Materials, Packaging, Packing, and Marking of

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Total Solids	56 - 62% (by weight)
Volatile (Water)	remainder

- 3.1.1 Pigment: Shall consist of commercially pure (99% min aluminum) spherical aluminum powder or atomized powder having an average particle size not greater than 10 microns and shall contain no other filler or adulterant.

SAE Technical Board rules provide that: "All technical reports, including standards approved by the Board, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or to be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 3.1.2 Binder: Shall be an acidic, water-base inorganic type.
- 3.1.3 Shelf Life: Shall be not less than 1 yr from date of manufacture when the product is stored in sealed containers at temperatures between 7° C (45° F) and 29° C (85° F).
- 3.2 Properties:
- 3.2.1 Product Properties:
- 3.2.1.1 General: Material, after mixing thoroughly, shall be of uniform consistency, and free from hydrogen evolution, grit, and floating or caked pigments. Ingredients shall be processed as required to produce a product which is stable and not subject to abnormal change with age in sealed containers. The formation of agglomerates which can be dispersed by high speed mixing is permissible.
- 3.2.1.2 Density: Shall be not less than 13.2 lb per gallon (1584 kg/m³), determined at 25° C + 1
ø (77° F + 2), in accordance with ASTM D1475.
- 3.2.1.3 Coarse Particles: Not more than 0.1% by wt of the product shall be retained on a No. 325 screen, determined in accordance with ASTM C430.
- 3.2.1.4 Viscosity: Shall be 16 - 18 sec at 25° C (77° F), determined in accordance with ASTM D1084,
ø Method D.
- 3.2.2 Film Properties: Shall be as specified in 3.2.2.1 through 3.2.2.7, determined on panels prepared as in 4.3.2.1.
- 3.2.2.1 Appearance: Shall be uniform matte gray and shall closely match the color of the standard panel agreed upon by purchaser and vendor.
- 3.2.2.2 Adhesion: Film shall not loosen from the panel or flake at the bend when the panel is bent at room temperature through an angle of 90 deg around a diameter equal to 8 times the nominal thickness of the uncoated panel. Flaking or loosening of film within 1/8 in. (3.2 mm) of edges is permissible.
- 3.2.2.3 Heat Resistance: Film, after heating for 23 hr + 0.5 at 370° C + 15 (700° F + 25) followed by 4 hr + 0.1 at 650° C + 15 (1200° F + 25) shall show no cracking, checking, or blistering; discoloration of the film is acceptable.
- 3.2.2.4 Hot Water Resistance: Film shall withstand immersion in boiling water for 10 min. + 0.2. When observed 5 min. after removal, film shall show no checking, blistering, or leaching-out of coating constituents. After 3 hr + 0.1 air drying, film shall meet the adhesion test of 3.2.2.2. Discoloration of the film is acceptable.
- 3.2.2.5 Fuel Resistance: Film shall withstand immersion in ASTM Reference Fuel B (ASTM D471) at room temperature for 4 hr + 0.1. Film, 24 hr after removal from fuel, shall meet the adhesion test of 3.2.2.2.
- 3.2.2.6 Hot Oil Resistance: Film, after immersion in ASTM Service Fluid No. 101 (ASTM D471) for 8 hr + 0.2 at 205° C + 15 (400° F + 25) shall show no peeling or blistering and not more than slight softening.
- 3.2.2.7 Corrosion Resistance: Coated panels which have been exposed to heat as in 3.2.2.3, cross scratched "X" on one face with a sharp instrument so that each leg of "X" is approximately 1 - 1-1/2 in. (25 - 38 mm) long, and then subjected to salt spray test in accordance with ASTM B117 for 100 hr + 0.5, shall show no pitting of the basis metal except within 1/8 in. (3.2 mm) of any edge or within 1/16 in. (1.6 mm) of scratches. Discoloration or superficial rust spots on the film is acceptable.

3.3 Quality: The product, as applied to panels or parts, shall produce a cured coating which shall be smooth, uniform, and free from pinholes, sags, runs, bubbles, heavy edges, foreign materials, and other imperfections detrimental to performance of parts.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.

∅ 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to composition (3.1), pigment (3.1.1), binder (3.1.2), density (3.2.1.2), coarse particles (3.2.1.3), and viscosity (3.2.1.4) requirements are classified as acceptance tests.

4.2.2 Periodic Tests: Tests to determine conformance to film property (3.2.2) requirements are classified as periodic tests.

4.2.3 Qualification Tests: Tests to determine conformance to all technical requirements of this specification are classified as qualification tests.

4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, qualification test material shall be submitted to the cognizant qualification agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling:

4.3.1 Acceptance Tests: Sufficient material shall be taken at random from each lot using two separate containers; two specimens for each test. A lot shall be all product produced in a single production run from the same batches of raw materials and presented for vendor's inspection at one time.

4.3.2 Periodic Tests: Tests shall be conducted on a semi-annual basis, with the extent of sampling agreed upon by purchaser and vendor.

4.3.2.1 Panels for evaluation of film properties shall be prepared by spraying the coating on both sides of abrasive-blasted, clean, smooth, ASTM A109, Temper No. 5, or equivalent, steel panels to a total dried film thickness of 0.0015 - 0.0025 in. (0.038 - 0.064 mm), attained in two coats.
∅ Following each coat, finish shall be dried by heating to $80^{\circ}\text{C} \pm 15$ ($175^{\circ}\text{F} \pm 25$) for not less than 15 min. and cured by heating to $345^{\circ}\text{C} \pm 15$ ($650^{\circ}\text{F} \pm 25$) for not less than 30 minutes. Following the final cure at $345^{\circ}\text{C} \pm 15$ ($650^{\circ}\text{F} \pm 25$), finish for the tests of 3.2.2.3, 3.2.2.6, and 3.2.2.7 shall be postcured by heating to $540^{\circ}\text{C} \pm 15$ ($1000^{\circ}\text{F} \pm 25$) for not less than 90 minutes.

4.3.3 Qualification Tests: Shall be as agreed upon by purchaser and vendor.

4.4 Approval:

4.4.1 Material shall be approved by purchaser before material for production use is supplied, unless such approval be waived. Results of tests on production material shall be essentially equivalent to those on the approved sample.