

AEROSPACE MATERIAL SPECIFICATION

SAE AMS3145

REV. D

Issued	1970-11
Revised	1985-10
Reaffirmed	1994-04
Noncurrent	1998-02
Reaf. Noncur.	2004-02
Stabilized	2013-07

Superseding AMS3145C

Paint, Marking
Epoxy

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

This document has been declared "Stabilized" by SAE G-8, Aerospace Organic Coatings Committee, and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAENORM.COM : Click to view the full PDF of AMS3145D

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3145D>**

SAE WEB ADDRESS:

1. SCOPE:

1.1 Type:

This specification covers two-component colored systems composed of a resin and a miscible hardener supplied in kit form.

1.2 Application:

Primarily for identification marking of parts and equipment exposed to temperatures from -55° to +150°C (-65° to +300°F) where various colors are needed. Systems produce tile-like compounds with good hardness, moisture and solvent resistance, and adhesion to metallic surfaces when properly cured.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

2.2 ASTM Publications:

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D1638 - Testing Urethane Foam Isocyanate Raw Materials
ASTM D2134 - Softening of Organic Coatings by Plastic Compositions
ASTM D3359 - Measuring Adhesion by Tape Test

2.3 U.S. Government Publications:

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Specifications:

PPP-P-1892 - Paint, Varnish, Lacquer, and Related Materials, Packaging, Packing, and Marking of

3. TECHNICAL REQUIREMENTS:

3.1 Material:

Shall be a thermosetting epoxy compound.

- 3.1.1 Storage Life: The components and the mixed product shall meet the requirements of 3.2 at any time up to one year from date of receipt by purchaser when stored in airtight containers at 10° - 30°C (50° - 85°F).
- 3.1.2 Pot Life: The pot life of a mixture of 100 parts + 1 by weight of resin and 100 parts ± 1 by weight of hardener, defined as the time to produce double the initial viscosity, shall be not less than 6 hr at 25°C ± 1 (77°F ± 2).

3.2 Properties:

The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified ASTM methods:

3.2.1 Uncured Resin:

- 3.2.1.1 Specific Gravity: Shall be as specified in Table I, determined in accordance with ASTM D1638, Method A.
- 3.2.1.2 Viscosity: Shall be as specified in Table I, determined in accordance with ASTM D1638 at 25°C ± 1 (77°F ± 2).
- 3.2.1.3 Color: Shall be as ordered, selected from those specified in Table I.

3.2.2 Hardener:

- 3.2.2.1 Specific Gravity: Shall be as specified in Table II, determined in accordance with ASTM D1638, Method A.
- 3.2.2.2 Viscosity: Shall be as specified in Table II, determined in accordance with ASTM D1638 at 25°C ± 1 (77°F ± 2).
- 3.2.3 Cured Resin: The mixture of 3.1.2 shall cure within 2 hr at 60°C ± 3 (140°F ± 5), or within 24 hr at 25°C ± 5 (77°F ± 9) and exhibit the properties specified in 3.2.3.1 and 3.2.3.2.
- 3.2.3.1 Sward Hardness: Shall be as specified in Table III, determined in accordance with ASTM D2134, without conditioning.
- 3.2.3.2 Surface Adhesion: Shall be 4A or better, determined in accordance with ASTM D3359, Method A, on panels prepared as in 3.2.3.2.1.

- 3.2.3.2.1 Panels shall be of aluminum or aluminum alloy, approximately 0.020 x 6 x 3 in. (0.5 x 150 x 75 mm) and having smooth edges and rounded corners. Panels shall be cleaned by vapor degreasing or washing with a chlorinated solvent, coated with resin-hardener mixture to a film thickness of approximately 0.005 in. (0.12 mm), and cured as in 3.2.3.

3.3 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, clean, homogeneous, and free from foreign materials and from imperfections detrimental to usage of the product.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Tests to determine conformance to requirements for pot life (3.1.2), specific gravity (3.2.1.1 and 3.2.2.1), viscosity (3.2.1.2 and 3.2.2.2), Sward hardness (3.2.3.1), and surface adhesion (3.2.3.2) are classified as acceptance tests and shall be performed on each lot.
- 4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the initial shipment of the product to a purchaser, when a change in material, processing, or both requires reapproval, and when purchaser deems confirmatory testing to be required.
- 4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling:

Shall be as follows:

- 4.3.1 For Acceptance Tests: Sufficient paint shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.
- 4.3.1.1 A lot shall be all paint of the same color produced in a single production run from the same batches of raw materials. An inspection lot shall not exceed 100 gal (380 L). A lot may be packaged in small quantities under the basic lot approval provided lot identification is maintained.