

AEROSPACE MATERIAL SPECIFICATIONS

AMS 3197G

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 12-1-42
Revised 2-15-65

SYNTHETIC RUBBER SPONGE Chloroprene Type, Soft

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **FORM:** Sheet, strip, molded shapes, or as ordered.
3. **APPLICATION:** Primarily for general applications requiring the use of open cell, soft sponge rubber as pads and seals in the temperature range of -40 to +80 C (-40 to +176 F).
4. **TECHNICAL REQUIREMENTS:**
 - 4.1 **General:**
 - 4.1.1 **Weathering:** When specified, the product shall have weather resistance acceptable to the purchaser as determined by a procedure agreed upon by purchaser and vendor.
 - 4.1.2 **Corrosion:** The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service. Discoloration of metal shall not be considered objectionable.
 - 4.1.3 **Finish:** The top and bottom surfaces of sheet and strip, and the exterior surfaces of molded parts, shall have a natural skin finish. Unless otherwise specified, fabric or wire mesh type of surface impressions are not objectionable.
 - 4.1.4 **Color:** Shall be black, unless otherwise specified.
 - 4.1.5 **Low Temperature:** When specified, the product shall have low temperature flexibility acceptable to the purchaser as determined by a procedure agreed upon by purchaser and vendor.
 - 4.2 **Properties:** The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with the issue of specified ASTM methods listed in the latest issue of AMS 2350, insofar as practicable.
 - 4.2.1 **As Received:**
 - 4.2.1.1 Compression-Deflection, psi 1 to 4
ASTM D1056
Temperature: 20 - 30 C
(68 - 86 F)

Section 8.3 of the SAE Technical Board rules provides that: "All technical reports including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no obligation to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

4.2.1.2 Specific Volume

Unless otherwise specified, the specific volume for each nominal thickness shall be as specified below; a tolerance of $\pm 10\%$ will be allowed.

Nominal Thickness Inches	Specific Volume cu in. per lb
1/16	36
3/32	42
1/8	48
3/16	55
1/4	58
5/16	61
3/8	63
1/2	66
5/8	70
3/4	73
7/8	77
1	80
1 - 1/2	87

4.2.1.3 Hydrogen Ion Concentration, pH

7.0 to ± 1.0

See Note 1

4.2.2 Dry Heat Resistance:

See Note 2

4.2.2.1 Compression-Deflection Change, %

 -5 to $+30$

Temperature: $100\text{ C} \pm 1$
($212\text{ F} \pm 1.8$)
Time: 22 hr

4.2.2.2 Specific Volume Change, %

 -10 to $+10$

4.2.2.3 Bend (flat)

No cracking
or checkingØ 4.2.3 Compression Set:

ASTM D1056

Ø 4.2.3.1 Per cent of original deflection, max

40

Temperature: $70\text{ C} \pm 1$
($158\text{ F} \pm 1.8$)
Time: 22 hr

4.2.3.2 Per cent of original thickness, max

20

Note 1. Dice approximately 1 cu in. of sponge to approximately 1/8 in. or smaller cubes and extract with continuous agitation for 1 hr with 100 ml of freshly distilled water. Determine pH of the extract.

Note 2. A sample of material 4 in. square shall be suspended in the oven by a wire attached to one corner of the sample. After heating, the sample shall be removed from the oven and trimmed to 2 in. square by removing 1 in. from each edge prior to testing. Standard compression-deflection specimens shall be cut from the sample and tested.

5. QUALITY: The product shall be uniform in quality and condition, clean, smooth, and free from foreign materials and from imperfections detrimental to fabrication, appearance, or performance of parts.

6. TOLERANCES: Unless otherwise specified, the following tolerances apply; measurements shall be made in accordance with the issue of ASTM D1056 listed in the latest issue of AMS 2350.