

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 3198A

Issued 12-1-42
Revised 11-1-44

SYNTHETIC RUBBER SPONGE (Medium)

Page 1 of 3 pages

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **FORM:** Sheet, strip, molded shapes, or as ordered.
3. **APPLICATION:** This material shall be suitable for general applications using sponge rubber.
4. **QUALITY:** (a) The material shall be free from manufacturing imperfections, which will affect the serviceability, and shall conform to the requirements specified herein.

(b) Workmanship shall be in accordance with high grade commercial practice governing this type of material.
5. **REQUIREMENTS:** (a) **Compression-Deflection.**- Tests shall be conducted in accordance with ASTM D552-43T. The pressure required to compress the material to 75% of its original thickness at room temperature shall be within the limits of 6 to 13 psi.

(b) **Compression Set.**- Tests shall be conducted in accordance with ASTM D552-43T. Compression set shall not exceed 25%.

(c) **Oven Aging.**- Oven aging samples shall be 4 inches square, and shall be suspended in the oven by a wire attached to one corner of the sample. After heating the material in a convection current air oven for 22 hours at 212°F, the samples shall be removed from the oven and trimmed to 2 inches square by removing 1 inch from each edge. The sponge shall not be hard or brittle and shall show no surface cracks when bent 180° flat. The specific volume change shall be within the limits of ±10%. The compressibility change shall be within the limits of ±20% of the original.

(d) **Sizes.**- Unless otherwise ordered, the thickness and specific volume shall be as specified below:

Thickness inches	Specific Volume cu. in. per pound
1/16	33
3/32	40
1/8	45
3/16	56
1/4	63
5/16	63
3/8	63
1/2	63
5/8	67
3/4	74
7/8	76
1	79
1 1/2	84

Note: A tolerance of ±10% is permissible on the above values of specific volumes.

(e) Weathering.-- Unless otherwise specified, a weathering test shall be conducted as between the purchaser and vendor.

(f) Finish.-- The finished material shall have rinds of finished surfaces on both the top and the bottom of the sheets.

(g) Color.-- Unless otherwise specified, synthetic sponge rubber shall be furnished in black only.

6. SAMPLES: Sampling procedure shall conform to ASTM D552-43T. When the form in which the material is furnished is unsuitable for the proper preparation of the test specimens required, the vendor shall furnish sufficient sheet material for such specimens from production-run materials which he guarantees to be of equal quality to the material supplied.

7. TOLERANCES: Unless otherwise specified on the drawing or purchase order, the following tolerances apply; all dimensions are in inches:

(a) Sheet and Strip.--

<u>Nominal Thickness</u>	<u>Tolerance Plus and Minus</u>
1/8 and less	1/64
Over 1/8 to 1/2, incl.	1/32
5/8 and over	3/64

<u>Nominal Width</u>	<u>Tolerance Plus and Minus</u>
6 and less	1/16
Over 6 to 18, incl.	1/8
Over 18	1/4

(b) Molded Parts.--

<u>Nominal Dimension</u>	<u>Tolerance Plus and Minus</u>
1/4 and less	1/32
Over 1/4 to 3, incl.	1/16
Over 3	1/4

8. REPORTS: Unless otherwise specified, the vendor shall furnish three copies of a notarized report of the results of tests to determine conformance to this specification. This report shall include the purchase order number, material specification number, vendor's compound number, percentages and specific type of synthetic or synthetics used, part number and quantity.

9. IDENTIFICATION: Unless otherwise agreed between the purchaser and the vendor, all material shall be identified and marked in accordance with the latest revision of AMS 2810.

10. PACKAGING: Packaging shall be accomplished in such a manner as to insure that the materials being shipped will not be permanently distorted or compressed, or be exposed to undue weathering or harmful materials of any kind.