

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 3200A

Issued 12-1-42

Revised 10-1-43

SYNTHETIC RUBBER Hydraulic Fluid (Petroleum Base) Resistant (55-65)

Page 1 of 4 pages

1. ACKNOWLEDGMENT: A vendor must mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. FORM: Sheet, strip, tubing, extrusions, molded shapes, or as ordered.
3. APPLICATION: The compound shall be suitable for seals, gaskets and similar parts used in aircraft control systems and which come in contact with petroleum base hydraulic fluids.
4. QUALITY: (a) It shall be uniform in quality, free from foreign materials or imperfections, tough and not easily torn by hand. It shall resist the solvent and swelling actions of petroleum base hydraulic fluids.
(b) Parts must be smooth and free from flash.
(c) If rings have a vulcanized joint, the joint section must have the same strength and size as the solid section.
5. REQUIREMENTS: (a) Physical Properties.- This material shall possess the following physical properties as received:

Shore Durometer "A" Hardness	60 ± 5
Tensile Strength, lb per sq in.	1400 min
Elongation, %	250 min

All tensile tests required by this and succeeding paragraphs shall conform to ASTM D412-41, except that tensile strengths after all aging tests shall be based on the original unaged cross-sectional area.

(b) Oil Aging.- Tests shall be conducted in accordance with ASTM D40T, except that physical properties after aging shall be determined immediately after removal from the oil. Test conditions shall be as follows:

Medium	Petroleum Base Hydraulic Fluid
	Viscosity 40.5 ± 2 sec. at 210°F
	Viscosity 95 ± 5 sec. at 100°F
	Viscosity 1870 ± 10 sec. at 0°F
	Four Point -54°F max
	Aniline Point 189° ± 2°F
Temperature	212° ± 2°F
Time	70 hours

After aging, the surface shall neither be tacky nor show signs of decomposition. The Shore Durometer "A" hardness change shall be within the limits of -15 to +5 points. The tensile strength shall have decreased by not more than 50% and the elongation by not more than 50% from the values found for the material as received. The volume change shall be within the limits of 0% to +20%.

(c) Oven Aging.- Tests shall be conducted in accordance with ASTM D573-41 for 70 hours at $212^{\circ} \pm 2^{\circ}\text{F}$. After aging, the surface shall be neither hard nor brittle, and specimens shall withstand bending 180° flat. The Shore Durometer "A" hardness change shall be within the limits of 0 to +15 points. The tensile strength shall have decreased by not more than 20% and the elongation by not more than 50% from the values found for the material as received.

(d) Compression Set.- Tests shall be conducted in accordance with ASTM D395-40T, Method B, under the following conditions:

Time	70 hours
Temperature	$212^{\circ} \pm 2^{\circ}\text{F}$
Compression, To.	70% of original thickness

(1) The maximum compression set shall be 75% when expressed as a percentage of the original deflection.

(2) The maximum compression set shall be 22% when expressed as a percentage of the original thickness.

(e) Cold Aging.- The cold resistance of the material shall be determined by the SAE-ASTM Bent Loop Method, which is as follows:

(1) The specimen, a strip $4'' \times 1/4'' \times .075''$, shall be aged in accordance with the Petroleum Base Hydraulic Fluid Aging requirements, as described in paragraph 5(b) of this specification. It is then clamped in a loop position between plates $2\ 1/2''$ apart and at least $2''$ wide, in such a manner that the bend in the test piece does not protrude beyond the edges when the plates are brought together, and that the ends are not held for more than $1/4''$. After exposure to cold dry air for the specified time and temperature, the jaws are rapidly brought together until they are $1''$ apart.

Medium	Dry Air
Time	5 hours
Temperature	-70°F

After this test the specimen shall show no signs of cracking.

(2) A similar test of the material as received shall also be made and the specimen shall show no signs of cracking after the test.

6. SAMPLES: Sampling procedures shall conform to ASTM D15-41. When the form in which the material is furnished is unsuitable for the proper preparation of the test specimens required, the vendor shall furnish sufficient material for such specimens from production-run materials which he guarantees to be of equal quality to the material supplied.

7. **TOLERANCES:** Unless otherwise specified on the drawing or purchase order, the following tolerances apply; all dimensions are in inches:

(a) Sheet and Strip.-

<u>Nominal Thickness</u>	<u>Tolerance plus or minus</u>
1/8 and less	1/64
Over 1/8 to 1/2, incl.	1/32
Over 1/2	3/64

(b) Tubing and Molded Hose.-

<u>Nominal Wall Thickness</u>	<u>Tolerance plus or minus</u>
Less than 1/16	0.005
1/16 and over	10%

(c) Extrusions and Molded Parts.- Sections may be as much as plus or minus 0.005 inch outside of drawing limits provided the cross-sectional area is within the limits given by the drawing dimensions.

8. **REPORTS:** Unless otherwise specified, the vendor shall furnish three copies of a notarized report of the results of tests to determine conformance to this specification. This report shall include the purchase order number, material specification number, vendor's compound number, percentages and specific type of synthetic or synthetics used, part number and quantity.

9. **IDENTIFICATION:** (a) Sheets.- Unless otherwise specified, each sheet shall be marked to show the manufacturer's identification, Predominant Polymer Symbol, Formula Number, AMS 3200, and the thickness in inches. The characters shall be not less than 3/8 inch in height and shall be applied in rows of constantly recurring symbols from one edge of the sheet to the opposite edge with rows spaced approximately 5 inches apart. The characters shall be clearly legible, and shall be applied to the material by suitable means and suitable marking fluid, and shall not be obliterated by normal handling.

(b) Extrusions and Molded Tubes.- Where the shape and nature of the material permit, each end of stock 10 feet or more in length shall be marked with the information and methods of 9(a) above.

(c) Where the shape and the nature of the materials, either extrusions, molded forms or strip stock, do not permit of the above marking, the identification shall appear on the package as in paragraph 10(b) below.

(d) Other forms shall be identified as agreed by the vendor and the purchaser.