

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 3202J

Issued 1 APR 1943
Revised 1 OCT 1991

Superseding AMS 3202H

Submitted for recognition as an American National Standard

NITRILE (NBR) RUBBER Dry Heat Resistant 55 - 65

1. SCOPE:

1.1 Form:

This specification covers a nitrile (NBR) rubber in the form of sheet, strip, tubing, extrusions, and molded shapes.

1.2 Application:

These products have been used typically for parts, such as packings, bushings, grommets, and seals, requiring resistance to dry heat, but usage is not limited to such applications.

1.3 Safety - Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 3202J

SAE

AMS 3202J

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2279 Tolerances, Rubber Products
 MAM 2279 Tolerances, Metric, Rubber Products
 AMS 2810 Identification and Packaging, Elastomeric Products

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM D 297 Rubber Products - Chemical Analysis
 ASTM D 395 Rubber Property - Compression Set
 ASTM D 412 Rubber Properties in Tension
 ASTM D 471 Rubber Property - Effect of Liquids
 ASTM D 518 Rubber Deterioration - Surface Cracking
 ASTM D 865 Rubber - Deterioration by Heating in Air (Test Tube Enclosure)
 ASTM D 1149 Rubber Deterioration - Surface Ozone Cracking in a Chamber
 (Flat Specimens)
 ASTM D 2137 Rubber Property - Brittleness Point of Flexible Polymers and
 Coated Fabrics
 ASTM D 2240 Rubber Property - Durometer Hardness

3. TECHNICAL REQUIREMENTS:**3.1 Material:**

Shall be a compound, based on an acrylonitrile-butadiene (NBR) elastomer, suitably cured to produce a product meeting the requirements of 3.2.

3.2 Properties:

The product shall conform to requirements of Table 1, 3.2.5, and 3.2.6; tests shall be performed on the product supplied and in accordance with specified ASTM methods, insofar as practicable:

TABLE 1 - Properties

Paragraph	Property	Requirement	Test Methods
3.2.1	As Received:		
3.2.1.1	Hardness, Durometer "A" or equivalent	60 ± 5	ASTM D 2240
3.2.1.2	Tensile Strength, minimum	1500 psi (10.3 MPa)	ASTM D 412; Die B or C
3.2.1.3	Elongation, minimum	250%	ASTM D 412, Die B or C

AMS 3202J

SAE

AMS 3202J

TABLE 1 - Properties (Continued)

Paragraph	Property	Requirement	Test Methods
3.2.1.4	Specific Gravity	Preproduction Value ± 0.02	ASTM D 297
3.2.2	Oil Resistance: (Immediate Deteriorated Properties)		ASTM D 471 ASTM Oil No. 3 100 °C ± 1 , (212 °F ± 2) 70 hours ± 0.5
3.2.2.1	Hardness Change, Durometer "A" or equivalent	-15 to +10	
3.2.2.2	Tensile Strength Change, maximum	-50%	
3.2.2.3	Elongation Change, maximum	-40%	
3.2.2.4	Volume Change	-10 to +50%	
3.2.2.5	Decomposition	None	
3.2.2.6	Surface Tackiness	None	
3.2.3	Dry Heat Resistance:		ASTM D 865 150 °C ± 3 , (302 °F ± 5) 70 hours ± 0.5
3.2.3.1	Hardness Change, Durometer "A" or equivalent	0 to +20	
3.2.3.2	Tensile Strength Change, maximum		
3.2.3.2.1	For parts other than extrusions	-60%	
3.2.3.2.2	For extruded parts	-70%	
3.2.3.3	Elongation Change, maximum		
3.2.3.3.1	For parts other than extrusions	-70%	
3.2.3.3.2	For extruded parts	-85%	
3.2.3.4	Surface Hardening	None	

AMS 3202J

SAE

AMS 3202J

TABLE 1 - Properties (Continued)

Paragraph	Property	Requirement	Test Methods
3.2.3.5	Bend (flat)	No cracking or checking	
3.2.4	Compression Set: Percent of Original Deflection, maximum	50	ASTM D 395, Method B 100 °C ± 1, (212 °F ± 2) 70 hours ± 0.5
3.2.5	Low-Temperature Resistance:		
3.2.5.1	Brittleness	Pass	ASTM D 2137, Method A -40 °C ± 1, (-40 °F ± 2)

3.2.6 Weathering: The product shall show no evidence of cracking when tested in accordance with ASTM D 1149 for 7 days at 40 °C ± 1 (104 °F ± 2). Test specimens shall be prepared and mounted in accordance with ASTM D 518, Method B.

3.2.7 Corrosion: The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service, determined by a procedure agreed upon by purchaser and vendor. Discoloration of metal shall not be considered objectionable.

3.3 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, smooth, as free from foreign material as commercially practicable, and free from imperfections detrimental to usage of the product.

3.4 Tolerances. (R)

Shall conform to all applicable requirements of AMS 2279 or MAM 2279:

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: (R)

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

AMS 3202J

SAE

AMS 3202J

4.2 Classification of Tests:

4.2.1 Acceptance Tests:
(R)

Tests for requirements shown in Table 2 are acceptance tests and shall be performed on each lot:

TABLE 2 - Acceptance Tests

Requirement	Paragraph
Hardness, as received	3.2.1.1
Tensile Strength, as received	3.2.1.2
Elongation, as received	3.2.1.3
Specific Gravity	3.2.1.4
Volume Change in oil	3.2.2.4
Compression Set	3.2.4
Tolerances	3.4

4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the first-article shipment of a product to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing:
(R)

Shall be as follows:

4.3.1 For Acceptance Tests: Sufficient product shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.