

Butadiene Acrylonitrile (NBR) Rubber
Dry Heat Resistant
55 - 65

RATIONALE

AMS3202M results from a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a nitrile (NBR) rubber in the form of sheet, strip, tubing, extrusions, and molded shapes.

1.2 Application

These products have been typically used for parts, such as packings, bushings, grommets, and seals, requiring resistance to dry heat, but usage is not limited to such applications. Each application should be considered individually.

1.3 Safety - Hazardous Materials

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS

2.1 The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.2 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2279 Tolerances, Rubber Products
AMS2810 Identification and Packaging, Elastomeric Products

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2009 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3202M>**

2.3 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM D 395	Rubber Property - Compression Set
ASTM D 412	Vulcanized Rubber and Thermoplastic Elastomers - Tension
ASTM D 471	Rubber Property - Effect of Liquids
ASTM D 792	Rubber Property - Specific Gravity
ASTM D 865	Rubber - Deterioration by Heating in Air (Test Tube Enclosure)
ASTM D 1149	Rubber Property - Deterioration - Surface Ozone Cracking in a Chamber (Flat Specimens)
ASTM D 2137	Rubber Property - Brittleness Point of Flexible Polymers and Coated Fabrics
ASTM D 2240	Rubber Property - Durometer Hardness

3. TECHNICAL REQUIREMENTS

3.1 Material

Shall be a compound, based on an acrylonitrile-butadiene (NBR) elastomer, suitably cured to produce a product meeting the requirements of 3.2.

3.2 Properties

The product shall conform to the following requirements in Table 1; 3.2.8 shall be performed on the product supplied and in accordance with specified ASTM methods, insofar as practicable:

TABLE 1 – INITIAL TEST REQUIREMENTS

	Property	Requirement	Test Method
3.2.1	Hardness, Durometer "A" or equivalent	60 ± 5	ASTM D 2240
3.2.2	Tensile Strength, min	1500 psi (10.3 MPa)	ASTM D 412, Die B or C
3.2.3	Elongation, min	250%	ASTM D 412, Die B or C
3.2.4	Specific Gravity	Preproduction Value ±0.02	ASTM D 792 (Hydrostatic Method)
3.2.5	Oil Resistance		ASTM D 471 IRM 903 oil (See 8.4) Temperature: 212 °F ± 2 (100 °C ± 1)
3.2.5.1	Hardness Change, Durometer "A" or equivalent	-15 to +10	Time: 70 hours ± 0.5
3.2.5.2	Tensile Strength Change, max	-50%	
3.2.5.3	Elongation Change, max	-40%	
3.2.5.4	Volume Change	-10 to +50%	
3.2.5.5	Decomposition	None	
3.2.5.6	Surface Tackiness	None	
3.2.6	Dry Heat Resistance		ASTM D 865 Temperature: 302 °F ± 5 (150 °C ± 3)
3.2.6.1	Hardness Change, Durometer "A" or equivalent	0 to +20	Time: 70 hours ± 0.5
3.2.6.2	Tensile Strength Change, max		
3.2.6.2.1	For parts other than extrusions	-60%	
3.2.6.2.2	For extruded parts	-70%	
3.2.6.3	Elongation Change, max		

TABLE 1 – INITIAL TEST REQUIREMENTS (CONTINUED)

Property	Requirement	Test Method
3.2.6.3.1 For parts other than extrusions	70%	
3.2.6.3.2 For extruded parts	-85%	
3.2.6.4 Surface Hardening	None	
3.2.6.5 Bend (flat)	No cracking or checking	
3.2.7 Compression Set		ASTM D 395 Method B
Percent of Original Deflection, max	50	Temperature: 212 °F ± 2 (100 °C ± 1)
		Time: 70 hours ± 0.5
3.2.8 Low-Temperature Resistance		
3.2.8.1 Brittleness	Pass	ASTM D 2137 Method A
		Temperature: -40 °F ± 1 (-40 °C ± 2)

3.3 Weathering

The product shall show no evidence of cracking when tested in accordance with ASTM D 1149 for 168 hours ± 0.5 at 40 °C ± 1 (104 °F ± 2). Test specimens shall be prepared and mounted in accordance with ASTM D 518, Method B.

3.4 Dimensions and Tolerances

Dimensions and tolerances shall be as specified in the parts standard, drawing or purchase document. If not specified, shall conform to all applicable requirements of AMS2279.

3.5 Toxicological Formulations

The material shall have no adverse effects on the health of personnel when used for its intended purpose in accordance with manufacturer's instructions and with appropriate handling procedures.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The manufacturer of the product shall be responsible for performance of all required tests. Purchaser reserves the right to sample and perform any testing deemed necessary to ensure that the product conforms to the AMS requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Requirements shown in Table 2 are acceptance tests and shall be performed on each lot:

TABLE 2 - ACCEPTANCE TEST REQUIREMENTS

Requirements	Paragraph
Hardness, as received	3.2.1
Tensile Strength, as received	3.2.2
Elongation, as received	3.2.3
Specific Gravity	3.2.4
Volume Change in oil	3.2.5.4
Compression Set	3.2.7
Tolerances	3.4

4.2.1.1 Lot

A quantity of one size of product processed and packaged as one production entity from a batch

4.2.1.2 Batch

The quantity of compound run through a mill or mixer at one time.

4.2.1.3 Random Sampling

The method shall be as specified in the parts standard, drawing or purchase document. If not specified, product shall be taken at random from each lot to perform all the required acceptance tests. The number of test iterations for each requirement shall be specified in the applicable test procedure.

4.2.1.4 Sample shall be from a production batch/lot

4.2.2 Preproduction Tests

All technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of the product by the manufacturer, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.3 Sampling and Testing

4.3.1 For Acceptance Tests

Sufficient product shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three except as specified in 4.3.1.4.

4.3.1.1 If specimens cannot be prepared from the product, ASTM test specimens prepared from the same batch and state of cure shall be used. When the product supplied is an extrusion of such shape that suitable test specimens cannot be cut from the product, a separate flat strip test sample from the same production lot shall be supplied upon request. This strip shall be prepared from tubing 1.000 inch \pm 0.063 (25.40 mm \pm 1.60) in OD by 0.075 inch \pm 0.008 (1.90 mm \pm 0.20) in wall thickness, mechanically slit and flattened into a strip while being extruded, and cured in the same manner as production product. When the product is a molded shape from which test specimens cannot be cut, a slab 6 inches (152 mm) square by 0.075 inch \pm 0.008 (1.90 mm \pm 0.20) thick molded from the same batch of compound shall be supplied upon request.

4.4 Approval

4.4.1 Sample product shall be approved by the purchaser before product for production use is supplied, unless such approval is waived by the purchaser. Results of the tests on production product shall be essentially equivalent to those on the approved sample. Production product made by the revised procedure shall not be shipped prior to receipt of reapproval. If necessary to make any change in parameters for the process control factors, manufacturer shall submit for reapproval a statement of the proposed changes in ingredients and/or processing and when requested, sample product.

4.4.2 Manufacturer shall use ingredients, manufacturing procedures, processes, and methods of inspection on production product which are essentially the same as those used on the approved sample.