

AEROSPACE MATERIAL SPECIFICATION



AMS 3217/5B

Issued JUL 1983
Revised JUN 1998
Reaffirmed NOV 2003

Superseding AMS 3217/5A

Test Slabs, Fluorosilicone (FVMQ) 55 - 65

1. SCOPE:

1.1 Form:

This specification covers a standard fluorosilicone (FVMQ) rubber stock in the form of molded test slabs.

1.2 Application:

See AMS 3217.

2. APPLICABLE DOCUMENTS:

See AMS 3217.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specifications:

The complete requirements for test slabs described herein and their procurement shall consist of this document and the latest issue of the basic specification AMS 3217.

3.2 Material:

Shall be a fluorosilicone (FVMQ) compounded to the formulation shown in Table 1.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2003 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: custsvc@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

TABLE 1 - Formulation

Ingredients	Parts
LS-63U [®] or equivalent ¹	100.0 (See 3.2.1)
Mapico 297 [®] or equivalent ¹	1.5 (See 3.2.2)
Cadox TS-5c [®] or equivalent ¹	1.3 (See 3.2.2)
Press Cure: 5 minutes \pm 0.5 at 115 °C \pm 3 (239 °F \pm 5)	
Oven Cure: 8 hours \pm 0.2 at 200 °C \pm 3 (392 °F \pm 5).	

¹Equivalent ingredients must be approved by SAE Committee CE.

3.2.1 Weigh parts to the nearest 0.1 gram.

3.2.2 Weigh parts to the nearest 0.02 gram.

3.3 Processing:

After the elastomer has banded on the rubber mill, the other ingredients shall be added in the order listed in 3.2.

3.3.1 The stock shall not be allowed to become hotter than can be handled with the bare hands; it is recommended that the stock be removed from the mill and cooled to room temperature before incorporating the final ingredient.

3.3.2 After all ingredients have been incorporated and the stock has been thoroughly milled, the stock shall be passed 10 times through a tight mill.

3.3.3 Suitable preforms shall be cut from the freshly milled stock and molded into test slabs as specified in ASTM D 3182, Figure 1.