

AEROSPACE
MATERIAL
SPECIFICATION

AMS 3239D
Superseding AMS 3239C

Issued 2-15-53
Revised 1-1-84

BUTYL (IIR) RUBBER
Phosphate Ester Resistant
85 - 95

1. SCOPE:

1.1 Form: This specification covers a butyl (IIR) rubber in the form of sheet, strip, tubing, extrusions, and molded shapes.

1.2 Application: Primarily for parts such as V-rings, gaskets, grommets, and seals requiring resistance to phosphate esters or low permeability to gases. Not suitable for use in contact with petroleum-base fluids due to excessive swell.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 2810 - Identification and Packaging, Elastomeric Products

REAFFIRMED

10-91

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS 3239D

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM D297 - Rubber Products - Chemical Analysis
- ASTM D395 - Rubber Property - Compression Set
- ASTM D412 - Rubber Properties in Tension
- ASTM D471 - Rubber Property - Effect of Liquids
- ASTM D518 - Rubber Deterioration - Surface Cracking
- ASTM D573 - Rubber - Deterioration in an Air Oven
- ASTM D624 - Rubber Property - Tear Resistance
- ASTM D797 - Rubber Property - Young's Modulus at Normal and Subnormal Temperatures
- ASTM D1149 - Rubber Deterioration - Surface Ozone Cracking in a Chamber (Flat Specimens)
- ASTM D2137 - Rubber Property - Brittleness Point of Flexible Polymers and Coated Fabrics
- ASTM D2240 - Rubber Property - Durometer Hardness

3. TECHNICAL REQUIREMENTS:

3.1 Material: Shall be a compound based on a butyl IIR elastomer, suitably cured to produce a product meeting the requirements of 3.2.

3.2 Properties: The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified ASTM methods, insofar as practicable:

3.2.1 As Received:

3.2.1.1	Hardness, Durometer "A" or equiv.	90 \pm 5	ASTM D2240
3.2.1.2	Tensile Strength, min	1500 psi (10.5 MPa)	ASTM D412, Die B or C
3.2.1.3	Elongation, min	200%	ASTM D412, Die B or C
3.2.1.4	Tear Resistance lb per in. (kg/m) min	80% of Preproduction Value	ASTM D624, Die B or C
3.2.1.5	Specific Gravity ρ	Preproduction	ASTM D297 Value \pm 0.03
3.2.2	<u>Phosphate Ester Resistance:</u> (Immediate Deteriorated Properties)		ASTM D471 Medium: Tri-n-butyl phosphate Temperature: 100°C \pm 1 (212°F \pm 2) Time: 70 hr \pm 0.5
3.2.2.1	Hardness Change, Durometer "A" or equiv.	0 to -35	

- 3.2.2.2 Tensile Strength Change, max -25%
- 3.2.2.3 Elongation Change, max -20%
- 3.2.2.4 Volume Change 0 to +30%

3.2.3 Dry Heat Resistance:

ASTM D573

- 3.2.3.1 Hardness Change, Durometer "A" or equiv. 0 to +5

Temperature: $100^{\circ}\text{C} \pm 1$
 $(212^{\circ}\text{F} \pm 2)$
 Time: 70 hr ± 0.5

- 3.2.3.2 Tensile Strength Change, max -15%
- 3.2.3.3 Elongation Change, max -35%

3.2.4 Compression Set:

ASTM D395, Method B

- 3.2.4.1 Percent of Original Deflection, max 90

Temperature: $100^{\circ}\text{C} \pm 1$
 $(212^{\circ}\text{F} \pm 2)$
 Time: 70 hr ± 0.5

3.2.5 Low Temperature Resistance:

- 3.2.5.1 Brittleness

Pass

ASTM D2137, Method A

Temperature: $-25^{\circ}\text{C} \pm 1$
 $(-13^{\circ}\text{F} \pm 2)$
 Time: 10 min. ± 0.5

- 3.2.5.2 Young's Modulus, max (See 8.2) 70,000 psi (48.5 MPa)

ASTM D797
 Temperature: $-40^{\circ}\text{C} \pm 1$
 $(-40^{\circ}\text{F} \pm 2)$

3.2.6 Weathering: The product, unless otherwise specified, shall show no evidence of cracking when tested in accordance with ASTM D1149 for seven days at $40^{\circ}\text{C} \pm 1$ ($105^{\circ}\text{F} \pm 2$). Test specimens shall be prepared and mounted in accordance with ASTM D518, Method B.

3.2.7 Corrosion: The product, unless otherwise specified, shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service, determined by a procedure agreed upon by purchaser and vendor. Discoloration of metal shall not be considered objectionable.

3.3 Quality: The product, as received by purchaser, shall be uniform in quality and condition, clean, smooth, as free from foreign materials as commercially practicable, and free from imperfections detrimental to usage of the product.

3.4 Tolerances: Unless otherwise specified, the following tolerances shall apply:

AMS 3239D

3.4.1 Sheet and Strip:

∅

TABLE I

Nominal Thickness (T) Inches	Tolerance, Inch Plus and Minus	
	Fixed	Closure (See 3.4.1.1)
Up to 0.400, incl	0.008	0.013
Over 0.400 to 0.630, incl	0.010	0.016
Over 0.630 to 1.000, incl	0.013	0.020
Over 1.000 to 1.600, incl	0.016	0.025
Over 1.600 to 2.500, incl	0.020	0.032
Over 2.500 to 4.000, incl	0.025	0.040
Over 4.000 to 6.300, incl	0.032	0.050
6.300 and over	0.005T	--

TABLE I (SI)

Nominal Thickness (T) Millimetres	Tolerance, Millimetres Plus and Minus	
	Fixed	Closure (See 3.4.1.1)
Up to 10.00, incl	0.20	0.32
Over 10.00 to 16.00, incl	0.25	0.40
Over 16.00 to 25.00, incl	0.32	0.50
Over 25.00 to 40.00, incl	0.40	0.63
Over 40.00 to 63.00, incl	0.50	0.80
Over 63.00 to 100.00, incl	0.63	1.00
Over 100.00 to 160.00, excl	0.80	1.25
160.00 and over	0.005T	--

3.4.1.1 Closure dimensions are across mold parting line.

∅

3.4.2 Tubing Diameter and Wall Thickness:

∅

TABLE II

Nominal OD or ID (D) (not both) and Wall Thickness Inches	Tolerance, Inch Plus and Minus	Ovality, %
		(See 3.4.2.1)
Up to 0.100, incl	0.013	10
Over 0.100 to 0.160, incl	0.016	15
Over 0.160 to 0.250, incl	0.020	15
Over 0.250 to 0.400, incl	0.025	15
Over 0.400 to 0.630, incl	0.032	15
Over 0.630 to 1.000, incl	0.040	15
Over 1.000	0.0350xD	15

TABLE II (SI)

Nominal OD or ID (D) (not both) and Wall Thickness Millimetres	Tolerance, Millimetres Plus and Minus	Ovality, % (See 3.4.2.1)
Up to 2.50, incl	0.32	10
Over 2.50 to 4.00, incl	0.40	15
Over 4.00 to 6.30, incl	0.50	15
Over 6.30 to 10.00, incl	0.63	15
Over 10.00 to 16.00, incl	0.80	15
Over 16.00 to 25.00, incl	1.00	15
Over 25.00	0.0350xD	15

3.4.2.1 Ovality applies to tubing ordered in straight lengths with wall thickness of 0.063 in. (1.60 mm) and over, and shall be computed from the difference between the minor and major axis diameter measurements, taken at the same transverse plane of the tube, expressed as a percentage of the nominal diameter.

3.4.3 Extrusions:

TABLE III

Nominal Cross-Sectional Dimension Inches	Tolerance, Inch Plus and Minus
Up to 0.100, incl (See 3.4.3.2)	0.013
Over 0.100 to 0.160, incl	0.016
Over 0.160 to 0.250, incl	0.020
Over 0.250 to 0.400, incl	0.025
Over 0.400 to 0.630, incl	0.032
Over 0.630 to 1.000, incl	0.040
Over 1.000 to 1.600, incl	0.050
Over 1.600 to 2.500, incl	0.063
Over 2.500	See 3.4.3.1

TABLE III (SI)

Nominal Cross-Sectional Dimension Millimetres	Tolerance, Millimetres Plus and Minus
Up to 2.50, incl (See 3.4.3.2)	0.32
Over 2.50 to 4.00, incl	0.40
Over 4.00 to 6.30, incl	0.50
Over 6.30 to 10.00, incl	0.63
Over 10.00 to 16.00, incl	0.80
Over 16.00 to 25.00, incl	1.00
Over 25.00 to 40.00, incl	1.25
Over 40.00 to 63.00, incl	1.60
Over 63.00	See 3.4.3.1

3.4.3.1 For dimensions over 2.500 in. (63.00 mm), tolerances shall be as agreed
 Ø upon by purchaser and vendor.

3.4.3.2 In general, cross-sectional dimensions less than 0.040 in. (1.00 mm) are
 Ø impractical to extrude.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all
 Ø samples for vendor's tests and shall be responsible for performing all
 required tests. Results of such tests shall be reported to the purchaser as
 required by 4.5. Purchaser reserves the right to sample and to perform any
 confirmatory testing deemed necessary to ensure that the product conforms to
 the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to the following
 requirements are classified as acceptance tests and shall be performed on
 each lot:

Requirements	Paragraph Reference
Hardness, as received	3.2.1.1
Tensile Strength, as received	3.2.1.2
Elongation, as received	3.2.1.3
Volume Change in oil	3.2.2.4
Compression Set	3.2.4

4.2.2 Preproduction Tests: Tests to determine conformance to all technical
 Ø requirements of this specification are classified as preproduction tests
 and shall be performed prior to or on the initial shipment of the product
 to a purchaser, when a change in material or processing, or both, requires
 reapproval as in 4.4.2, and when purchaser deems confirmatory testing to
 be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be as follows:

4.3.1 For Acceptance Tests: Sufficient product shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three. When the product supplied is an extrusion of such shape that suitable test specimens cannot be cut from the product, a separate flat strip test sample shall be supplied upon request. This strip shall be prepared from tubing 1.00 in. \pm 0.063 (25 mm \pm 1.60) in OD by 0.075 in. \pm 0.008 (1.90 mm \pm 0.20) in wall thickness, mechanically slit and flattened into a strip while being extruded, and cured in the same manner as production material. When the product is a molded shape from which test specimens cannot be cut, a slab 6 x 6 x 0.075 in. (150 x 150 x 2 mm) molded from the same batch of compound shall be supplied upon request.

4.3.1.1 A lot shall be all product from the same batch of compound processed in one continuous run and presented for vendor's inspection at one time. An inspection lot shall not exceed 500 lb (225 Kg).

4.3.1.2 A batch shall be the quantity of compound run through a mill or mixer at one time.

4.3.1.3 When a statistical sampling plan and acceptance quality level (AQL) have been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.5.1 shall state that such plan was used.

4.3.2 For Preproduction Tests: As agreed upon by purchaser and vendor.

4.4 Approval:

4.4.1 Sample material shall be approved by purchaser before material for production use is supplied, unless such approval be waived by purchaser. Results of tests on production material shall be essentially equivalent to those on the approved sample.

4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production material which are essentially the same as those used on the approved sample material. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in material or processing, or both, and, when requested, sample material. Production material made by the revised procedure shall not be shipped prior to receipt of reapproval.