

# AERONAUTICAL MATERIAL SPECIFICATIONS

## AMS 3240c

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 11-1-44  
Revised 1-15-59

### SYNTHETIC RUBBER Weather Resistant, Chloroprene Type (35 - 45)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. FORM: Sheet, strip, tubing, molded shapes, extrusions, or as ordered.
3. APPLICATION: Primarily for parts, such as window channels, bumper pads, chafing strips, and seals, requiring resistance to weather.
4. TECHNICAL REQUIREMENTS:
  - 4.1 General:
    - 4.1.1 Condition: Unless otherwise specified, a suitably cured product shall be furnished.
    - 4.1.2 Weathering: When specified, the product shall have weather resistance acceptable to the purchaser as determined by a procedure agreed upon by purchaser and vendor.
    - 4.1.3 Corrosion: The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service. Discoloration of metal shall not be considered objectionable.
  - 4.2 Properties: The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with listed ASTM methods, insofar as practicable. When the product supplied is an extrusion of such shape that suitable test specimens cannot be cut from the product, a separate flat strip test sample shall be supplied upon request. This strip shall be prepared from 1 in.  $\pm$  1/16 OD by 0.075 in.  $\pm$  0.008 thick wall tubing which shall be mechanically split and flattened into a strip while being extruded and then cured in the same manner as production material.
    - 4.2.1 As Received:

4.2.1.1 Hardness, Durometer "A" or equiv.	40 $\pm$ 5	
4.2.1.2 Tensile Strength, psi, min	900	ASTM D412-51T, Die B or C
4.2.1.3 Elongation, %, min	350	ASTM D412-51T, Die B or C
∅ 4.2.1.4 Tensile Stress at 100% Elongation, psi	See Note 1	ASTM D412-51T, Die B or C
∅ 4.2.1.5 Tear Resistance, lb per in., min	See Note 2	ASTM D624-54, Die B
∅ 4.2.1.6 Specific Gravity	See Note 3	ASTM D297-55T

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. They are not to be used as a basis for any legal action. The use by anyone engaged in industry or trade is entirely voluntary. There is no obligation to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

4.2.2	<u>Oil Resistance:</u> (Immediate Deteriorated Properties)		ASTM D471-57T
			Medium: ASTM Oil No. 3
			Temperature: 212 F $\pm$ 2
			Time: 70 hr
4.2.2.1	Tensile Strength Change, %, max (based on area before immersion)	-70	
4.2.2.2	Elongation Change, %, max	-50	
4.2.2.3	Volume Change (Method A), %, max	+60 to +120	
4.2.2.4	Decomposition	None	
4.2.2.5	Surface Tackiness	None	
4.2.3	<u>Dry Heat Resistance:</u>		ASTM D573-53
			Temperature: 212 F $\pm$ 2
			Time: 70 hr
4.2.3.1	Hardness Change, Durometer "A" or equiv.	0 to +15	
4.2.3.2	Tensile Strength Change, %, max	-25	
4.2.3.3	Elongation Change, %, max		
∅ 4.2.3.3.1	For parts other than extrusions	-50	
∅ 4.2.3.3.2	For extruded parts	-60	
4.2.3.4	Bend (flat)	No cracking or checking	
4.2.4	<u>Compression Set:</u>		ASTM D395-55, Method B
			Temperature: 212 F $\pm$ 2
			Time: 70 hr
			Compressed to 60% of original thickness
4.2.4.1.1	Per cent of original deflection, max For parts other than extrusions	75	
∅ 4.2.4.1.2	For extruded parts	83	
4.2.4.2	Per cent of original thickness, max		
4.2.4.2.1	For parts other than extrusions	30	
∅ 4.2.4.2.2	For extruded parts	33	
4.2.5	<u>Low Temperature Resistance:</u>		
4.2.5.1	Brittleness	Pass	ASTM D746-57T, Procedure B
∅			Temperature: -40 F $\pm$ 2
4.2.5.2	Young's Modulus, psi, max (See Note 4)	10,000	ASTM D797-46
∅			Temperature: -40 F $\pm$ 2
Note 1.	Value to be reported. Specimens shall be prestretched to 125% elongation twice within 5 min. of test.		
∅ Note 2.	Value to be reported.		

Note 3. Value to be reported. Production material shall be within  $\pm 0.02$  of the qualification test value.

Note 4. This test is not normally required but may be used in case of disagreement on the results of the brittleness test.

5. **QUALITY:** The product shall be uniform in quality and condition, clean, smooth, and free from foreign materials and from imperfections detrimental to fabrication, appearance, or performance of parts.

6. **TOLERANCES:** Unless otherwise specified, the following tolerances apply:

6.1 Sheet and Strip:

Nominal Thickness Inches	Tolerance, Inch Plus and Minus
1/8 and under	1/64
Over 1/8 to 1/2, incl	1/32
Over 1/2	3/64

6.2 Tubing:

6.2.1 Nominal OD or ID (not both), Inches	Tolerance Plus and Minus	Ovality (See Note 5)
1/2 and under	0.020 in.	10%
Over 1/2 to 1, incl	0.030 in.	15%
Over 1	4%	15%

Note 5. Ovality applies to tubing ordered in straight lengths with wall thickness of 1/16 in. and over, and shall be computed from the difference of the minor and major axis diameter measurements, taken at the same location on the tube, expressed as a percentage of the nominal diameter.

6.2.2 Nominal Wall Thickness Inch	Tolerance Plus and Minus
Under 1/16	0.005 in.
1/16 and over	10%

7. REPORTS:

7.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report stating that the product meets the requirements of this specification. This report shall include the purchase order number, material specification number, vendor's compound number, values to be reported, form or part number, and quantity.