

SEALING COMPOUND, LOW ADHESION, CORROSION INHIBITING  
9,000 - 14,000 Poises (900 - 1400 Pa·s), 1/2 Hour Application Time (B-1/2)

1. SCOPE:

- 1.1 Form: This specification covers accelerated curing synthetic rubber compounds with corrosion inhibitors and low adhesive strength supplied as a two-component system.
- 1.2 Application: Primarily for sealing aircraft access doors and accessories where gaskets are required. Material specified herein is classified as a B-1/2 sealing compound; the compound being suitable for application by an extrusion gun or spatula with a minimum application time after mixing of 1/2 hour.

2. APPLICABLE DOCUMENTS: See AMS 3267.

3. TECHNICAL REQUIREMENTS:

- 3.1 Basic Specification: The complete requirements for procuring the sealing compound described herein shall consist of this document and the latest issue of the basic specification, AMS 3267.
- 3.2 Properties: Compound, mixed in accordance with manufacturer's instructions and cured as specified in the basic specification, shall conform to the following requirements, determined in accordance with test methods listed in AMS 3267 and herein:

3.2.1 Color

- |                        |          |
|------------------------|----------|
| 3.2.1.1 Base Compound  | Reddish  |
| 3.2.1.2 After Curing   | Reddish  |
| 3.2.2 Specific Gravity | 1.65 max |

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

# AMS 3267/2

3.2.3	Nonvolatile Content	92% by weight, min
3.2.4	Viscosity of Base Compound (See 4.2)	9,000 - 14,000 poises (900 - 1400 Pa·s)
3.2.5	Flow (See 4.3)	0.1 - 0.75 in. (2.5 - 19.0 mm)
3.2.6	Application Time (See 4.4)	1/2 hr after the beginning of mixing, 15 per min., min, shall be extruded
3.2.7	Tack-Free Time	10 hr max, measured from the beginning of mixing
3.2.8	Hardness (cure time to attain 30 Durometer "A" min)	24 hr
3.2.9	Peel Adhesion	4 lb per in. (700 N/m) width, max 98% adhesive failure, min
3.2.10	Resistance to Heat	No visual evidence of softening, sponging, blistering, checking, cracking, shrinkage, or powdering
3.2.11	Resistance to Salt Water and Hydrocarbons	No visual evidence of softening, blistering, or evidence of corrosion
3.2.12	Weight loss and Flexibility	No cracking when bent, 8%, max, weight loss
3.2.13	Low Temperature Flexibility	No visual evidence of cracking or checking
3.2.14	Accelerated Storage Stability	
3.2.14.1	Application Time	1/2 hr min, measured from the beginning of mixing
3.2.14.2	Tack-Free Time	10 hr max, measured from the beginning of mixing
3.2.14.3	Viscosity of Base Compound	9,000 - 14,000 poises (900 - 1400 Pa·s)
3.2.15	Soluble Chromate Content	2.5% by weight, min

#### 4. QUALITY ASSURANCE PROVISIONS: See AMS 3267 and the following provisions:

4.1 Application of Sealing Compound: Unless otherwise specified herein, test panels shall be given an application of sealing compound to produce a coating having a thickness of 1/8 in.  $\pm$  1/64 (3  $\pm$  0.5 mm) when cured.

- 4.2 Viscosity of Base Compound: Shall be determined with the base compound placed in a 1 qt (1 L) can. The can shall be filled with base compound to within 1/2 in. (12.5 mm) of the top, covered, and stored at  $25^{\circ}\text{C} \pm 1$  ( $77^{\circ}\text{F} \pm 2$ ) for at least 8 hours. The base compound shall then be thoroughly mixed by stirring slowly for 3 min. after which the can shall be closed and the base compound allowed to stand for 1 hour. The Brookfield Model RVF viscosimeter, or equivalent, shall be used and the readings obtained converted to poises. The No. 7 spindle at 2 rpm shall be used. The highest reading shall be taken after the instrument has run in the compound for 1 minute.
- 4.3 Flow: A standard Semco sealant gun cartridge, or equivalent, fitted with a nozzle, shall be filled with freshly mixed sealing compound. The gun and sealing compound shall be maintained at standard conditions throughout the test. The test shall be conducted with a flow-test jig as shown in Fig 1. Depth of plunger tolerance is critical and shall be controlled within the tolerance during all tests. The flow-test jig shall be placed on a table with the front face upward and the plunger depressed to the limit of its travel. Within 15 min. after the beginning of mixing, enough of the mixed sealing compound shall be extruded from the application gun to fill the recessed cavity of the jig and leveled off even with the block. The test at this interval shall be considered the initial flow of the sealing compound. Within 10 sec after the leveling operation, the jig shall be placed upright on its end and the plunger immediately advanced to the limit of its forward travel. The flow measurement shall be taken 30 min. after the sealing compound has been applied to the test jig. The flow shall be measured from tangent to the lower edge of the plunger to the furthest point to which flow has advanced.
- 4.4 Application Time: The base compound, accelerator, and application gun shall be stabilized at standard conditions for at least 8 hr before not less than 250 g of base compound is mixed with the proper amount of accelerator. The mixed sealing compound shall be promptly used to fill a standard Semco sealing compound gun cartridge, or equivalent, having a Semco 440 nozzle with an orifice diameter of  $0.125 \text{ in.} \pm 0.004$  ( $3.18 \text{ mm} \pm 0.13$ ). The gun and sealing compound shall be maintained at standard conditions throughout the test. The gun shall be attached to a constant air supply of  $90 \text{ psi} \pm 5$  ( $620 \text{ kPa} \pm 35$ ). From 2 to 3 in. (50 to 80 mm) of sealing compound shall be extruded initially to clear trapped air. At the end of 1/2 hr, measured from the beginning of the mixing period, the sealing compound shall be extruded onto a suitable receptacle for 1 min. and the amount of extruded sealing compound determined.
5. PREPARATION FOR DELIVERY: See AMS 3267.
6. ACKNOWLEDGMENT: See AMS 3267.
7. REJECTIONS: See AMS 3267.
8. NOTES: See AMS 3267.