

AEROSPACE

MATERIAL SPECIFICATIONS

AMS 3274D

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 12-1-51

Revised 2-15-65

SYNTHETIC RUBBER SHEET, NYLON FABRIC REINFORCED Aromatic Fuel Resistant

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. FORM: Sheet, and shapes molded and cured from partly cured sheet.
3. APPLICATION: Primarily for diaphragms in aircraft power plant fuel supply and control systems.
4. MATERIAL AND FABRICATION: Basis material shall be either a plain weave, or 2-up and 1-down twill weave, nylon fabric coated, on both sides unless otherwise specified, with a nitrile type of synthetic rubber compound. Thickness of coating shall be substantially equal and uniform on both sides of the sheet.
5. TECHNICAL REQUIREMENTS:
 - 5.1 General:
 - 5.1.1 Color: Shall be black.
 - 5.1.2 Surface Cleanliness: Material having evenly dusted surfaces will be acceptable. When specified, surfaces shall be capable of being cleaned without damage to the material and shall be cementable.
 - 5.1.3 Weathering: When specified, the product shall have weather resistance acceptable to the purchaser as determined by a procedure agreed upon by purchaser and vendor.
 - 5.1.4 Corrosion: The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service. Discoloration of metal shall not be considered objectionable.
 - 5.2 Properties: The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with the issue of specified ASTM methods listed in the latest issue of AMS 2350, insofar as practicable.

5.2.1 As Received:

5.2.1.1 Breaking Strength,

ASTM D751

Grab Method, lb, min

Nominal Thickness, in.

Warp Filling

0.008	35	35
0.010, 0.013	65	60
0.017, 0.020		
0.025	300	300
0.030	65	60
0.050	300	300

Section 8.3 of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no obligation to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report, in formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

5.2.1.2 Tear Resistance, Trapezoid Method, lb, min ASTM D751

Nominal Thickness, in.	Warp	Filling
0.008, 0.010, 0.013)	2.0	2.0
0.017, 0.020)		
0.025	25.0	25.0
0.030	5.0	5.0
0.050	25.0	25.0

5.2.1.3 Bursting Strength, Diaphragm Bursting Tester, psi, min ASTM D751
Nominal Thickness, in.

0.008	75
0.010, 0.013)	
0.017, 0.020)	135
0.025	500
0.030	135
0.050	500

5.2.1.4 Adhesion, lb per in. width, min ASTM D751

7

5.2.2 Non-Aromatic Fuel Resistance:

Ø (After 24 hr drying at 70 C ± 1 (158 F ± 1.8))

ASTM D471

Medium: ASTM Ref. Fuel A

Temperature: 20 - 30 C

(68 - 86 F)

Time: 24 hr

5.2.2.1 Volume Change, %

Nominal Thickness, in.

0.008	-20 to +10
0.010, 0.013, 0.017)	
0.020, 0.025, 0.030)	-25 to 0
0.050)	

5.2.3 Aromatic Fuel Resistance:

Ø (Immediate Deteriorated Properties)

ASTM D471

Medium: ASTM Ref. Fuel B

Temperature: 20 - 30 C

(68 - 86 F)

Time: 24 hr

5.2.3.1 Volume Change, %

Nominal Thickness, in.

0.008, 0.010)	0 to +35
0.013, 0.017)	
0.020, 0.025)	
0.030, 0.050)	0 to +40

5.2.3.2 Volume Change on Drying

(after 24 hr aromatic fuel immersion) at 70 C ± 1 (158 F ± 1.8)) for 24 hr, %
(based on unimmersed volume)

-25 to 0

www.amscrm.com : Click to view the full PDF of ams3274d

5.2.4 Dry Heat Resistance:

ASTM D573

Temperature: 100 C ± 1
(212 F ± 1.8)

Time: 70 hr

5.2.4.1 Breaking Strength,
Grab Method, lb, min
Nominal Thickness, in.

ASTM D751

Nominal Thickness, in.	Warp	Filling
0.008	35	35
0.010, 0.013)	65	60
0.017, 0.020)	300	300
0.025	65	60
0.030	300	300
0.050		

5.2.4.2 Bursting Strength, Diaphragm
Bursting Tester, psi, min
Nominal Thickness, in.

ASTM D751

0.008	75
0.010, 0.013)	135
0.017, 0.020)	500
0.025	135
0.030	500
0.050	

5.2.4.3 Surface Hardening

None

5.2.4.4 Bend (flat)

No cracking

∅ 5.2.5 Low Temperature Brittleness:

ASTM D2137

5.2.5.1 As Received

Pass

Temperature: -55 C ± 1
(-67 F ± 1.8)

5.2.5.2 After Aromatic Fuel Aging
Without Drying

Pass

Time: 10 min.

6. QUALITY: The product shall be uniform in quality and condition, clean, smooth, and free from foreign materials and from imperfections detrimental to fabrication, appearance, or performance of parts.

7. THICKNESSES AND TOLERANCES: Unless otherwise specified, sheet shall be supplied in nominal thicknesses of 0.008, 0.010, 0.013, 0.017, 0.020, 0.025, 0.030, and 0.050 in., as ordered; tolerances shall be as specified below.

7.1 Thickness:

∅

Nominal Thickness, Inch	Tolerance, Inch	
	Plus	Minus
0.008	0.002	0.001
0.010, 0.013, 0.017)	0.002	0.002
0.020, 0.025, 0.030)		
0.050	0.003	0.003

∅ 7.2 Width: +1.0 inch.