

AEROSPACE MATERIAL SPECIFICATION



AMS 3332D

Issued JUL 1957
Revised APR 1990
Reaffirmed APR 2001

Superseding AMS 3332C

Silicone Rubber Extreme Low-Temperature Resistant 15 - 30

FOREWORD

This Reaffirm contains format/editorial changes only.

1. SCOPE:

1.1 Form:

This specification covers an extreme low-temperature-resistant silicone rubber in the form of sheet, strip, and molded shapes.

1.2 Application:

Primarily for rubber-like parts required to operate or seal from -80 to +230 °C (-112 to +446 °F), compounded especially for operation at extreme low temperatures. Silicone rubber is resistant to deterioration by weathering and by high-aniline-point petroleum-base oils and remains flexible over the temperature range noted. These products are not normally suitable for use in contact with low-aniline-point petroleum-base fluids, including fuels, due to excessive swelling.

1.3 Safety - Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2001 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

2.1.1 Aerospace Material Specifications:

- AMS 2279 Tolerances, Rubber Products
- MAM 2279 Tolerances, Metric, Rubber Products
- AMS 2810 Identification and Packaging, Elastomeric Products

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

- ASTM D 297 Rubber Products - Chemical Analysis
- ASTM D 395 Rubber Property - Compression Set
- ASTM D 412 Rubber Properties in Tension
- ASTM D 471 Rubber Property - Effect of Liquids
- ASTM D 518 Rubber Deterioration - Surface Cracking
- ASTM D 573 Rubber - Deterioration in an Air Oven
- ASTM D 624 Rubber Property - Tear Resistance
- ASTM D 797 Rubber Property - Young's Modulus at Normal and Subnormal Temperatures
- ASTM D 1149 Rubber Deterioration - Surface Ozone Cracking in a Chamber (Flat Specimens)
- ASTM D 2137 Rubber Property - Brittleness Point of Flexible Polymers and Coated Fabrics
- ASTM D 2240 Rubber Property - Durometer Hardness

3. TECHNICAL REQUIREMENTS:

3.1 Material:

Shall be a compound, based on a silicone rubber, suitably cured to produce a product meeting the requirements of 3.2.

3.2 Properties:

The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified ASTM methods, insofar as practicable:

TABLE 1

3.2.1	As Received:			
3.2.1.1	Hardness, Durometer "A" or equivalent	15 - 30	ASTM D 2240	
3.2.1.2	Tensile Strength, minimum	400 psi (2.76 MPa)	ASTM D 412, Die B or C	
3.2.1.3	Elongation, minimum	350%	ASTM D 412, Die B or C	
3.2.1.4	Tear Resistance, minimum	30 pounds force per inch (5.25 kN/m)	ASTM D 624, Die B	
3.2.1.5	Specific Gravity	Preproduction Value ± 0.03	ASTM D 297	
3.2.2	Petroleum Lubricating Oil Resistance: (Immediate Deteriorated Properties)		ASTM D 471 Medium: Temperature:	ASTM Oil No. 1 175 °C ± 3
3.2.2.1	Hardness Change, Durometer "A" or equivalent	-10 to +5	Time:	(347 °F ± 5) 70 hours ± 0.5
3.2.2.2	Tensile Strength Change, maximum	-50%		
3.2.2.3	Elongation Change, maximum	-20%		
3.2.2.4	Volume Change	0 to +25%		
3.2.2.5	Decomposition	None		
3.2.2.6	Surface Tackiness	None		
3.2.3	Dry Heat Resistance:		ASTM D 573 Temperature:	225 °C ± 3
3.2.3.1	Hardness Change, Durometer "A" or equivalent	-5 to +10	Time:	(437 °F ± 5) 22 hours ± 0.5
3.2.3.2	Tensile Strength Change, maximum	-15%		
3.2.3.3	Elongation Change, maximum	-20%		
3.2.3.4	Bend (flat)	No cracking or checking		

TABLE 1 (Continued)

3.2.4	Compression Set:		ASTM D 395, Method B Temperature: 175 °C ± 3
3.2.4.1	Percent of Original Deflection, maximum	60	(347 °F ± 5) Time: 22 hours ± 0.5
3.2.5	Low-Temperature Resistance:		
3.2.5.1	Brittleness	Pass	ASTM D 2137, Method A Temperature: -80 °C ± 3 (-112 °F ± 5)
3.2.5.2	Young's Modulus, maximum (See 8.2)	1000 psi (6.90 MPa)	ASTM D 797 Temperature: -75 °C ± 3 (-103 °F ± 5) Time: 5 hours ± 0.2

3.2.6 Weathering: The product shall show no evidence of cracking when tested in accordance with ASTM D 1149 for 7 days at 40 °C ± 1 (104 °F ± 2). Test specimens shall be prepared and mounted in accordance with ASTM D 518, Method B.

3.2.7 Corrosion: The rubber shall not have a corrosive effect on other materials, determined by a procedure agreed upon by purchaser and vendor. Discoloration of metal shall not be considered objectionable.

3.3 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, smooth, as free from foreign material as commercially practicable, and free from imperfections detrimental to usage of the product.

3.4 Tolerances:

Shall conform to all applicable requirements of AMS 2279 or MAM 2279.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for the following requirements are acceptance tests and shall be performed on each lot:

TABLE 2

Requirement	Paragraph Reference
Hardness, as received	3.2.1.1
Tensile Strength, as received	3.2.1.2
Elongation, as received	3.2.1.3
Specific Gravity	3.2.1.5
Compression Set	3.2.4
Brittleness	3.2.5.1

4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of the product to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing:

Shall be as follows:

4.3.1 For Acceptance Tests: Sufficient product shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

4.3.1.1 If test specimens cannot be prepared from the product, ASTM test specimens prepared from the same batch and state of cure shall be used. When the product is a molded shape from which test specimens cannot be cut, a slab 6 x 6 inches (152 x 152 mm) by 0.075 inch \pm 0.008 (1.90 mm \pm 0.20) molded from the same batch of compound shall be supplied upon request.

4.3.1.2 A lot shall be all product from the same batch of compound processed in one continuous run and presented for vendor's inspection at one time.

4.3.1.3 A batch shall be the quantity of compound run through a mill or mixer at one time.

4.3.1.4 When a statistical sampling plan has been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.6.1 shall state that such plan was used.

4.3.2 For Preproduction Tests: As agreed upon by purchaser and vendor.

4.4 Approval:

4.4.1 Sample product shall be approved by purchaser before product for production use is supplied, unless such approval be waived by purchaser. Results of tests on production product shall be essentially equivalent to those on the approved sample.

4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production product which are essentially the same as those used on the approved sample product. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in ingredients and/or processing and, when requested, sample product. Production product made by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests to determine conformance to the acceptance test requirements and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, lot number, AMS 3332D, vendor's compound number, form and size or part number, and quantity.

4.6 Resampling and Retesting:

If any specimen used in the above tests fails to meet the specified requirements, disposition of the product may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the product represented and no additional testing shall be permitted. Results of all tests shall be reported.