



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 3336B
Superseding AMS 3336A

Issued 3-1-55
Revised 7-1-76

SILICONE RUBBER Extreme-Low-Temperature Resistant 55 - 65

1. SCOPE:

1.1 Form: This specification covers an extreme-low-temperature-resistant silicone rubber in the form of sheet, strip, tubing, molded shapes, and extrusions.

1.2 Application: Primarily for rubber-like parts required to operate or seal at temperatures from -75° to +120° C (-103° to +248° F), compounded especially for operation at extreme low temperatures. Silicone elastomer is resistant to deterioration by weathering and aircraft piston engine oil and remains flexible over the temperature range noted. This material is not normally suitable for use in contact with gasoline or aromatic fuels and low-aniline-point petroleum-base fluids due to excessive swelling of the elastomer.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods
AMS 2810 - Identification and Packaging, Elastomeric Products

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D297 - Chemical Analysis of Rubber Products
ASTM D395 - Compression Set of Vulcanized Rubber
ASTM D412 - Tension Testing of Vulcanized Rubber
ASTM D471 - Change in Properties of Elastomeric Vulcanizates Resulting from Immersion in Liquids
ASTM D573 - Accelerated Aging of Vulcanized Rubber by the Oven Method
ASTM D624 - Tear Resistance of Vulcanized Rubber
ASTM D797 - Young's Modulus in Flexure of Elastomers at Normal and Subnormal Temperatures
ASTM D2137 - Low-Temperature Impact Test for Brittleness Determination of Flexible Polymeric Materials or Fabrics Coated Therewith, or Both
ASTM D2240 - Indentation Hardness of Rubber and Plastics by Means of a Durometer

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia PA 19120.

2.3.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

SAE Technical Board rules provide that: "All technical reports, including standards and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

AMS 3336B

- 2 -

3.1 Material: Shall be a compound based on a silicone rubber, suitably cured to produce a product meeting the requirements of 3.2.

3.2 Properties: The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified ASTM methods, insofar as practicable:

3.2.1 As Received:

3.2.1.1 Hardness, Durometer 60 ± 5 ASTM D2240
Ø "A" or equiv.

3.2.1.2 Tensile Strength, min 600 psi (4.14 MPa) ASTM D412, Die B or C

3.2.1.3 Elongation, min 150% ASTM D412, Die B or C

3.2.1.4 Tear Resistance, min 40 lb per in. (7.0 kN/m) ASTM D624, Die B

3.2.1.5 Specific Gravity Qualification Value ± 0.03 ASTM D297
Ø

3.2.2 Petroleum Lubricating Oil Resistance: (Immediate Deteriorated Properties)

ASTM D471

Medium: ASTM Oil No. 1

Temperature: $100^{\circ}\text{C} \pm 1$
($212^{\circ}\text{F} \pm 1.8$)

Time: 70 hr ± 0.5

3.2.2.1 Hardness Change, Durometer -10 to +5
"A" or equiv.

3.2.2.2 Tensile Strength Change, -20%
max

3.2.2.3 Elongation Change, max -10%

3.2.2.4 Volume Change 0 to +10%

3.2.2.5 Decomposition None

3.2.2.6 Surface Tackiness None

3.2.3 Dry Heat Resistance:

ASTM D573

Temperature: $100^{\circ}\text{C} \pm 1$
($212^{\circ}\text{F} \pm 1.8$)

Time: 24 hr ± 0.5

3.2.3.1 Hardness Change, Duro- 0 to +5
meter "A" or equiv.

3.2.3.2 Tensile Strength Change, -10%
max

3.2.3.3 Elongation Change, max -15%

3.2.3.4 Bend (flat) No cracking
or checking

3.2.4 Compression Set:

ASTM D395, Method B

3.2.4.1 Percent of Original Deflection, max

30

Temperature: 100° C \pm 1
(212° F \pm 1.8)
Time: 22 hr \pm 0.5

3.2.5 Low Temperature Resistance:

3.2.5.1 Brittleness
 \emptyset

Pass

ASTM D2137, Method A

Temperature: -80° C \pm 3
(112° F \pm 5.4)

3.2.5.2 Young's Modulus, max
 \emptyset

10,000 psi
(69 MPa)

ASTM D797

Temperature: -75° C \pm 3
(-103° F \pm 5.4)
Time: 5 hr \pm 0.2

3.2.6 **Weathering:** When specified, the product shall have weather resistance acceptable to the purchaser, determined by a procedure agreed upon by purchaser and vendor.

3.2.7 **Corrosion:** The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service. Discoloration of metal shall not be considered objectionable.

3.3 **Quality:** The product shall be uniform in quality and condition, clean, smooth, as free from foreign material as commercially practicable, and free from imperfections detrimental to fabrication, appearance, or performance of parts.

3.4 **Tolerances:** Unless otherwise specified, the following tolerances shall apply:

3.4.1 **Sheet and Strip:**

TABLE I

Nominal Thickness Inches	Tolerance, Inch plus and minus
Up to 0.125, incl	0.016
Over 0.125 to 0.500, incl	0.031
Over 0.125	0.047

TABLE I (SI)

Nominal Thickness Millimetres	Tolerance, Millimetres plus and minus
Up to 3.18, incl	0.41
Over 3.18 to 12.70, incl	0.79
Over 12.70	1.19

3.4.2 **Tubing:**

3.4.2.1 **Diameter:**

TABLE II

Nominal OD or ID (not both), Inches	Tolerance plus and minus	Ovality, % (See 3.4.2.1.1)
Up to 0.500, incl	0.020 in.	10
Over 0.500 to 1.000, incl	0.030 in.	15
Over 1.000	4%	15

TABLE II (SI)

Nominal OD or ID (not both), Millimetres	Tolerance plus and minus	Ovality, % (See 3.4.2.1.1)
Up to 12.70, incl	0.51 mm	10
Over 12.70 to 25.40, incl	0.76 mm	15
Over 25.40	4%	15

3.4.2.1.1 Ovality applies to tubing ordered in straight lengths with wall thickness of 0.063 in. (1.60 mm) and over and shall be computed from the difference between the minor and major axis diameter measurements, taken at the same transverse plane on the tube, expressed as a percentage of the nominal diameter.

3.4.2.2 Wall Thickness:

TABLE III

Nominal Wall Thickness Inches	Tolerance plus and minus
Up to 0.063, excl	0.005 in.
0.063 and over	10%

TABLE III (SI)

Nominal Wall Thickness Millimetres	Tolerance plus and minus
Up to 1.60, excl	0.13 mm
1.60 and over	10%

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests: