

Issued 1967-04
Reaffirmed 2003-11
Revised 2014-05

Superseding AMS3347B

Rubber, Silicone
1200 psi (8.27 MPa), High Modulus
45 - 55

RATIONALE

AMS3347C results from a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a silicone rubber material that can be used to manufacture product in the form of sheet, strip, tubing, extrusions, and molded shapes.

This specification should not be used to address products such as O-rings, compression seals, O-ring cord, and molded-in-place gaskets.

1.2 Application

These products have been used typically for parts required to operate or seal from -103 to +401 °F (-75 to +205 °C), compounded especially for high strength, but usage is not limited to such applications. Silicone elastomer is resistant to deterioration by weathering and by high-aniline-point petroleum-base oils and remains flexible over the temperature range noted. These products are not normally suitable for use in contact with gasoline or aromatic fuels and low-aniline-point petroleum-base fluids due to excessive swelling.

1.3 Terms / Definitions

1.3.1 "Material"

The mixed rubber compound used to manufacture product.

1.3.2 "Product"

The 'end product' being supplied to the contract/purchase order originator, usually in the form(s) specified in 1.1 above.

1.3.3 "Lot"

Shall be all product from the same batch of compound processed in one continuous run and submitted for inspection at one time. The material batch size allowed to form any single inspection lot of product shall not exceed 500 pounds (227 kg).

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2013 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3347C>**

1.3.4 "Batch"

Shall be the quantity of compound run through a mill or mixer at one time.

(Note: Smaller batches of mixed compound may be formed into a larger batch by utilizing a cross blending process that insures the homogenous nature of the newly formed larger batch. When utilizing this process all ingredient traceability of the smaller batches must be maintained and directly tied to the resulting larger batch. Only the resulting larger batch needs to be subject to Batch Acceptance Testing requirements of this specification.)

1.3.5 "Mixer"

The vendor in the supply chain that performs the actual mixing of the Rubber Compound utilized to produce product.

1.3.6 "Masterbatch"

A batch of compound that has been mixed to completely incorporate most of the compound ingredients, omitting the active chemicals that constitute the cure system. Typically for silicone compounds this includes catalysts and color pigments.

1.3.7 "Material Rework"

Minor adjustments made to the existing ingredient content levels of a compound recipe, while still remaining within the tolerance limits of the recipe, which may enhance physical property or processability performance, yet still maintain the original compound identity.

1.4 Safety - Hazardous Materials

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS 2279 Tolerances, Rubber Products

AMS 2810 Identification and Packaging, Elastomeric Products

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM D 297 Standard Test Methods for Rubber Products - Chemical Analysis

ASTM D 395 Standard Test Methods for Rubber Property - Compression Set

ASTM D 412 Standard Test Methods for Vulcanized Rubber and Thermoplastic Elastomers – Tension

- ASTM D 471 Standard Test Methods for Rubber Property - Effect of Liquids
- ASTM D 573 Standard Test Method for Rubber - Deterioration in an Air Oven
- ASTM D 624 Standard Test Method for Tear Strength of Conventional Vulcanized Rubber and Thermoplastic Elastomers
- ASTM D 2137 Standard Test Methods for Rubber Property - Brittleness Point of Flexible Polymers and Coated Fabrics
- ASTM D 2240 Standard Test Method for Rubber Property - Durometer Hardness
- ASTM D 3182 Standard Practice for Rubber – Materials, Equipment, and Procedures for Mixing Standard Compounds and Preparing Standard Vulcanized Sheets.

2.2 ASQ Publications

Available from American Society for Quality (ASQ), 600 North Plankinton Ave., Milwaukee, WI 53203, www.asq.org

ANSI/ASQ-Z1.4 Sampling Procedures and Tables for Inspection by Attribute

3. TECHNICAL REQUIREMENTS

3.1 Material

Shall be a compound based on a silicone rubber, suitably cured to produce a product meeting the requirements of 3.2.

3.1.1 Toxicological Formulations

The material shall have no adverse effects on the health of personnel when used for its intended purpose in accordance with manufacturer's instructions and with appropriate handling procedures.

3.1.2 Color

The color of the material shall be as specified on available design data or per customer contract. When no color is specified, the color shall be the natural color of the compound furnished.

3.2 Properties

The product shall conform to the requirements shown in Table 1; tests shall be performed in accordance with specified ASTM methods, insofar as practicable (also see 4.2.3):

TABLE 1 - REQUIREMENTS

Paragraph	Test	Requirement	Test Method
3.2.1	Original Properties		
3.2.1.1	Hardness, Durometer "A" or equivalent	50 ± 5	ASTM D 2240
3.2.1.2	Tensile Strength, minimum	1200 psi (8.27 MPa)	ASTM D 412, Die B or C
3.2.1.3	Elongation, minimum	500%	ASTM D 412, Die B or C
3.2.1.4	Tear Resistance, minimum	150 pounds force per inch (26.3 kN/m)	ASTM D 624, Die B
3.2.1.5	Specific Gravity	Preproduction Value ± 0.03	ASTM D 297
3.2.2	Petroleum Lubricating Oil Resistance (Immediate Deteriorated Properties)		ASTM D 471 Medium: ASTM Oil No. 1 Temperature: 347 °F ± 5 (175 °C ± 3) Time: 70 hours ± 0.5
3.2.2.1	Hardness Change, Durometer "A" or equivalent	-15 to +5	
3.2.2.2	Tensile Strength Change, maximum	-35%	
3.2.2.3	Elongation Change, maximum	-30%	
3.2.2.4	Volume Change	0 to +10%	
3.2.2.5	Decomposition	None	
3.2.2.6	Surface Tackiness	None	
3.2.3	Dry Heat Resistance		ASTM D 573 Temperature: 437 °F ± 5 (225 °C ± 3) Time: 22 hours ± 0.5
3.2.3.1	Hardness Change, Durometer "A" or equivalent	0 to +10	
3.2.3.2	Tensile Strength Change, maximum	-25%	
3.2.3.3	Elongation Change, maximum	-25%	
3.2.4	Compression Set		ASTM D 395, Method B Temperature: 347 °F ± 5 (175 °C ± 3) Time: 22 hours ± 0.5
3.2.4.1	Percent of Original Deflection, maximum	50	
3.2.5	Low-Temperature Resistance		
3.2.5.1	Brittleness Pass		ASTM D 2137, Method A Temperature: -103 °F ± 5 (-75 °C ± 3) Time: 3 minutes ± 0.3

3.3 Product Quality

The product, as received by purchaser, shall be uniform in quality and condition, smooth, as free from foreign materials as commercially practicable, and free from imperfections detrimental to usage of the product

3.4 Dimensions and Tolerances

Dimensions and tolerances shall be as specified in the parts standard, drawing, other design data, or purchase document, and shall conform to all applicable requirements of AMS2279.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The manufacturer of the product shall be responsible to assure that all required material testing and product inspection has been performed and that the data is available. Unless specified otherwise by contractual requirements, testing may be performed either at the product manufacture's own test facility, at the mixer, or at a suitable independent test facility. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Preproduction Testing

Preproduction testing shall consist of all of the Physical Property requirements listed in Table 1 and shall be performed prior to certification of materials to this Specification. Compound preproduction testing is valid for a period of three (3) years or until preproduction re-testing may be required (See 4.2.1.1). Objective evidence of this testing must be kept on file and available for review during the validity period.

4.2.1.1 Preproduction retesting shall be required if one of the following occurs:

- At the end of the current three year preproduction testing validity period – or;
- When a change in ingredients and/or processing requires re-approval as in 4.5.2 - or;
- Upon three consecutive failures of batch Acceptance Testing – or,
- When the Purchaser contractually requires that preproduction Testing be performed.

4.2.2 Acceptance Tests

The following requirements are acceptance tests and shall be performed on each lot of product (See 4.1) in accordance with Table 2.

TABLE 2 - ACCEPTANCE TEST REQUIREMENTS

Paragraph	Requirement Reference
Hardness, Original Properties	3.2.1.1
Tensile Strength, Original Properties	3.2.1.2
Elongation, Original Properties	3.2.1.3
Specific Gravity, Original Properties	3.2.1.5
Compression Set	3.2.4

4.2.3 Test Samples

4.2.3.1 For Qualification Testing, specimens shall be prepared from 6 inch (152 mm) square by 0.075 inch \pm 0.008 (1.90 mm \pm 0.20) thick molded test slabs per ASTM D3182 compounded for the same intended curing process as the end product.

4.2.3.2 For Acceptance Testing, sufficient material shall be taken at random from each lot of product to provide specimens to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three (See 4.2.3.3 below). If specimens cannot be prepared from the product, test specimens prepared from the same batch of material and in the same state of cure as the product shall be used.

4.2.3.2.1 When the product supplied is an extrusion of such shape that suitable test specimens cannot be cut from the product, a separate extruded flat strip test sample, 3.0 inches \pm 0.25 (76.2 mm \pm 6.4) by 0.075 inch \pm 0.008 (1.90 mm \pm 0.20) thick, produced from the same production batch of compound, in the same state of cure as the product being supplied, shall be used to prepare test specimens.

4.2.3.2.2 When the product is a molded item of such shape that suitable test specimens cannot be cut, a slab 6 inches (152 mm) square by 0.075 inch \pm 0.008 (1.90 mm \pm 0.20) thick per ASTM D3182, molded from the same batch of compound, in the same state of cure as the product being supplied, shall be used to prepare test specimens.

4.2.3.3 Specimen Test Values

All individual specimen test result values used to determine pass/fail criteria must be within acceptable limits as indicated in Table 1. Where Test Methods dictate that results be reported as Average or Median values, 'failed' values shall not be allowed in these calculations, (see 4.2.4).

4.2.4 Retesting and Rework

4.2.4.1 If any specimen fails to meet the pass/fail criteria as listed in Table 1, a retesting of three (3) additional specimens with acceptable results for each nonconforming specimen, shall be necessary for acceptance. The same material batch as was used for the failed test shall be used for retesting. Failure of any retest specimen shall be cause for rejection of the batch along with the rejection of any product that may have been produced from the batch. Results of all tests shall be reported. Records of all rejections and material rework shall be maintained.

4.2.4.1.1 Individual specimen failures that occur due to obvious flaws in the specimen itself or because of mechanical failure of the test equipment, may be disregarded with only a single retest specimen required for acceptance. All such occurrences must be recorded.

4.2.4.2 Any rejected batch that has undergone material rework because of failed Acceptance Testing must be retested to the full Acceptance Criteria, not just the failed test.

4.2.4.3 No batch may be reworked more than two (2) times.

4.3 Sampling

When a statistical sampling plan for product acceptance has been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan and the report of 4.6 shall state that such plan was used, otherwise sampling shall be in accordance with ANSI/ASQ-Z1.4, Single Sampling Plan, Inspection Level II, AQL 1.0, except that the acceptance number shall be zero (0).

4.4 Certification

Certification to this Material Specification shall only be permitted if all testing requirements specified in 4.2 have been met.

4.5 Approval

4.5.1 When the contract requires that sample product be submitted for approval by the purchaser before product for production use is supplied, results of tests on production product shall be essentially equivalent to those on the approved sample.

4.5.2 The vendor(s) shall use ingredients, manufacturing procedures, processes, and methods of inspection on production product which are essentially the same as those used on the qualified product. If necessary to make