



# AEROSPACE MATERIAL SPECIFICATION

## AMS 3348

Society of Automotive Engineers, Inc.  
TWO PENNSYLVANIA PLAZA, NEW YORK, N. Y. 10001

Issued 11-1-69  
Revised

### SILICONE RUBBER 1150 psi Tensile Strength, High Resiliency 25 - 35

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. **FORM:** Sheet, strip, tubing, molded shapes, extrusions, or as ordered.
3. **APPLICATION:** Primarily for rubber-like parts required to operate or seal at temperatures from -75 to +205 C (-103 to +401 F), compounded especially for high strength. Silicone rubber is resistant to deterioration by weathering and by high aniline point petroleum base oils and remains flexible over the temperature range noted. This material is not normally suitable for use in contact with gasoline or aromatic fuels and low aniline point petroleum base fluids due to excessive swelling.
4. **TECHNICAL REQUIREMENTS:**
  - 4.1 **General:**
    - 4.1.1 **Condition:** Unless otherwise specified, a suitably cured product shall be furnished.
    - 4.1.2 **Weathering:** When specified, the product shall have weather resistance acceptable to the purchaser as determined by a procedure agreed upon by purchaser and vendor.
    - 4.1.3 **Corrosion:** The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service. Discoloration of metal shall not be considered objectionable.
    - 4.2 **Properties:** The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with the issue of specified ASTM methods listed in the latest issue of AMS 2350, insofar as practicable. When the product supplied is of such shape that suitable test specimens cannot be cut from the product, a separate flat strip test sample shall be supplied upon request. This strip shall be prepared from 1 in.  $\pm$  1/16 OD by 0.075 in.  $\pm$  0.008 thick wall tubing which shall be mechanically split and flattened into a strip while being extruded and cured in the same manner as production material.
      - 4.2.1 **As Received:**

4.2.1.1 Hardness, Durometer "A" or equiv.	30 $\pm$ 5	ASTM D2240
4.2.1.2 Tensile Strength, psi, min	1150	ASTM D412, Die B or C
4.2.1.3 Elongation, %, min	550	ASTM D412, Die B or C
4.2.1.4 Impact Resilience, min	40	ASTM D2632
4.2.1.5 Tear Resistance, lb per in., min	140	ASTM D624, Die B
4.2.1.6 Specific Gravity	See Note 1	ASTM D297

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

4.2.2 <u>Lubricating Oil Resistance:</u> (Immediate Deteriorated Properties)		ASTM D471
4.2.2.1	Hardness Change, Durometer "A" or equiv.	Medium: ASTM Oil No. 1 Temperature: 175 C $\pm$ 3 (347 F $\pm$ 5.4) Time: 70 hr
4.2.2.2	Tensile Strength Change, %, max (based on area before immersion)	-10 to +5
4.2.2.3	Elongation Change, %, max	-60
4.2.2.4	Volume Change, %	-45
4.2.2.5	Decomposition	0 to +10
4.2.2.6	Surface Tackiness	None
4.2.3 <u>Dry Heat Resistance:</u>		ASTM D573
4.2.3.1	Hardness Change, Durometer "A" or equiv.	Temperature: 225 C $\pm$ 3 (437 F $\pm$ 5.4) Time: 24 hr
4.2.3.2	Tensile Strength Change, %, max	-10 to +5
4.2.3.3	Elongation Change, %, max	-30
4.2.3.4	Bend (flat)	-35 No cracking or checking
4.2.4 <u>Compression Set:</u>		ASTM D395, Method B
4.2.4.1	Per cent of original deflection, max	Temperature: 175 C $\pm$ 3 (347 F $\pm$ 5.4) Time: 22 hr
4.2.4.2	Per cent of original thickness, max	10
4.2.5 <u>Low Temperature Resistance:</u>		
4.2.5.1	Brittleness	Pass ASTM D746 Procedure B Temperature: -75 C $\pm$ 3 (-103 F $\pm$ 5.4) Time: 10 min.

Note 1. Value to be reported. Production material shall be within  $\pm$  0.05 of the value agreed upon by purchaser and vendor.

5. **QUALITY:** The product shall be uniform in quality and condition, clean, smooth, and free from chalky spots and foreign materials, and from imperfections detrimental to fabrication, appearance, or performance of parts.

6. **TOLERANCES:** Unless otherwise specified, the following tolerances apply:

6.1 **Sheet:**

Nominal Thickness Inches	Tolerance, Inch Plus and Minus
Up to 1/8, incl	1/64
Over 1/8 to 1/2, incl	1/32
Over 1/2	3/64

6.2 Tubing:

6.2.1	Nominal OD or ID (not both), Inches	Tolerance Plus and Minus	Ovality, % (See Note 2)
	Up to 1/2, incl	0.020 in.	10
	Over 1/2 to 1, incl	0.030 in.	15
	Over 1	4%	15

Note 2. Ovality applies to tubing ordered in straight lengths with wall thickness of 1/16 in. and over, and shall be computed from the difference between the minor and major axis diameter measurements, as a percentage of the nominal diameter.

6.2.2	Nominal Wall Thickness Inches	Tolerance Plus and Minus
	Up to 1/16, excl	0.005 in.
	1/16 and over	10%

7. REPORTS:

- 7.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report showing the results of tests to determine conformance to the requirements of this specification. This report shall include the purchase order number, material specification number, vendor's compound number, specific gravity value, form or part number, and quantity.
- 7.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of material, supplier's compound number, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

8. IDENTIFICATION: Unless otherwise specified, all material shall be identified in accordance with the latest issue of AMS 2810 except cure date is not required.

9. PACKAGING:

- 9.1 Packaging shall be accomplished in such a manner as to ensure that the product, during shipment and storage, will not be permanently distorted and will be protected against damage from exposure to weather or any normal hazard.
- 9.2 Each package shall be permanently and legibly marked in accordance with the latest issue of AMS 2810 except cure date is not required.

10. APPROVAL:

- 10.1 Sample material shall be approved by purchaser before material for production use is supplied, unless such approval be waived. Results of tests on production material shall be essentially equivalent to those on the approved sample.