



## 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

## 2.1.1 Aerospace Material Specifications:

AMS 2279	Tolerance, Rubber products
MAM 2279	Tolerances, Metric, Rubber Products
AMS 2810	Identification and Packaging, Elastomeric Products

## 2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187

ASTM D 297	Rubber Products - Chemical Analysis
ASTM D 395	Rubber Property - Compression Set
ASTM D 412	Rubber Properties in Tension
ASTM D 471	Rubber Property - Effect of Liquids
ASTM D 573	Rubber - Deterioration in an Air Oven
ASTM D 624	Rubber Property - Tear Resistance
ASTM D 797	Rubber Property - Young's Modulus at Normal and Subnormal Temperatures
ASTM D 2137	Rubber Property - Brittleness Point of Flexible Polymers and Coated Fabrics
ASTM D 2240	Rubber Property - Durometer Hardness

## 3. TECHNICAL REQUIREMENTS:

## 3.1 Material:

Shall be a compound based on a silicone (VMQ) rubber, suitably cured to produce a product meeting the requirements of 3.2.

## 3.2 Properties:

The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified ASTM methods, Insofar as practicable:

## 3.2.1 As Received:

3.2.1.1	Hardness, Durometer "A" or equivalent	70 ± 5	ASTM D 2240
3.2.1.2	Tensile Strength, minimum	800 psi (5.52 MPa)	ASTM D 412, Die B or C
3.2.1.3	Elongation, minimum	150%	ASTM D 412, Die B or C

AMS 3357G	SAE	AMS 3357G
3.2.1.4 Tensile Stress at 50% Elongation, minimum	200 psi (1.39 MPa)	ASTM D 412, Die B or C
3.2.1.5 Tear Strength, minimum	60 pounds force per inch (10.5 kN/m)	ASTM D 624, Die B
3.2.1.6 Specific Gravity Value $\pm$ 0.03	Preproduction	ASTM D 297
3.2.2 Petroleum Lubricating Oil Resistance: (Immediate Deteriorated Properties)		ASTM D 471 Medium: ASTM Oil No. 1 Temperature: 175°C $\pm$ 3 (347°F $\pm$ 5) Time: 70 hours $\pm$ 0.5
3.2.2.1 Hardness Change, Durometer "A" or equivalent	-10 to +5	
3.2.2.2 Tensile Strength Change, maximum	-20%	
3.2.2.3 Elongation Change, maximum	-15%	
3.2.2.4 Volume Change, maximum	0 to +15%	
3.2.2.5 Decomposition	None	
3.2.2.6 Surface Tackiness	None	
3.2.3 Dry Heat Resistance:		ASTM D 573 Temperature: 225°C $\pm$ 3 (437°F $\pm$ 5) Time: 22 hours $\pm$ 0.5
3.2.3.1 Hardness Change, maximum "A" or equivalent	-5 to +10	
3.2.3.2 Tensile Strength Change, maximum	-15%	
3.2.3.3 Elongation Change, maximum	-25%	
3.2.4 Compression Set:		ASTM D 395, Method B Temperature: 175°C $\pm$ 3 (347°F $\pm$ 5) Time: 22 hours $\pm$ 0.5
3.2.4.1 Percent of Original Deflection, maximum	35	
3.2.5 Low Temperature Resistance:		

3.2.5.1	Brittleness	Pass	ASTM D 2137, Method A Temperature: -65°C ± 3 (-85°F ± 0.5)
3.2.5.2	Young's Modulus, maximum (See 8.2)	10,000 (68.9 MPa)	ASTM D 797 Temperature: -50°C ± 3 (-58°F ± 5) Time: 5 hours ± 0.2

3.2.6 Weathering: The product shall have weather resistance acceptable to purchaser, determined by a procedure agreed upon by purchaser and vendor.

3.2.7 Corrosion: The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service, determined by a procedure agreed upon by purchaser and vendor. Discoloration of metal shall not be considered objectionable.

### 3.3 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, smooth, as free from foreign materials as commercially practicable, and free from imperfections detrimental to usage of the product.

### 3.4 Tolerances:

Shall conform to AMS 2279 or MAM 2279.

## 4. QUALITY ASSURANCE PROVISIONS:

### 4.1 Responsibility for Inspection:

φ

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

#### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for the following requirements are acceptance tests and shall be performed on each lot:

Requirement	Paragraph Reference
Hardness, as received	3.2.1.1
Tensile Strength, as received	3.2.1.2
Elongation, as received	3.2.1.3
Specific Gravity	3.2.1.6
Petroleum Lubricating Oil Resistance	3.2.2
Compression Set	3.2.4

4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of the product to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

#### 4.3 Sampling and Testing:

φ

Shall be as follows:

4.3.1 For Acceptance Tests: Sufficient product shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure if not specified therein, not less than three.

4.3.1.1 If specimens cannot be prepared from the product, ASTM test specimens prepared from the same batch and state of cure shall be used. When the product supplied is an extrusion of such shape that suitable test specimens cannot be cut from the product, a separate flat strip test sample from the same production lot shall be supplied upon request. This strip shall be prepared from tubing 1.000 inch  $\pm$  0.063 (25.40 mm  $\pm$  1.60) in OD by 0.075 inch  $\pm$  0.008 (1.90 mm  $\pm$  0.20) in wall thickness, mechanically slit and flattened into a strip while being extruded, and cured in the same manner as production product. When the product is a molded shape from which test specimens cannot be cut, a slab 6 inches (152 mm) square by 0.075 inch  $\pm$  0.008 (1.90 mm  $\pm$  0.020) thick molded from the same batch of compound shall be supplied upon request.

4.3.1.2 A lot shall be all product from the same batch of compound processed in one continuous run and presented for vendor's inspection at one time. An inspection lot shall not exceed 500 pounds (227 kg) and may be packaged in smaller quantities and delivered under the basic lot approval provided lot identification is maintained.