

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc
29 West 39th Street
New York City

AMS 3410 D

Issued 3-13-40

Revised 2-1-56

FLUX, SILVER BRAZING

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. FORM: Paste containing not more than 30% water by weight.
3. APPLICATION: Primarily for silver brazing nonferrous (excluding aluminum- and magnesium-base alloys) and ferrous metals (including austenitic steels) at temperatures between 1150 F and 1600 F.
4. TECHNICAL REQUIREMENTS:
 - 4.1 General:
 - 4.1.1 Flux shall be an intimately blended mixture of uniform consistency. It shall not separate in container to such an extent that it cannot be restored to uniform consistency by stirring.
 - 4.1.2 Flux, diluted with water as required, shall have acceptable fusibility and acceptable application and fluxing characteristics, and shall produce satisfactory brazed joints of any type on copper- and nickel-base alloys and all types of steels, including corrosion resistant types, when used in conjunction with silver brazing alloys.
 - 4.2 Properties:
 - 4.2.1 Flux shall withstand heating in a suitable container to 1600 F and holding at heat for 30 min. without appreciable change in physical characteristics; loss of water will not be considered as change in characteristics. On heating, flux shall fuse at 1150 F or lower; on cooling from 1600 F, flux shall remain in the liquid state until temperature drops to 1150 F or lower.
 - 4.2.2 Flux, when placed on a 40-mesh sieve and worked lightly with a brush, shall pass completely through the sieve. If the flux has partially coagulated in the container, the flux may, before conducting the test, be warmed over a water bath until it has returned to its normal consistency.
 - 4.2.3 Flux shall not produce, during use, a flame or smoke of sufficient intensity to obscure the work.
 - 4.2.4 Flux shall be soluble in water at 175 F or lower after being subjected to brazing operations.
5. QUALITY: Flux shall be free from all substances which might affect its serviceability.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."