

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 3410H

Issued 13 MAR 1940
Revised 1 OCT 1992
Superseding AMS 3410G

Submitted for recognition as an American National Standard

FLUX, SILVER BRAZING

1. SCOPE:

1.1 Form:

This specification covers a silver-brazing flux in the form of a paste which contains not more than 35% water by weight.

1.2 Application:

This flux has been used typically for silver brazing nonferrous metals, excluding aluminum, magnesium, and zinc alloys, and ferrous metals including austenitic steels, at temperatures in the range 1150 to 1600 °F (621 to 871 °C), but usage is not limited to such applications.

1.3 Safety - Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2825 Material Safety Data Sheets

AMS 4769 Silver Alloy Brazing Filler Metal, 45Ag - 24Cd - 16Zn - 15Cu,
1125 to 1145 °F (607 to 618 °C) Solidus-Liquidus Range

AMS 4770 Silver Alloy Brazing Filler Metal, 50Ag - 18Cd - 16.5Zn - 15.5Cu,
1160 to 1175 °F (627 to 635 °C) Solidus-Liquidus Range

AMS 5510 Steel, Corrosion and Heat Resistant, Sheet, Strip, and Plate, 18Cr -
10.5Ni - 0.40Ti (SAE 30321), Solution Heat Treated

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM E 11 Wire-Cloth Sieves for Testing Purposes

2.3 U.S. Government Publications:

Available from Standardization Documents Order Desk, Building 4D, 700 Robbins
Avenue, Philadelphia, PA 19111-5094.

MIL-STD-2073-1 DOD Materiel, Procedures for Development and Application of
Packaging Requirements

3. TECHNICAL REQUIREMENTS:**3.1 Material:**

The flux shall be a blended mixture of uniform consistency. It shall not
separate in the container to an extent that it cannot be restored to uniform
consistency by stirring.

3.1.1 The flux, diluted with water as required, shall have acceptable fusibility
and acceptable application and fluxing characteristics, and shall produce
satisfactory brazed joints of any type on copper alloys, nickel alloys, and
all types of steel, including corrosion-resistant alloys when used in
conjunction with silver brazing filler metal.

3.2 Properties:

The flux shall conform to the following requirements:

3.2.1 During heating to 1600 °F (871 °C), flux shall fuse at 1150 °F (621 °C) or
(R) lower; when cooled from 1600 °F (871 °C), flux shall remain in the liquid
state until temperature drops to 1150 °F (621 °C) or lower.

3.2.2 Flux, placed on a U.S. Standard 40-mesh (425 μm) sieve conforming to
ASTM E 11 and worked lightly with a brush, shall pass completely through
the sieve. If the flux has partially coagulated in the container, the flux
may, before conducting the test, be warmed over a water bath until it has
returned to its normal consistency.

AMS 3410H

SAE

AMS 3410H

- 3.2.3 Flux shall not produce, during use, a flame or smoke of sufficient intensity to obscure the work.
- 3.2.4 Flux shall be soluble in water at 175 °F (79 °C) or lower after being subjected to normal brazing operations.
- 3.2.5 Flux shall have a shelf life of not less than six months; not more than thorough mixing shall be required to restore flux for use during that time.
- 3.2.6 When applied to AMS 5510 corrosion-resistant steel, using AMS 4769 or (R) AMS 4770 filler metal and heated in air to 1300 to 1350 °F (704 to 732°C), flux shall cause braze filler metal to flow with no evidence of balling or de-wetting.
- 3.3 Quality:
(R) Flux, as received by purchaser, shall be free from contaminants and from foreign materials detrimental to the usage of the flux.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection:
(R) The vendor of flux shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the flux conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests for all technical requirements, except shelf life (R) (3.2.5), are acceptance tests and shall be performed on each batch.
- 4.2.2 Periodic Tests: Tests for shelf life (3.2.5) are periodic tests and shall (R) be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.
- 4.3 Sampling and Testing:
(R) At least one randomly selected sample of flux from each batch. A batch shall be all flux in an identifiable quantity processed at one time and presented for vendor's inspection at one time.
- 4.4 Reports:
The vendor of flux shall furnish with each shipment a report stating that the flux conforms to the technical requirements. This report shall include the purchase order number, batch number, AMS 3410H, date of manufacture, and quantity.

AMS 3410H

SAE

AMS 3410H

4.4.1 (R) A material safety data sheet conforming to AMS 2825, or equivalent, shall be supplied to each purchaser prior to, or concurrent with, the report of preproduction test results or, if preproduction testing be waived by purchaser, concurrent with the first shipment of flux for production use. Each request for modification of flux formulation shall be accompanied by a revised data sheet for the proposed formulation.

4.5 Resampling and Retesting:
(R)

If any sample used in the above tests fails to meet the specified requirements, disposition of the flux may be based on the results of testing three additional samples for each original nonconforming sample. Failure of any retest sample to meet the specified requirements shall be cause for rejection of the flux represented. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification:

5.1.1 (R) Flux shall be assigned a name or number representing a specific set of materials and manufacturing procedures. Any change in raw materials or manufacturing methods shall require that the name or number be changed.

5.1.2 Each package of flux shall be permanently and legibly marked with not less than the following information:

FLUX, SILVER BRAZING
AMS 3410H
PURCHASE ORDER NUMBER _____
MANUFACTURER'S NAME _____
MANUFACTURER'S DESIGNATION (See 5.1.1) _____
BATCH NUMBER _____
DATE OF MANUFACTURE _____
DIRECTIONS FOR MIXING AND APPLICATION _____
WEIGHT OF CONTENTS _____

5.2 Packaging:

5.2.1 Flux shall be supplied in 8 ounce (227 g), 16 ounce (454 g), or 5 pound (2.3 kg) containers, unless otherwise ordered.

5.2.2 (R) Containers of flux shall be packaged to ensure that the flux, during shipment and storage, will be protected against damage from exposure to moisture, weather, or any other normal hazard.

5.2.3 (R) Packages of flux shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the flux to ensure carrier acceptance and safe delivery.

5.2.4 (R) For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-2073-1, Commercial Level, unless Level A is specified in the request for procurement.