

COATING, ABRASION RESISTANT
For Polycarbonate Parts

1. SCOPE:

1.1 Purpose: This specification covers the optical and abrasion resistance requirements for coatings applied to polycarbonate plastic surfaces.

1.2 Application: Primarily for improving abrasion resistance of flying helmet visors and other transparent polycarbonate plastic parts.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods
AMS 3611 - Plastic Sheet, Polycarbonate

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D673 - Mar Resistance of Plastics
ASTM D1003 - Haze and Luminous Transmittance of Transparent Plastics
ASTM D1044 - Resistance of Transparent Plastics to Abrasion
ASTM D3359 - Measuring Adhesion by Tape Test
ASTM G23 - Operating Light- and Water-Exposure Apparatus (Carbon-Arc Type) for Exposure of Nonmetallic Materials

REAFFIRMED

10/91

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Material: Shall be an optically clear finish, compatible with polycarbonate resin which, when applied, meets the requirements of 3.2.

3.2 Properties: The applied coating shall conform to the following requirements; tests shall be performed on coated parts, where practical, or on witness specimens (See 4.5.1) coated with the parts and in accordance with specified test methods insofar as practicable:

3.2.1 Abrasion Resistance: The increase in haze shall not exceed 6% and the decrease in luminous transmittance shall not exceed 4%, measured in accordance with ASTM D1003, Method A, on specimens abraded as in 4.5.2.

3.2.2 Coating Adhesion: The coating, tested in accordance with ASTM D3359, Method B, shall not exhibit loss of adhesion from the as applied value after environmental exposure as in 4.5.3 and 4.5.4.

3.2.3 Weather Resistance: Coated specimens shall not exhibit yellowing or crazing determined in accordance with 4.5.4.

3.3 Quality: The coating shall be smooth, uniform, and free from pin holes, sags, runs, bubbles, heavy edges, handling defects, scratches, foreign materials, and other imperfections detrimental to usage of the coating.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the coated parts shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.6. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the coating conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each lot.

4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the initial shipment of a coated part to a purchaser, when a change in material or processing, or both, requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.3 Sampling: Shall be as follows:

4.3.1 For Acceptance Tests: Sufficient coated parts or witness specimens as in 4.5.1 shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

4.3.1.1 A lot shall be all parts and witness specimens coated in a continuous operation using the same batch of coating material and presented for vendor's inspection at one time. An inspection lot shall not exceed 200 parts.

4.3.1.2 When a statistical sampling plan and acceptance quality level (AQL) have been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.6 shall state that such plan was used.

4.3.2 For Preproduction Tests: As agreed upon by purchaser and vendor.

4.4 Approval:

4.4.1 Sample coated parts shall be approved by purchaser before parts for production use are supplied unless such approval be waived by purchaser. Results of tests on production parts shall be essentially equivalent to those on the approved sample parts.

4.4.2 Vendor shall use coating material, manufacturing procedures, processes, and methods of inspection on production parts which are essentially the same as those used on the approved sample parts. If necessary to make any change in coating material or method of application, vendor shall submit for reapproval a statement of the proposed changes in material or processing, or both, and, when requested, sample coated parts, witness specimens, or both. Production parts coated by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Test Methods: Shall be as follows:

4.5.1 Witness Specimens: Shall be prepared in suitable quantity and size from AMS 3611 polycarbonate plastic sheet, and shall be coated with the parts they represent.

AMS 3510

4.5.2 Abrasion Resistance: Measure and record the haze and luminous transmittance of coated specimens in accordance with ASTM D1003, Method A, before and after abrasion testing. Specimens shall be abraded in accordance with ASTM D1044, except that the test shall be run for only 50 cycles.

4.5.3 Humidity Test:

4.5.3.1 The chamber and accessories shall be constructed and arranged in such a manner as to avoid condensate dripping on the test specimens. The chamber shall be trap-vented to the atmosphere to prevent the buildup of total pressure. Relative humidity shall be determined by the dry bulb-wet bulb thermometer comparison method or an equivalent method. When readout charts are used, they shall be capable of being read with a resolution within 0.6°C (1°F). When the wet bulb control method is used, the wet bulb and tank shall be cleaned and a new wick installed at least every 30 days. The air velocity flowing across the wet bulb shall be not less than 900 ft per min. (4.6 m/s). Provisions shall be made for controlling the flow of air throughout the internal chamber test space where the velocity of air shall not exceed 150 ft per min. (0.75 m/s). Steam or distilled, demineralized, or deionized water having a pH value between 6.0 and 7.2 at $23^{\circ}\text{C} \pm 1$ ($73^{\circ}\text{F} \pm 2$) shall be used to obtain the specified humidity.

4.5.3.2 Prepare coated polycarbonate specimens or use actual parts if flat surface areas are appropriate for subsequent required testing. After completion of required drying or baking operations, store the coated test specimens at room temperature for $24 \text{ hr} \pm 0.5$. Suspend the specimens in the humidity chamber, which is at ambient temperature, in a manner which ensures that each test specimen hangs free, not touching the chamber surfaces or other specimens. Gradually raise the temperature in the chamber to $65^{\circ}\text{C} \pm 1$ ($150^{\circ}\text{F} \pm 2$) and to a relative humidity of $95\% \pm 4$ over a period of $2 \text{ hr} \pm 0.25$. Maintain these conditions of temperature and relative humidity for $6 \text{ hr} \pm 0.5$. Reduce the temperature in the chamber to $30^{\circ}\text{C} \pm 1$ ($86^{\circ}\text{F} \pm 2$) over a period of 16 hr, maintaining the relative humidity at not less than 85%. Repeat the complete cycle 5 times over a period of not less than 120 hours. Remove the test specimens from the chamber at the end of the last cycle, blow dry with clean, filtered air, and perform the adhesion test within 45 minutes.

4.5.4 Weather Resistance: Test in accordance with ASTM G23, Type E, Method 1, for not less than 100 hours.

4.6 Reports: The processing vendor shall furnish with each shipment copies of a report stating that the parts have been processed and tested in accordance with the requirements of this specification and that they conform to the technical requirements. This report shall include the purchase order number, AMS 3510, lot number, part number, and quantity.