

FOAM, POLYETHER URETHANE (EU) ELASTOMER, SHOCK ABSORBING  
5 lb/cu ft (72 kg/m<sup>3</sup>) Density

1. **SCOPE:** This specification covers a chemically or mechanically expanded polyether urethane (EU) elastomeric foam material in the form of ready-to-use sheet.
- 1.2 **Application:** Primarily for use in applications where shock absorbing characteristics and cushioning are required and where flammability does not preclude its use.
2. **APPLICABLE DOCUMENTS:** See AMS 3568.
3. **TECHNICAL REQUIREMENTS:**
  - 3.1 **Basic Specification:** The complete requirements for procuring the foam sheet described herein shall consist of this document and the latest issue of the basic specification, AMS 3568.
  - 3.2 **Material:** Shall be an elastomeric polyether urethane (EU) foam as specified in AMS 3568 formed by open or closed cells, with natural (cream) color.
  - 3.3 **Properties:** The foam sheet shall conform to the following requirements, determined in accordance with test methods listed in AMS 3568:

3.3.1 Density	3.0 - 6.0 lb per cu ft (48 - 96 kg/m <sup>3</sup> )
3.3.2 Compression Deflection for 20% Compression, max	5 psi (0.345 MPa)
3.3.3 Compression Deflection for 40% Compression, max	8 psi (0.55 MPa)
3.3.4 Tensile Strength, min	25 psi (0.170 MPa)
3.3.5 Elongation, min	60.0%

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."